

10/567728

IAP5 Rec'd PCT/PTO 31 JAN 2006
DESCRIPTION

BEST AVAILABLE COPY

THREE-DIMENSIONAL TISSUE STRUCTURE

5

TECHNICAL FIELD

The present invention relates to a three-dimensional structure applicable to the heart, and more particularly, to a three-dimensional structure applicable to the heart, which comprises cells derived from parts of an adult other than the heart. The present invention also relates to a method for producing such a three-dimensional structure.

15

BACKGROUND ART

Myocardial infarct is an irreversible injury (Ho K.K., Anderson K.M., Kannel W.B., Grossman W., Levy D., Circulation, 1993; 88: 107-115). Ischemic heart diseases are the cause of death responsible for 50% of all cardiovascular system-related deaths and the major cause of congestive heart failure. The 1-year mortality observed in patients who are diagnosed as having congestive heart failure and eventually die from chronic heart disease is 20% (American Heart Association, Dallas, Tex: American Heart Association; 2001). Most therapies currently available to clinicians can significantly improve the prognosis of patients suffering from acute myocardial infarct. Angioplasty and thrombolytic agents may remove the cause of the acute myocardial infarct, though the period of time from the onset of occlusion to reperfusion determines the degree of irreversible myocardial injury (Ryan T.J., Antman E.M., Brooks N.H., Califf R.M., Hillis L.D., Hiratzka L.F., Rapaport E., Riegel B., Russell R.O., Smith E.E. III, Weaver

W.D., Gibbons R.J., Alpert J.S., Eagle K.A., Gardner T.J.,
Garson A. Jr., Gregoratos G., Ryan T.J., Smith S.C. Jr.,
J. Am. Coll. Cardiol., 1999; 34: 890-911). No clinically
used pharmaceutical agent or treatment has an efficacy on
5 the replacement of myocardial scars with functional
contraction tissue. There is a demand for a novel therapy
for regenerating normal cardiomyocytes.

Cardiomyoplasty has been proposed as a surgical
10 method for improving the function of the left ventricle (LV)
of a patient suffering from congestive heart failure, however,
the effect thereof on the cardiac function remains unclear
(Corin W.J., George D.T., Sink J.D. et al., J. Thorac.
Cardiovasc. Surg., 1992, 104:1662-1671; Kratz J.M., Johnson
15 W.S., Mukherjee R. et al., J. Thorac. Cardiovasc. Surg.,
1994, 107:868-878; Carpentier A., Chachques J.C., Lancet,
1985, 8840:1267; and Hagege A.A., Desnos M., Chachques J.C.
et al., Preliminary report: follow-up after dynamic
cardiomyoplasty, Lancet, 1990, 335:1122-1124). Recently,
20 implantation of a biologically modified heart graft, in which
a biodegradable scaffold is used, has been proposed as another
novel approach. However, the graft hardly attaches to the
myocardium, resulting in the least possible benefit for the
improvement of the cardiac function (Leor J., Etzion S.A.,
25 Dar A. et al., Circulation, 2000; 102 [suppl. III]
III-56-III-61; and Li R.K., Jia Z.Q., Weisel R.D. et al.,
Circulation, 1999; 100 [suppl II]: II-63-II-69). The
histological and electrical integration of biologically
modified heart tissue and a recipient heart may be crucial
30 for the regeneration of impaired myocardium.

The recent development of tissue engineering is
expected to make possible the production of a functional

heart tissue using a novel technique, in which cell sheets are three-dimensionally layered without any biodegradable substitute for extracellular matrices (ECM) (Okano T., Yamada N., Sakai H., Sakurai Y., J. Biomed. Mater. Res., 1993; 27:1243-1251). In this novel technique, both intracellular adhesion and adhesion proteins within a confluent cultured cell monolayer are fully maintained. Endogenous ECM supporting a cell sheet whose base portion has been collected by a collecting method (Kushida A., Yamato M., Konno C., Kikuchi A., Sakurai Y., Okano T., J. Biomed. Mater. Res., 45:355-362, 1999) plays an important role as an adhesion factor for the integration to the recipient heart. Further, the cardiomyocyte sheet is a pulsating 3-D heart construct which transmits electricity (Shimizu T., Yamato M., Akutsu T. et al., Circ. Res., Feb 22, 2002, 90(3):e40). However, it is unknown whether or not cardiomyocyte sheets retain their functions after *in vivo* implantation.

The recent progress in tissue engineering has the potential of providing an implantable functional tissue comprising various cells and an extracellular matrix.

Implantation of organs (e.g., heart, blood vessel, etc.) using an exogenous tissue is mainly hindered by immunological rejections. Changes occurring in allografts and xenografts were first described 90 or more years ago (Carrel A., 1907, J. Exp. Med. 9:226-228; Carrel A., 1912, J. Exp. Med. 9:389-392; Calne R.Y., 1970, Transplant Proc. 2:550; and Auchincloss 1988, Transplantation 46:1). Rejection to artery grafts pathologically leads either to enlargement (up to rupture) or occlusion of the grafts. The former is caused by decomposition of extracellular matrices, while the latter is caused by proliferation of cells in a

blood vessel (Uretsky B.F., Mulari S., Reddy S., et al., 1987, Circulation 76:827-834). Such grafts are often made from non-biological materials which lead to adverse effects.

5 Recently, cell implantation has attracted attention as a therapy utilizing biological material. However, the implantation of human myoblasts into the infarcted heart has the following drawbacks: 1. damage and loss of
10 implantation cells; 2. tissue injury of the recipient heart during implantation; 3. tissue supply efficiency to the recipient heart; 4. occurrence of arrhythmia; 5. difficulty in treating the entirety of the infarcted site; and the like. Therefore, cell implantation cannot be said to be very successful.

15 Myocardium-derived sheets have been developed. Typically, autologous myocardium is required for the myocardium-derived sheet in view of immune reactions. Therefore, the applications of the sheet are limited.

20 Accordingly, there is a keen demand for a prosthetic tissue, a three-dimensional structure, or a sheet capable of withstanding implantation operations, being used in actual operations, and being produced by culture.

25 DISCLOSURE OF THE INVENTION

 An object of the present invention is to provide a prosthetic tissue or sheet capable of withstanding
30 implantation operations, being used in actual operations, and being produced by culture. Another object of the present invention is to provide a novel therapy, which is an alternative to cell therapy. The present invention is

particularly directed to production of a prosthetic tissue comprising cells derived from parts other than the myocardium, which can withstand implantation operations.

5 The above-described objects of the present invention were achieved by providing a three-dimensional structure comprising cells derived from parts other than the myocardium. The objects of the present invention were partially achieved by finding that by culturing cells under specific culture
10 conditions, the cells are unexpectedly organized into a tissue, and the resultant prosthetic tissue is capable of being detached from culture dishes.

 The present invention was also achieved by
15 unexpectedly finding that a three-dimensional structure comprising cells derived from parts other than the myocardium can function in a manner similar to that of the myocardium.

 Therefore, the present invention provides the
20 following.

(Non-cardiac sheet/three-dimensional structure)

(1) A three-dimensional structure applicable to
25 heart, comprising a cell derived from a part other than myocardium of an adult.

(2) A structure according to item 1, wherein the cell
is a stem cell or a differentiated cell.

30 (3) A structure according to item 1, wherein the cell is a mesenchymal cell.

- 6 -

(4) A structure according to item 1, wherein the cell is derived from a myoblast.

5 (5) A structure according to item 4, wherein the myoblast is a skeletal myoblast.

(6) A structure according to item 1, wherein the cell is a fibroblast.

10 (7) A structure according to item 1, wherein the cell is a synovial cell.

(8) A structure according to item 1, wherein the cell is derived from a stem cell.

15

(9) A structure according to item 1, wherein the cell is derived from a subject, the structure being applied to the subject.

20 (10) A structure according to item 1, wherein the cell is not derived from a subject, the structure being applied to the subject.

25 (11) A structure according to item 1, wherein the structure expresses at least one non-adult heart marker selected from the group consisting of myosin heavy chain IIa, myosin heavy chain IIb, myosin heavy chain IIc(IIx), CD56, MyoD, Myf5, and myogenin.

30 (12) A structure according to item 11, wherein an expression level of the non-adult heart marker in the structure is at least 50% of an expression level of the non-adult heart marker in skeletal myoblasts.

(13) A structure according to item 1, wherein the three-dimensional structure expresses all of myosin heavy chain IIa, myosin heavy chain IIb, myosin heavy chain IId(IIx),
5 CD56, MyoD, Myf5, and myogenin.

(14) A structure according to item 13, wherein an expression level of each of myosin heavy chain IIa, myosin heavy chain IIb, myosin heavy chain IId(IIx), CD56, MyoD,
10 Myf5, and myogenin in the structure is at least about 50% of an expression level thereof in skeletal myoblasts.

(15) A structure according to item 13, wherein an expression level of each of myosin heavy chain IIa, myosin heavy chain IIb, myosin heavy chain IId(IIx), CD56, MyoD,
15 Myf5, and myogenin in the structure is at least about 100% of an expression level thereof in skeletal myoblasts.

(16) A structure according to item 1, wherein the
20 cell derived from a part other than myocardium is a cell not derived from heart.

(17) A structure according to item 1, wherein the applicability to heart includes applicability to myocardium.
25

(18) A structure according to item 1, comprising a monolayer cell sheet.

(19) A structure according to item 1, comprising a
30 multilayer cell sheet.

(20) A structure according to item 19, wherein the multilayer cell sheet has biological connection.

(21) A structure according to item 20, wherein the biological connection is selected from the group consisting of connection via extracellular matrix, electrical connection, and connection without scaffold.

(22) A medicament, comprising a three-dimensional structure according to any one of items 1 to 21.

(23) A medicament according to item 22, wherein the heart has a disease or disorder selected from the group consisting of heart failure, ischemic heart disease, myocardial infarct, cardiomyopathy, myocarditis, hypertrophic cardiomyopathy, dilated phase hypertrophic cardiomyopathy, and dilated cardiomyopathy.

(24) A method for producing a three-dimensional structure applicable to heart comprising a cell derived from a part other than myocardium of an adult, the method comprising the steps of:

a) culturing the cell derived from the part other than myocardium of an adult on a cell culture support grafted with a temperature responsive macromolecule having an upper limit critical solution temperature or lower limit critical solution temperature to water of from 0°C to 80°C;

b) setting a culture medium temperature to the upper limit critical solution temperature or more or the lower limit critical solution temperature or less; and

c) detaching the cultured cell as a three-dimensional structure.

(25) A method according to item 24, wherein a treatment using a protein degrading enzyme is not performed

in or before the detaching step.

(26) A method according to item 24, wherein the
temperature responsive macromolecule is
5 poly(N-isopropylacrylamide).

Hereinafter, the present invention will be described
by way of preferred embodiments. It will be understood by
those skilled in the art that the embodiments of the present
10 invention can be appropriately made or carried out based
on the description of the present specification and commonly
used techniques well known in the art. The function and
effect of the present invention can be easily recognized
by those skilled in the art.

15

The present invention provides an implantable
prosthetic tissue. This tissue has a large size, which cannot
be achieved by conventional techniques, and has an excellent
strength. Thereby, it is made possible to treat sites which
20 cannot be conventionally accessible to implantation
treatment using conventional prosthetic materials. The
present invention makes it possible to provide a prosthetic
tissue or three-dimensional structure made of not only
myocardial tissue but also parts other than the myocardium.
25 Therefore, parts other than autologous myocardium can be
used as material to conduct implantation therapies.

BRIEF DESCRIPTION OF THE DRAWINGS

30

Figure 1A shows an example in which a prosthetic
tissue of the present invention is produced using a
temperature responsive polymer.

Figure 1B shows another example in which a prosthetic tissue of the present invention is produced using a temperature responsive polymer.

5 Figure 2 shows an example in which a therapy using a prosthetic tissue of the present invention is compared with a cell therapy.

10 Figure 3 shows an exemplary therapy scheme using a prosthetic tissue of the present invention.

15 Figure 4 shows a limit of myocardial regenerative therapies using cell implantation. As shown in the right portion, an injured site is not completely healed by cells in cell implantation.

 Figure 5 shows a limit of tissue implantation using a scaffold.

20 Figure 6 shows an example of implantation of a prosthetic tissue of the present invention into an infarcted heart.

25 Figure 7 shows a state of a prosthetic tissue of the present invention after implantation. The left portion shows the tissue 2 weeks after implantation, while the right portion shows the tissue 8 weeks after implantation. HE staining is shown over the left panel (left: $\times 100$; right: $\times 200$). Factor VIII staining is shown below the left panel, 30 while Connexin 43 staining is shown to the right. The right panel shows HE staining (upper: $\times 40$; lower: $\times 100$).

 Figure 8 is an ultrasound echogram showing an example

of evaluation of cardiac function ameliorated by a prosthetic tissue of the present invention. The left portion shows a control, while the right portion shows a cardiomyocyte sheet.

5 Figure 9 shows an example of evaluation of cardiac function ameliorated by a prosthetic tissue of the present invention. In the figure, the ejection fraction (EF), the fractional shortening (FS), and the endo-systolic area (ESA) are shown. Squares indicate the cardiomyocyte sheet, while
10 triangles indicate the control. A left panel photograph is an ultrasound echo photograph (upper: control; lower: cardiomyocyte sheet).

 Figure 10 shows a technique for
15 electrophysiological evaluation of a prosthetic tissue of the present invention. The right portion schematically shows changes in electric potential, while the right portion shows numerical values of threshold. The right portion shows a control, and a fibroblast sheet of the present invention
20 and a cardiomyocyte sheet of the present invention.

 Figure 11 shows electrophysiological evaluation of a prosthetic tissue of the present invention. The upper left portion shows a normal heart, the lower left portion shows
25 an infarct model, and the lower right portion shows a therapy using a cardiomyocyte sheet.

 Figure 12 shows an example of procedures for isolating and culturing myoblasts in a method according to
30 the present invention.

 Figure 13 shows an example of prosthetic tissue culture containing myoblasts in a method according to the

present invention.

Figure 14 shows an exemplary experimental scheme using a prosthetic myoblast tissue of the present invention.

5

Figure 15 shows photographs indicating a myoblast prosthetic tissue of the present invention 4 weeks after implantation ($\times 10$, $\times 200$, and $\times 1000$).

10

Figure 16 shows an exemplary implantation operation using a prosthetic myoblast tissue of the present invention.

Figure 17 shows an exemplary implantation of a prosthetic myoblast tissue of the present invention (histological staining). The upper portion shows the prosthetic tissue, cell injection, and control from the right ($\times 10$). The lower portion shows a photograph ($\times 400$) for each.

15

Figure 18 shows an ultrasound echogram of implantation of a prosthetic myoblast tissue of the present invention (upper) and an exemplary result of M-mode analysis (lower). The left portion shows an, while the right portion shows the infarcted heart after treatment.

20

Figure 19 shows exemplary results of a test for the cardiac function of a prosthetic myoblast tissue of the present invention after implantation. The ejection fraction (EF), fractional shortening (FS), endo-systolic area (ESA), and E-Wave are shown. Diamonds indicate a prosthetic myoblast tissue, squares indicate myoblast injection, and triangles indicate a control.

25

30

Figure 20 shows an example of comparison in wall

pressure between a prosthetic myoblast tissue of the present invention and myoblast. The results of photographs (upper left: prosthetic tissue; upper right: cell injection; lower right: control) are summarized to a lower left graph.

5

Figure 21 shows comparison between a prosthetic myoblast tissue of the present invention and a control visualized by desmin staining, Factor VIII staining, and GFP expression. The upper portion shows desmin staining (left: prosthetic tissue), GFP expression (right: prosthetic tissue), and GFP expression (middle: control). The lower portion shows Factor VIII staining (prosthetic tissue, cell injection, and control from the right).

10

Figures 22A to 22F show electrophysiological connection when a prosthetic tissue of the present invention is used. Figures 22A to 22C show a control, while Figures 22D to 22F show a prosthetic myoblast tissue. In the prosthetic myoblast tissue, electrophysiological connection is observed.

15

20

Figures 23A to 23C show GFP expression when a prosthetic tissue of the present invention is used. GFP expression is shown by motion picture display. Figures 23A to 23C provide representative frames as still pictures.

25

Figures 24A to 24C show an exemplary ultrasound echography temporal analysis of treatment using a prosthetic tissue of the present invention. Results of ultrasound echography for an infarcted heart treated according to the present invention are shown by motion picture display. Figures 24A to 24C provide representative frames as still pictures.

30

Figures 25A to 25C show an exemplary ultrasound echography temporal analysis of treatment using a prosthetic tissue of the present invention. Figure 25A shows a control, while Figure 25B shows use of a prosthetic tissue of the present invention. Results of ultrasound echography are shown by motion picture display. Figures 25A to 25C provide representative frames as still pictures. The left portion shows an infarcted heart control, while the right portion shows a result of a myoblast sheet of the present invention.

Figure 26A shows an exemplary ultrasound echography analysis of treatment using a prosthetic tissue of the present invention. Figure 26A is a photograph showing the same sample as in Figures 25A to 25C at a different time point. Results of ultrasound echography are shown by motion picture display. Figure 26A provides representative frames as still pictures. The left portion shows an infarcted heart control, while the right portion shows a result of a myoblast sheet of the present invention.

Figure 26B shows an exemplary ultrasound echography analysis of treatment using a prosthetic tissue of the present invention. Figure 26B is a photograph showing the same sample as in Figures 25A to 25C at a different time point. Results of ultrasound echography are shown by motion picture display. Figure 26B provides representative frames as still pictures. The left portion shows an infarcted heart control, while the right portion shows a result of a myoblast sheet of the present invention.

Figure 26C shows an exemplary ultrasound echography analysis of treatment using a prosthetic tissue of the present

invention. Figure 26C is a photograph showing the same sample as in Figures 25A to 25C at a different time point. Results of ultrasound ecography are shown by motion picture display. Figure 26C provides representative frames as still pictures. The left portion shows an infarcted heart control, while the right portion shows a result of a myoblast sheet of the present invention.

Figures 27A to 27C show an exemplary ultrasound echography analysis of treatment using a prosthetic tissue of the present invention. Results of ultrasound ecography for an infarcted heart treated according to the present invention are shown by motion picture display. Figures 27A to 27C provide representative frames as still pictures.

Figure 28 shows cell affinity by RT-PCR.

Figure 29 shows a change in an implanted myoblast sheet after implantation.

Figure 30A shows an example of Masson's Trichrome staining of a prosthetic tissue of the present invention using myoblasts, which was applied to a cardiomyopathic hamster. The upper portion shows sheet (prosthetic tissue) implantation, cell implantation, and a control ($\times 10$). The lower portion shows an enlarged view for each ($\times 40$).

Figure 30B shows histology (myoblast sheet is accepted by a dilated cardiomyopathic heart and enlarges a ventricular wall).

Figure 30C shows comparison of expression levels of α -sarcoglycan (myoblast sheet implantation enhances

expression of α -sarcoglycan).

Figure 30D shows comparison of expression levels of β -sarcoglycan (myoblast sheet implantation enhances expression of β -sarcoglycan).

Figure 31 shows a survival rate of cardiomyopathic hamsters into which a prosthetic tissue (sheet) comprising myoblasts of the present invention has been implanted myoblast. Injection of cells as they are is compared with administration of a prosthetic tissue.

Figure 32 shows electrical characteristics after implantation of a prosthetic tissue of the present invention. The left portion shows a prosthetic tissue comprising cardiomyocytes, while the right portion shows a prosthetic tissue comprising myoblasts.

Figure 33A shows a therapy for dilated cardiomyopathic hamsters using a prosthetic tissue of the present invention. The left portion shows EF, while the right portion shows HE staining. The lower right portion shows Masson's Trichrome staining.

Figure 33B shows a result of echocardiography 48 weeks after implantation (myoblast sheet implantation ameliorates the cardiac function of a dilated cardiomyopathy heart).

Figure 33C shows a result of echocardiography (the contractility of a left ventricle) 48 weeks after implantation (myoblast sheet implantation ameliorates the contractility of the left ventricle with dilated

cardiomyopathy).

Figure 34 shows an example of a therapy for a pig
infarct model using a prosthetic tissue of the present
5 invention.

Figure 35 shows a therapeutic effect
(contractility) in a pig infarct model using a prosthetic
tissue of the present invention.

10 Figure 36 shows a therapeutic effect
(expansibility) in a pig infarct model using a prosthetic
tissue of the present invention.

15 Figure 37 shows a sheet produced by a prosthetic
tissue production method without ascorbic acid.

Figure 38 shows a sheet produced by a prosthetic
tissue production method with ascorbic acid according to
20 the present invention.

Figure 39 shows a sheet produced by a prosthetic
tissue production method with ascorbic acid according to
the present invention (HE staining).

25 Figure 40 shows a technique for measuring stress and
distortion characteristics to determine tensile strength.

Figure 41 shows a method for obtaining a load/removal
30 of a load curve.

Figure 42 shows a state of a tissue obtained by
culturing synovial cells in the presence of ascorbic acid

2-phosphate.

(Description of Sequencing List)

5 SEQ ID NO. 1 sets forth a nucleic acid sequence of
myosin heavy chain IIa (human: Accession No. NM_017534).

 SEQ ID NO. 2 sets forth an amino acid sequence of
myosin heavy chain IIa (human: Accession No. NM_017534).

10 SEQ ID NO. 3 sets forth a nucleic acid sequence of
myosin heavy chain IIb (human: Accession No. NM_017533).

 SEQ ID NO. 4 sets forth an amino acid sequence of
myosin heavy chain IIb (human: Accession No. NM_017533).

15 SEQ ID NO. 5 sets forth a nucleic acid sequence of
myosin heavy chain IIId(IIx) (human: Accession
No. NM_005963).

20 SEQ ID NO. 6 sets forth an amino acid sequence of
myosin heavy chain IIId(IIx) (human: Accession
No. NM_005963).

 SEQ ID NO. 7 sets forth a nucleic acid sequence of
25 CD56 (human: Accession No. U63041).

 SEQ ID NO. 8 sets forth an amino acid sequence of
CD56 (human: Accession No. U63041).

30 SEQ ID NO. 9 sets forth a nucleic acid sequence of
human MyoD (GENBANK Accession No. X56677).

 SEQ ID NO. 10 sets forth a polypeptide sequence

encoded by the nucleic acid sequence set forth in SEQ ID NO. 2.

5 SEQ ID NO. 11 sets forth a nucleic acid sequence of human myogenic factor 5 (MYF5) (GENBANK Accession No. NM_005593).

10 SEQ ID NO. 12 sets forth a polypeptide sequence encoded by the nucleic acid sequence set forth in SEQ ID NO. 3.

15 SEQ ID NO. 13 sets forth a nucleic acid sequence of human myogenin (myogenic factor 4) (GENBANK Accession No. BT007233).

 SEQ ID NO. 14 sets forth a polypeptide sequence encoded by the nucleic acid sequence set forth in SEQ ID NO. 5.

20 SEQ ID NO. 15 sets forth a forward primer in RT-PCR for SRY.

 SEQ ID NO. 16 sets forth a reverse primer in RT-PCR for SRY.

25 SEQ ID NO. 17 sets forth a probe in RT-PCR for SRY.

 SEQ ID NO. 18 sets forth a forward primer in RT-PCR for IL2.

30 SEQ ID NO. 19 sets forth a reverse primer in RT-PCR for IL3.

SEQ ID NO. 20 sets forth a probe in RT-PCR for IL2.

BEST MODE FOR CARRYING OUT THE INVENTION

5 The present invention will be described below. It should be understood throughout the present specification that articles for singular forms include the concept of their plurality unless otherwise mentioned. Therefore, articles or adjectives for singular forms (e.g., "a", "an", "the",
10 and the like in English) include the concept of their plurality unless otherwise specified. Also, it should be also understood that terms as used herein have definitions ordinarily used in the art unless otherwise mentioned. Therefore, all technical and scientific terms used herein
15 have the same meanings as commonly understood by those skilled in the relevant art. Otherwise, the present application (including definitions) takes precedence.

(Definition of terms)

20 The definitions of specific terms used herein are described below.

(Regenerative medicine)

25 As used herein, the term "regeneration" refers to a phenomenon in which when an individual organism loses a portion of tissue, the remaining tissue grows and recovers. The extent or manner of regeneration varies depending among animal species or among tissues in the same individual. Most human tissues have limited regeneration capability, and
30 therefore, complete regeneration is not expected if a large portion of tissue is lost. In the case of severe damage, a tissue may grow which has strong proliferation capability different from that of lost tissue, resulting in incomplete

regeneration where the damaged tissue is incompletely regenerated and the function of the tissue cannot be recovered. In this case, a structure made of a bioabsorbable material is used to prevent a tissue having strong proliferation capability from infiltrating the defective portion of the tissue so as to secure space for proliferation of the damaged tissue. Further, by supplementing with a cell growth factor, the regeneration capability of the damaged tissue is enhanced. Such a regeneration technique is applied to cartilages, bones, and peripheral nerves, for example. It has been so far believed that nerve cells and cardiac muscles have no or poor regeneration capability. Recently, it was reported that there are tissue stem cells (somatic stem cells), which have both the capability of differentiating into these tissues and self-proliferation capability. Expectations are running high for regenerative medicine using tissue stem cells. Embryonic stem cells (ES cells) are cells, which have the capability of differentiating into all tissues. Efforts have been made to use ES cells for regeneration of complicated organs, such as kidney, liver, and the like, but have not yet been realized.

The term "cell" is herein used in its broadest sense in the art, referring to a structural unit of tissue of a multicellular organism, which is capable of self-replicating, has genetic information and a mechanism for expressing it, and is surrounded by a membrane structure which isolates the living body from the outside. In the method of the present invention, any cell can be used as a subject. The number of cells used in the present invention can be counted through an optical microscope. When counting using an optical microscope, the number of nuclei is counted. Tissues are sliced into tissue sections, which are then stained with

hematoxylin-eosin (HE) to variegate nuclei derived from extracellular matrices (e.g., elastin or collagen) and cells. These tissue sections are observed under an optical microscope and the number of nuclei in a particular area
5 (e.g., 200 μm \times 200 μm) can be estimated to be the number of cells. Cells used herein may be either naturally-occurring cells or artificially modified cells (e.g., fusion cells, genetically modified cells, etc.). Examples of cell sources include, but are not limited to,
10 a single-cell culture; the embryo, blood, or body tissue of a normally-grown transgenic animal; a cell mixture of cells derived from normally-grown cell lines; and the like.

As used herein, the term "stem cell" refers to a cell
15 capable of self replication and pluripotency. Typically, stem cells can regenerate an injured tissue. Stem cells used herein may be, but are not limited to, embryonic stem (ES) cells or tissue stem cells (also called tissular stem cell, tissue-specific stem cell, or somatic stem cell). A stem
20 cell may be an artificially produced cell (e.g., fusion cells, reprogrammed cells, or the like used herein) as long as it can have the above-described abilities. Embryonic stem cells are pluripotent stem cells derived from early embryos. An embryonic stem cell was first established in 1981, and
25 has been applied to production of knockout mice since 1989. In 1998, a human embryonic stem cell was established, which is currently becoming available for regenerative medicine. Tissue stem cells have a relatively limited level of differentiation unlike embryonic stem cells. Tissue stem
30 cells are present in tissues and have an undifferentiated intracellular structure. Tissue stem cells have a higher nucleus/cytoplasm ratio and have few intracellular organelles. Most tissue stem cells have pluripotency, along

cell cycle, and proliferative ability beyond the life of the individual. As used herein, stem cells may be preferably embryonic stem cells, though tissue stem cells may also be employed depending on the circumstance.

5

Tissue stem cells are separated into categories of sites from which the cells are derived, such as the dermal system, the digestive system, the bone marrow system, the nervous system, and the like. Tissue stem cells in the dermal system include epidermal stem cells, hair follicle stem cells, and the like. Tissue stem cells in the digestive system include pancreatic (common) stem cells, hepatic stem cells, and the like. Tissue stem cells in the bone marrow system include hematopoietic stem cells, mesenchymal stem cells, and the like. Tissue stem cells in the nervous system include neural stem cells, retinal stem cells, and the like.

As used herein, the term "somatic cell" refers to any cell other than a germ cell, such as an egg, a sperm, or the like, which does not transfer its DNA to the next generation. Typically, somatic cells have limited or no pluripotency. Somatic cells used herein may be naturally-occurring or genetically modified as long as they can achieve the intended treatment.

25

The origin of a stem cell is categorized into the ectoderm, endoderm, or mesoderm. Stem cells of ectodermal origin are mostly present in the brain, including neural stem cells. Stem cells of endodermal origin are mostly present in bone marrow, including blood vessel stem cells, hematopoietic stem cells, mesenchymal stem cells, and the like. Stem cells of mesoderm origin are mostly present in organs, including hepatic stem cells, pancreatic stem cells,

30

and the like. As used herein, somatic cells may be derived from any mesenchyme. Preferably, somatic cells derived from mesenchyme may be employed.

5 As cells for use in construction of a prosthetic tissue or three-dimensional structure of the present invention, differentiated cells or stem cells derived from the above-described ectoderm, endoderm, or mesoderm may be employed, for example. Examples of such cells include
10 mesenchymal cells. In a certain embodiment, as such cells, myoblasts (e.g., skeletal myoblast, etc.), fibroblasts, synovial cells, and the like may be employed. As such cells, differentiated cells or stem cells can be used as they are. Cells differentiated from stem cells into a desired direction
15 can be used.

 As used herein, the term "mesenchymal stem cell" refers to a stem cell found in mesenchyme. The term "mesenchymal stem cell" may be herein abbreviated as "MSC".
20 Mesenchyme refers to a population of free cells which are in the asterodal shape or have irregular projections and bridge gaps between epithelial tissues, and which are recognized in each stage of development of multicellular animals. Mesenchyme also refers to tissue formed with
25 intracellular cement associated with the cells. Mesenchymal stem cells have proliferation ability and the ability to differentiate into bone cells, cartilage cells, muscle cells, stroma cells, tendon cells, and fat cells. Mesenchymal stem cells are employed in order to culture or
30 grow bone marrow cells or the like collected from patients, or differentiate them into cartilage cells or osteoblasts. Mesenchymal stem cells are also employed as reconstruction material, such as alveolar bones; bones, cartilages or joints

for arthropathy or the like; and the like. There is a large demand for mesenchymal stem cells. Also, mesenchymal stem cells can be differentiated into blood cells and lymphoid cells. Therefore, there is an increasing demand for mesenchymal stem cells. A prosthetic tissue or three-dimensional structure of the present invention comprising mesenchymal stem cells or differentiated mesenchymal stem cells is particularly useful when a structure is required in these applications.

As used herein, the term "isolated" means that naturally accompanying material is at least reduced, or preferably substantially completely eliminated, in normal circumstances. Therefore, the term "isolated cell" refers to a cell substantially free from other accompanying substances (e.g., other cells, proteins, nucleic acids, etc.) in natural circumstances. The term "isolated tissue" refers to a tissue substantially free from substances other than that tissue (e.g., in the case of prosthetic tissues, substances, scaffolds, sheets, coats, etc. used when the prosthetic tissue is produced). The term "isolated" in relation to nucleic acids or polypeptides means that, for example, the nucleic acids or the polypeptides are substantially free from cellular substances or culture media when they are produced by recombinant DNA techniques; or precursory chemical substances or other chemical substances when they are chemically synthesized. Isolated nucleic acids are preferably free from sequences naturally flanking the nucleic acid within an organism from which the nucleic acid is derived (i.e., sequences positioned at the 5' terminus and the 3' terminus of the nucleic acid).

As used herein, the term "intact" in relation to

prosthetic tissues, three-dimensional structures, and the like, refers to no physical external injury. For example, when a prosthetic tissue or the like is produced and is then separated from a circumstance in which the production has
5 been conducted, it has substantially no external injury, such as physical impact or the like.

As used herein, the term "established" in relation to cells refers to a state of a cell in which a particular
10 property (pluripotency) of the cell is maintained and the cell undergoes stable proliferation under culture conditions. Therefore, established stem cells maintain pluripotency.

As used herein, the term "non-embryonic" refers to
15 not being directly derived from early embryos. Therefore, the term "non-embryonic" refers to cells derived from parts of the body other than early embryos. Also, modified embryonic stem cells (e.g., genetically modified or fusion embryonic stem cells, etc.) are encompassed by non-embryonic
20 cells.

As used herein, the term "differentiated cell" refers to a cell having a specialized function and form (e.g., muscle cells, neurons, etc.). Unlike stem cells, differentiated
25 cells have no or little pluripotency. Examples of differentiated cells include epidermic cells, pancreatic parenchymal cells, pancreatic duct cells, hepatic cells, blood cells, cardiac muscle cells, skeletal muscle cells, osteoblasts, skeletal myoblasts, neurons, vascular
30 endothelial cells, pigment cells, smooth muscle cells, fat cells, bone cells, cartilage cells, and the like.

As used herein, the term "tissue" refers to a group

of cells having the same function and form in cellular organisms. In multicellular organisms, constituent cells are usually differentiated so that the cells have specialized functions, resulting in division of labor. Therefore, multicellular organisms are not simple cell aggregations, but constitute organic or social cell groups having a certain function and structure. Examples of tissues include, but are not limited to, integument tissue, connective tissue, muscular tissue, nervous tissue, and the like. Tissue targeted by the present invention may be derived from any organ or part of an organism. In a preferred embodiment of the present invention, tissue targeted by the present invention includes, but is not limited to, blood vessels, blood vessel-like tissue, cardiac valves, pericardia, dura mater, cornea, joints, and bones.

As used herein, the term "prosthetic tissue" refers to tissue having a state different from natural states. Typically, a prosthetic tissue is herein prepared by cell culture. Tissue which is removed from an organism and is not subjected to any treatment is not referred to as a prosthetic tissue. A prosthetic tissue may include materials derived from organisms and materials not derived from organisms. The prosthetic tissue of the present invention typically comprises a cell and/or a biological material, and may comprise other materials. More preferably, a prosthetic tissue of the present invention is composed substantially only of a cell and/or a biological material. Such a biological material is preferably derived from cells constituting the tissue (e.g., extracellular matrix, etc.).

As used herein, the term "implantable prosthetic tissue" refers to a prosthetic tissue, which can be used

for actual clinical implantation and can function as a tissue at the implantation site for a certain period of time after implantation. Implantable prosthetic tissue typically has sufficient strength, sufficient size, sufficient nonporousness, sufficient thickness, sufficient biocompatibility, sufficient affinity, and the like.

The sufficient strength of an implantable prosthetic tissue varies depending on a part targeted by implantation, but can be determined as appropriate by those skilled in the art. However, an implantable prosthetic tissue preferably has at least a certain level of strength. Such a level of strength (e.g., tensile strength) is at least about 50% of the natural strength of a part targeted by implantation, preferably at least about 60%, more preferably about 70%, even more preferably about 80%, and most preferably at least about 100%. The strength can be measured by measuring stress or distortion characteristics or conducting a creep characteristics indentation test as described below.

20

The sufficient size of an implantable prosthetic tissue varies depending on a part targeted by implantation, but can be determined as appropriate by those skilled in the art. However, an implantable prosthetic tissue preferably has at least a certain size. Such a size (e.g., area) is at least 1 cm², preferably at least 2 cm², more preferably at least 3 cm², even more preferably at least 4 cm², at least 5 cm², at least 6 cm², at least 7 cm², at least 8 cm², at least 9 cm², at least 10 cm², at least 15 cm², or at least 20 cm².

30

The sufficient nonporousness of an implantable prosthetic tissue varies depending on a part targeted by

implantation, but can be determined as appropriate by those skilled in the art. As used herein, the term "nonporousness" refers to a state lacking pore(s). Here, the pore refers to a hole having a substantial size such that body fluid or its equivalent (e.g., an aqueous solution, etc.) leaks from a prosthetic tissue. Therefore, nonporousness can be determined as follows. A prosthetic tissue is placed horizontally. Body fluid or its equivalent is placed on the tissue. It is observed whether or not the body fluid or its equivalent leaks from the tissue. If there is no leak, the tissue is judged to have nonporousness.

The sufficient thickness of an implantable prosthetic tissue varies depending on a part targeted by implantation, but can be determined as appropriate by those skilled in the art. However, an implantable prosthetic tissue preferably has at least a certain thickness. Such a thickness is typically at least about 50 μm , preferably at least about 100 μm , more preferably about 150 μm , even more preferably at least about 200 μm , at least about 300 μm , at least about 400 μm , at least about 500 μm , at least about 600 μm , at least about 700 μm , at least about 800 μm , at least about 900 μm , at least about 1 mm. When an implantable prosthetic tissue is implanted into the heart, the tissue may only have these minimum thicknesses. When implantable prosthetic tissue is used in other applications, the tissue may preferably have a greater thickness. In such a case, for example, implantable prosthetic tissue has preferably a thickness of at least 2 mm, more preferably at least 3 mm, and even more preferably 5 mm.

The sufficient biocompatibility of implantable prosthetic tissue varies depending on a part targeted by

implantation, but can be determined as appropriate by those skilled in the art. However, an implantable prosthetic tissue preferably has at least a certain level of biocompatibility. Typically, a desired level of biocompatibility is, for example, such that biological connection to surrounding tissues is achieved without any inflammation, any immune reaction or the like. The present invention is not limited to this. In some cases (e.g., corneas, etc.), an immune reaction is less likely to occur.

Therefore, an implantable prosthetic tissue has biocompatibility to an extent, which achieves the object of the present invention even when an immune reaction is likely to occur in other organs. Examples of parameters indicating biocompatibility include, but are not limited to, the presence or absence of an extracellular matrix, the presence or absence of an immune reaction, the degree of inflammation, and the like. Such biocompatibility can be determined by examining the compatibility of a prosthetic tissue at an implantation site after implantation (e.g., confirming that an implanted prosthetic tissue is not destroyed). See "Hito Ishoku Zoki Kyozeitsu Hanno no Byori Soshiki Shindan Kijyun Kanbetsu Shindan to Seiken Hyohon no Toriatsukai (Zufu) Jinzo Ishoku, Kanzo Ishoku Oyobi Shinzo Ishoku [Pathological Tissue Diagnosis Criterion for Human Transplanted Organ Rejection Reaction Handling of Differential Diagnosis and Biopsy Specimen (Illustrated Book) Kidney Transplantation, Liver Transplantation and Heart Transplantation]" The Japan Society for Transplantation and The Japanese Society for Pathology editors, Kanehara Shuppan Kabushiki Kaisha (1998). According to this document, biocompatibility is divided into Grade 0, 1A, 1B, 2, 3A, 3B, and 4. At Grade 0 (no acute rejection), no acute rejection reaction, cardiomyocyte

failure, or the like is found in biopsy specimens. At Grade 1A (focal, mild acute rejection), there is focal infiltration of large lymphocytes around blood vessels or into interstitial tissue, while there is no damage to cardiomyocytes. This observation is obtained in one or a plurality of biopsy specimens. At Grade 1B (diffuse, mild acute rejection), there is diffuse infiltration of large lymphocytes around blood vessels or into interstitial tissue or both, while there is no damage to cardiomyocytes. At Grade 2 (focal, moderate acute rejection), there is a single observed infiltration focus of inflammatory cells clearly bordered from the surrounding portions. Inflammation cells are large activated lymphocytes and may include eosinophils. Damage to cardiomyocytes associated with modification of cardiac muscle is observed in lesions. At Grade 3A (multifocal, moderate acute rejection), there are multiple infiltration foci of inflammatory cells which are large activated lymphocytes and may include eosinophils. Two or more of the multiple inflammatory infiltration foci of inflammatory cells have damages to cardiomyocytes. In some cases, there is also rough infiltration of inflammatory cells into the endocardium. The infiltration foci are observed in one or a plurality of biopsy specimens. At Grade 3B (multifocal, borderline severe acute rejection), there are more confluent and diffuse infiltration foci of inflammatory cells found in more biopsy specimens than those observed at Grade 3A. There is infiltration of inflammatory cells including large lymphocytes and eosinophils, in some cases neutrophils, as well as damage to cardiomyocytes. There is no hemorrhage. At Grade 4 (severe acute rejection), there is infiltration of various inflammatory cells including activated lymphocytes, eosinophils, and neutrophils. There is always damage to cardiomyocytes and necrosis of

cardiomyocytes. Edema, hemorrhage, and/or angitis are also typically observed. Infiltration of inflammatory cells into the endocardium, which is different from the "Quilty" effect, is typically observed. When a therapy is strongly
5 conducted using an immunosuppressant for a considerably long period of time, edema and hemorrhage may be more significant than infiltration.

The sufficient affinity of an implantable prosthetic
10 tissue varies depending on a part targeted by implantation, but can be determined as appropriate by those skilled in the art. Examples of parameters for affinity include, but are not limited to, biological connection ability between an implanted prosthetic tissue and its implantation site,
15 and the like. Such affinity can be determined based on the presence of biological connection at an implantation site after implantation. Preferable affinity is herein such that an implanted prosthetic tissue has the same function as that of a site in which the tissue is implanted, for example.

20

As used herein, the term "membranous tissue" refers to a tissue in the form of membrane and is also referred to as "planar tissue". Examples of membranous tissue include a portion of tissue having a certain area of an organ (e.g.,
25 pericardium, dura mater, cornea, etc.) or bag-shaped tissue, and the like.

As used herein, the term "organ" refers to a structure which is a specific part of an individual organism where
30 a certain function of the individual organism is locally performed and which is morphologically independent. Generally, in multicellular organisms (e.g., animals and plants), organs are made of several tissues in specific

spatial arrangement and tissue is made of a number of cells. Examples of such organs include, but are not limited to, skin, blood vessel, cornea, kidney, heart, liver, umbilical cord, intestine, nerve, lung, placenta, pancreas, brain, joint, bone, cartilage, peripheral limbs, retina, and the like. Examples of such organs include, but are not limited to, organs of the skin system, the parenchyma pancreas system, the pancreatic duct system, the hepatic system, the blood system, the myocardial system, the skeletal muscle system, the osteoblast system, the skeletal myoblast system, the nervous system, the blood vessel endothelial system, the pigment system, the smooth muscle system, the fat system, the bone system, the cartilage system, and the like.

As used herein, the term "bag-shaped organ" refers to an organ which has a three-dimensional expanse and the inside of which may be connected via a tubular tissue to the outside. Examples of bag-shaped organs include, but are not limited to, heart, liver, kidney, stomach, spleen, and the like.

In one embodiment, the present invention targets vascular system-related organs, and preferably ischemic organs (e.g., heart having myocardial infarcted heart having ischemia, etc.). In a preferred embodiment, the present invention targets blood vessels, blood vessel-like tissue, heart, heart valves, pericardia, dura mater, cornea, and bones. In another preferred embodiment, the present invention targets heart, heart valves, pericardia, and blood vessels.

As used herein, the term "wrap" in relation to a prosthetic tissue, a three-dimensional structure, or the

like, which is wrapped around a certain part (e.g., an injured site, etc.), means that the prosthetic tissue or the like is arranged so as to cover the part (i.e., conceal an injury or the like). The terms "wrap" and "arrange (or locate) so as to cover" are used interchangeably. By observing the spatial relationship between the part and the prosthetic tissue or the like, it can be determined whether or not the part is covered by the prosthetic tissue or the like. In a preferred embodiment, in a wrapping step, a prosthetic tissue or the like can be wrapped one turn around a certain site.

A "sufficient time required for a prosthetic tissue to biologically join with a part" herein varies depending on a combination of the part and the prosthetic tissue, but can be determined as appropriate by those skilled in the art based on the combination. Examples of such a time include, but are not limited to, 1 week, 2 weeks, 1 month, 2 months, 3 months, 6 months, 1 year, and the like, after operation. In the present invention, a prosthetic tissue preferably comprises substantially only cells and materials derived from the cells, and therefore, there is no particular material which needs to be extracted after operation. Therefore, the lower limit of the sufficient time is not particularly important. Thus, in this case, a longer time is more preferable. If the time is substantially extremely long, reinforcement is substantially completed.

As used herein, the term "immune reaction" refers to a reaction due to the dysfunction of immunological tolerance between a graft and a host. Examples of immune reactions include, but are not limited to, a hyperacute rejection reaction (within several minutes after

implantation) (immune reaction caused by antibodies, such as β -Gal or the like), an acute rejection reaction (reaction caused by cellular immunity about 7 to 21 days after implantation), a chronic rejection reaction (rejection reaction caused by cellular immunity 3 or more months after operation), and the like.

As used herein, the elicitation of an immune reaction can be confirmed by pathological and histological examination of the type, number, or the like of infiltration of (immunological) cells into implanted tissue using staining (e.g., HE staining, etc.), immunological staining, or microscopic inspection of tissue sections.

As used herein, the term "calcification" refers to precipitation of calcareous substances in organisms.

As used herein, "calcification" *in vivo* can be determined by measuring calcium concentration. Specifically, implanted tissue is taken out; the tissue section is dissolved by acid treatment or the like; and the atomic absorption of the solution is measured by a trace element quantifying device.

As used herein, the term "within organism(s) (or in organism(s))" or "*in vivo*" refers to the inner part of organism(s). In a specific context, "within organism(s)" refers to a position at which a subject tissue or organ is placed.

30

As used herein, "*in vitro*" indicates that a part of an organism is extracted or released outside the organism for various purposes of research (e.g., in a test tube).

The term *in vitro* is in contrast to the term *in vivo*.

As used herein, the term "*ex vivo*" refers to a series of operations where target cells into which a gene will be introduced are extracted from a subject; a therapeutic gene is introduced *in vitro* into the cells; and the cells are returned into the same subject.

As used herein, the term "material derived from cell(s)" refers to any material originating from the cell(s), including, but not being limited to, materials constituting the cell(s), materials secreted by the cell(s), materials metabolized by the cell(s), and the like. Representative examples of materials derived from cells include, but are not limited to, extracellular matrices, hormones, cytokines, and the like. Materials derived from cells typically have substantially no adverse effect on the cells and their hosts. Therefore, when the material is contained in a prosthetic tissue, a three-dimensional structure, or the like, the material typically has substantially no adverse effect on the prosthetic tissue, three-dimensional structure, or the like.

As used herein, the term "extracellular matrix" (ECM) refers to a substance existing between somatic cells no matter whether the cells are epithelial cells or non-epithelial cells. Extracellular matrices are typically produced by cells, and therefore, are biological materials. Extracellular matrices are involved in supporting tissue as well as in internal environmental structure essential for survival of all somatic cells. Extracellular matrices are generally produced from connective tissue cells. Some extracellular matrices are secreted from cells possessing

basal membrane, such as epithelial cells or endothelial cells. Extracellular matrices are roughly divided into fibrous components and matrices filling there between. Fibrous components include collagen fibers and elastic fibers. A
5 basic component of matrices is a glycosaminoglycan (acidic mucopolysaccharide), most of which is bound to non-collagenous protein to form a polymer of a proteoglycan (acidic mucopolysaccharide-protein complex). In addition, matrices include glycoproteins, such as laminin of basal
10 membrane, microfibrils around elastic fibers, fibers, fibronectins on cell surfaces, and the like. Particularly differentiated tissue has the same basic structure. For example, in hyaline cartilage, chondroblasts characteristically produce a large amount of cartilage
15 matrices including proteoglycans. In bones, osteoblasts produce bone matrices which cause calcification. In one embodiment of the present invention, the prosthetic tissue, three-dimensional structure, or the like of the present invention may be advantageously similar to the composition
20 of an extracellular matrix (e.g., elastin, collagen (e.g., Type I, Type IV, etc.), laminin, etc.) of a site of an organ for which implantation is intended. In the present invention, extracellular matrices include cell adhesion molecules. As used herein, the terms "cell adhesion molecule" and "adhesion
25 molecule" are used interchangeably, referring to a molecule capable of mediating the joining of two or more cells (cell adhesion) or adhesion between a substrate and a cell. In general, cell adhesion molecules are divided into two groups: molecules involved in cell-cell adhesion (intercellular
30 adhesion) (cell-cell adhesion molecules) and molecules involved in cell-extracellular matrix adhesion (cell-substrate adhesion) (cell-substrate adhesion molecules). A prosthetic tissue or three-dimensional

structure of the present invention typically comprises such a cell adhesion molecule. Therefore, cell adhesion molecules herein include a protein of a substrate and a protein of a cell (e.g., integrin, etc.) in cell-substrate adhesion.

5 A molecule other than proteins falls within the concept of cell adhesion molecule as long as it can mediate cell adhesion.

For cell-cell adhesion, cadherin, a number of molecules belonging in an immunoglobulin superfamily (NCAM1, 10 ICAM, fasciclin II, III, etc.), selectin, and the like are known, each of which is known to join cell membranes via a specific molecular reaction. Therefore, in one embodiment, the prosthetic tissue, three-dimensional structure, or the like of the present invention preferably has substantially 15 the same composition of cadherin, immunoglobulin superfamily molecules, or the like as that of a site for which implantation is intended.

Thus, various molecules are involved in cell adhesion 20 and have different functions. Those skilled in the art can appropriately select a molecule to be contained in a prosthetic tissue or three-dimensional structure of the present invention depending on the purpose. Techniques for cell adhesion are well known as described above and as 25 described in, for example, "Saibogaimatorikkusu-Rinshoheno Oyo- [Extracellular matrix -Clinical Applications-], Medical Review.

It can be determined whether or not a certain molecule 30 is a cell adhesion molecule, by an assay, such as biochemical quantification (an SDS-PAG method, a labeled-collagen method, etc.), immunological quantification (an enzyme antibody method, a fluorescent antibody method, an immunohistological

study, etc.), a PCR method, a hybridization method, or the like, in which a positive reaction is detected. Examples of such a cell adhesion molecule include, but are not limited to, collagen, integrin, fibronectin, laminin, vitronectin, 5 fibrinogen, an immunoglobulin superfamily member (e.g., CD2, CD4, CD8, ICM1, ICAM2, VCAM1), selectin, cadherin, and the like. Most of these cell adhesion molecules transmit into a cell an auxiliary signal for cell activation due to intercellular interaction as well as cell adhesion. 10 Therefore, an adhesion factor for use in an implant of the present invention preferably transmits an auxiliary signal for cell activation into a cell. This is because cell activation can promote growth of cells originally present or aggregating in a tissue or organ at an injured site after application of an implant thereto. It can be determined 15 whether or not such an auxiliary signal can be transmitted into a cell, by an assay, such as biochemical quantification (an SDS-PAG method, a labeled-collagen method, etc.), immunological quantification (an enzyme antibody method, a fluorescent antibody method, an immunohistological study, 20 etc.), a PDR method, a hybridization method, or the like, in which a positive reaction is detected.

An example of a cell adhesion molecule is cadherin 25 which is present in many cells capable of being fixed to tissue. Cadherin can be used in a preferred embodiment of the present invention. Examples of a cell adhesion molecule in cells of blood and the immune system which are not fixed to tissue, include, but are not limited to, immunoglobulin 30 superfamily molecules (CD 2, LFA-3, ICAM-1, CD2, CD4, CD8, ICM1, ICAM2, VCAM1, etc.); integrin family molecules (LFA-1, Mac-1, gpIIbIIIa, p150, p95, VLA1, VLA2, VLA3, VLA4, VLA5, VLA6, etc.); selectin family molecules (L-selectin,

E-selectin, P-selectin, etc.), and the like. Therefore, such a molecule may be useful for treatment of a tissue or organ of blood and the immune system.

5 Nonfixed cells need to be adhered to a specific tissue in order to act on the tissue. In this case, it is believed that cell-cell adhesion is gradually enhanced via a first adhesion by a selectin molecule or the like which is constantly expressed and a second adhesion by a subsequently activated
10 integrin molecule. Therefore, in the present invention, a cell adhesion molecule for mediating the first adhesion and another cell adhesion molecule for mediating the second adhesion may be used together.

15 As used herein, the term "tissue injury rate" refers to a parameter which indicates a function of a tissue or organ; an indicator which indicates how much a treated tissue or organ is injured; and an indicator which indicates whether or not a tissue or organ can have its original function.
20 Methods for determining a tissue injury rate are known in the art. For example, a tissue injury rate can be determined by counting elastin ruptured sites. Herein, a visual field is divided into units of $100\ \mu\text{m} \times 100\ \mu\text{m}$. In each unit, the presence or absence of an elastin ruptured site is determined.
25 If there is an elastin ruptured site in a unit, the count is incremented. One visual field has 24 units. The extracellular matrices of tissue sections stained by HE staining are subjected to microscopic inspection and counting. Non-treated tissue is defined as having a tissue injury rate
30 of 0%. A tissue injury rate is calculated by $x/24$. In this case, non-treated tissue corresponds to $x=0$.

As used herein, the term "tissue strength" refers

to a parameter which indicates a function of a tissue or organ and a physical strength of the tissue or organ. Tissue strength can be generally determined by measuring tensile strength (e.g., break strength, modulus of rigidity, Young's modulus, etc.). Such a general tensile test is well known. By analyzing data obtained by a general tensile test, various data, such as break strength, modulus of rigidity, Young's modulus, and the like, can be obtained. These values can be herein used as indicators of tissue strength. Typically, tissue strength which allows clinical applications is herein required.

The tensile strength of a prosthetic tissue, three-dimensional structure, or the like of the present invention can be determined by measuring the stress and distortion characteristics thereof. Briefly, a load is applied to a sample; the resultant distortion and the load are input to respective A/D converters (e.g., ELK-5000) (1 ch: distortion, 2 ch: load); the stress and distortion characteristics are measured to determine the tensile strength of the sample (Figure 40). Tensile strength can also be determined by testing creep characteristics. A creep characteristics indentation test is conducted to investigate how a sample is extended over time while a constant load is applied to the sample. For small materials, thin materials, and the like, an indentation test is conducted using, for example, a triangular pyramid-shaped indenter with a tip having a radius of about 0.1 μm to about 1 μm . Initially, the indenter is pushed into a test piece so that a load is given to the test piece. When the indenter reaches from several tens of nanometers to several micrometers deep in the test piece, the indenter is drawn off to remove the load. Figure 41 shows a load/removal of load curve obtained by

the above-described test method. Rigidity, Young's modulus, or the like can be obtained based on the behavior of the load and the push depth derived from the curve.

5 In a preferred embodiment, the tensile strength of the prosthetic tissue or three-dimensional structure of the present invention is typically at least about 50% of the natural strength of a part in which implantation is intended, preferably at least about 60%, more preferably about 70%,
10 even more preferably about 80%, and most preferably at least about 100%.

 In an alternative embodiment, the prosthetic tissue of the present invention may have a tissue strength of at
15 least about 75% of that of a portion of natural tissue (e.g., a portion in which a clinical application is intended (e.g., heart, etc.)), preferably at least about 80%, more preferably at least about 85%, and even more preferably about 90%. The tissue strength of the prosthetic tissue may be equal to
20 or greater than that of the natural tissue. The tissue strength of a natural tissue refers to a tissue strength which is possessed by a tissue of interest in its natural state. In addition to membranous tissue, other tissues (e.g., tubular tissue, etc.) preferably have a sufficiently strong
25 tissue strength. In the case of tubular tissue, the tissue strength can be represented by a β value. A method for calculating a β value will be described in detail in another portion of the present specification and will also be illustrated in the Examples below. In a certain embodiment,
30 the prosthetic tissue of the present invention has a tissue strength corresponding to a β value of at least about 15, preferably at least about 18, more preferably at least about 20, and even more preferably at least about 22. In another

embodiment, the prosthetic tissue of the present invention has a β value of at least about 75% of that of the tissue before treatment, preferably at least about 80%, more preferably at least about 85%, and even more preferably at least about 90%. The β value of the prosthetic tissue may be equal to or greater than that originally possessed by the untreated tissue. A characteristic (e.g., a β value) of untreated tissue refers to a characteristic of the tissue before treatment (e.g., treatment using 1,2-epoxide polymer in the present invention) (e.g., in the natural state). Therefore, for example, if an original tissue has a β value of 25, a prosthetic tissue of the present invention may preferably have a β value of at least 17.5, preferably at least 20, more preferably at least 21.25, and even more preferably at least 22.5.

As used herein, in the case of tubular tissue, the tissue strength can be represented by a rigidity parameter (β value). The β value can be calculated based on the following expression after the P-D (pressure-diameter) relationship is established:

$$\ln(P/P_s) = \beta(D/D_s - 1) \quad (1)$$

where P_s and D_s represents their standard values at 100 mmHg. The value of the diameter (D) is measured under each P (pressure).

Both ends of a tubular tissue (e.g., a blood vessel, etc.) are each fixed to a pipe-like unit. The inside and outside of the tissue are filled with physiological saline. In this situation, pressure is applied to the inside of the tissue by an external device, while the outer diameter of

the tissue under the pressure is monitored. The measured pressure and outer diameter are substituted into expression (1) to calculate a β value (Sonoda H., Takamizawa K. et al., J. Biomed. Matr. Res., 2001: 266-276).

5

As used herein, the term "physiologically active substance" refers to a substance capable of acting on a cell or tissue. Physiologically active substances include cytokines and growth factors. A cellular physiologically active substance may be naturally-occurring or synthesized. Preferably, a cellular physiologically active substance is one that is produced by a cell or one that has a function similar thereto. As used herein, a cellular physiologically active substance may be in the form of a protein or a nucleic acid or in other forms. In actual practice, cellular physiologically active substances are typically proteins. In the present invention, a physiologically active substance may be used to promote the affinity of an implanted prosthetic tissue of the present invention, for example.

20

The term "cytokine" is used herein in the broadest sense in the art and refers to a physiologically active substance which is produced from a cell and acts on the same or different cell. Cytokines are generally proteins or polypeptides having a function of controlling an immune response, regulating the endocrine system, regulating the nervous system, acting against a tumor, acting against a virus, regulating cell growth, regulating cell differentiation, or the like. Cytokines are herein in the form of a protein or a nucleic acid or in other forms. In actual practice, cytokines are typically proteins.

30

The terms "growth factor" or "cell growth factor"

are used herein interchangeably and each refers to a substance which promotes or controls cell growth. Growth factors are also called "proliferation factors" or "development factors". Growth factors may be added to cell or tissue culture medium, substituting for serum macromolecules. It has been revealed that a number of growth factors have a function of controlling differentiation in addition to a function of promoting cell growth.

Examples of cytokines representatively include, but are not limited to, interleukins, chemokines, hematopoietic factors such as colony stimulating factors, a tumor necrosis factor, interferons, a platelet-derived growth factor (PDGF), an epidermal growth factor (EGF), a fibroblast growth factor (FGF), a hepatocyte growth factor (HGF), an endothelial cell growth factor (VEGF), cardiotrophin, and the like, which have proliferative activity.

Cellular physiologically active substances, such as cytokines, growth factors, and the like, typically have redundancy in function. Accordingly, reference herein to a particular cytokine or growth factor by one name or function also includes any other names or functions by which the factor is known to those of skill in the art, as long as the factor has the activity of a cellular physiologically active substance for use in the present invention. Cytokines or growth factors can be used in a therapeutic or pharmaceutical agent according to a preferred embodiment of the present invention as long as they have preferable activity as described herein.

Therefore, in one embodiment of the present invention, it was revealed that when such a cytokine or growth factor

(e.g., HGF) is provided to an implantation site (e.g., an implantation site of the myocardium, etc.) concomitantly with a prosthetic tissue or three-dimensional structure of the present invention, the affinity of the prosthetic tissue or three-dimensional structure and an improvement in the function of the implantation site are observed. Thus, the present invention also provides such a combined therapy.

As used herein, the term "differentiation" refers to a developmental process of the state of the composite parts of organisms, such as cells, tissues, or organs and a process in which a characteristic tissue or organ is formed. The term "differentiation" is mainly used in embryology, developmental biology, and the like. In organisms, various tissues and organs are formed from divisions of a fertilized ovum (a single cell) to an adult. At early developmental stages (i.e., before cell division or after insufficient cell division), each cell or cell group has no morphological or functional feature and is not much distinguishable. Such a state is referred to as "undifferentiated". "Differentiation" may occur at the level of organs. A cell constituting an organ may develop into various cells or cell groups having different features. This phenomenon is also referred to as differentiation within an organ in the formation of the organ. Therefore, a prosthetic tissue or three-dimensional structure of the present invention may comprise a tissue including differentiated cells.

As used herein, the terms "implant", "graft", and "tissue graft" are used interchangeably, referring to homologous or heterologous tissue or a cell group, or an artificial material, which is inserted into a particular site of a body and thereafter forms a part of the body.

Therefore, a prosthetic tissue or three-dimensional structure of the present invention can be used as an implant. Examples of conventional grafts include, but are not limited to, organs or portions of organs, blood vessels, blood vessel-like tissue, heart, cardiac valves, pericardia, and the like. Therefore, grafts encompass any one of these which is inserted into a deficient part so as to compensate for the deficiency. Grafts include, but are not limited to, autografts, allografts, and xenografts, which depend on the type of their donor.

As used herein, the term "autograft" (a tissue, a cell, an organ, etc.) refers to a graft (a tissue, a cell, an organ, etc.) which is implanted into the same individual from which the graft is derived. As used herein, the term "autograft" (a tissue, a cell, an organ, etc.) may encompass a graft from a genetically identical individual (e.g. an identical twin) in a broad sense. As used herein, the terms "autologous" and "derived from a subject" are used interchangeably. Therefore, the term "not derived from a subject" in relation to a graft indicates that the graft is not autologous (i.e., heterologous).

As used herein, the term "allograft" (a tissue, a cell, an organ, etc.) refers to a graft (a tissue, a cell, an organ, etc.) which is implanted into an individual which is the same species but is genetically different from that from which the graft is derived. Since an allograft (a tissue, a cell, an organ, etc.) is genetically different from an individual (recipient) to which the graft is implanted, the graft may elicit an immune reaction. Such a graft (a tissue, a cell, an organ, etc.) includes, but is not limited to, for example, a graft (a tissue, a cell, an organ, etc.) derived

from a parent.

As used herein, the term "xenograft" (a tissue, a cell, an organ, etc.) refers to a graft (a tissue, a cell, an organ, etc.) which is implanted from a different species. Therefore, for example, when a human is a recipient, a porcine-derived graft (a tissue, a cell, an organ, etc.) is called a xenograft (a tissue, a cell, an organ, etc.).

As used herein, "recipient" (acceptor) refers to an individual which receives a graft (a tissue, a cell, an organ, etc.) or implanted matter (a tissue, a cell, an organ, etc.) and is also called "host". In contrast, an individual providing a graft (a tissue, a cell, an organ, etc.) or implanted matter (a tissue, a cell, an organ, etc.) is called "donor" (provider).

With a prosthetic tissue forming technique of the present invention, a prosthetic tissue derived from any cell can be used. This is because a prosthetic tissue (e.g., membranous tissues, organs, etc.) formed by the method of the present invention can exhibit a desired function while the tissue injury rate is maintained at a level which does not interfere with the therapy (i.e., a low level). Conventionally, tissues or organs are used as grafts without modification. In contrast to this, the present invention provides a tissue comprising three-dimensionally connected cells. Such a prosthetic three-dimensional tissue cannot be achieved by conventional techniques, and therefore, constitutes one significant effect of the present invention.

As used herein, the term "subject" refers to an organism to which treatment of the present invention is

applied and is also referred to as "patient". A patient or subject may be preferably a human.

Cells optionally used in a prosthetic tissue, three-dimensional structure, or tissue graft of the present invention may be derived from a syngeneic origin (self origin), an allogenic origin (non-self origin), or a heterologous origin. In view of rejection reactions, syngeneic cells are preferable. If rejection reactions do not raise problems, allogenic cells may be employed. Cells which elicit rejection reactions can be employed by optionally treating the cells in a manner that overcomes rejection reactions. Procedures for avoiding rejection reactions are known in the art (see, for example, "Shin Gekagaku Taikai, Dai 12 Kan, Zoki Ishoku (Shinzo Ishoku : Hai Ishoku Gijutsuteki, Rinriteki Seibi kara Jisshi ni Mukete [New Whole Surgery, Vol. 12, Organ Transplantation (Heart Transplantation · Lung Transplantation From Technical and Ethical Improvements to Practice)" (Revised 3rd ed.), Nakayama Shoten]. Examples of such methods include, but are not limited to, a method using immunosuppressants or steroidal drugs, and the like. For example, there are currently the following immunosuppressants for preventing rejection reactions: "cyclosporine" (SANDIMMUNE/NEORAL); "tacrolimus" (PROGRAF); "azathioprine" (IMURAN); "steroid hormone" (prednine, methylprednine); and "T-cell antibodies" (OKT3, ATG, etc.). A method which is used worldwide as a preventive immunosuppression therapy in many facilities, is the concurrent use of three drugs: cyclosporine, azathioprine, and steroid hormone. An immunosuppressant is desirably administered concurrently with a pharmaceutical agent of the present invention. The present invention is not limited to this. An immunosuppressant may be administered before

or after a regeneration/therapeutic method of the present invention as long as an immunosuppression effect can be achieved.

5 Cells used in the present invention may be derived from any organism (e.g., vertebrates and invertebrates). Preferably, cells derived from vertebrates are used. More preferably, cells derived from mammals (e.g., primates, rodents, etc.) are used. Even more preferably, cells derived
10 from primates are used. Most preferably, cells derived from a human are used. Typically, cells from the same species as the host are preferably used.

 Examples of a subject treated by a prosthetic tissue
15 of the present invention include, but are not limited to, the heart suffering from a heart disease (e.g., heart failure, ischemic heart diseases, myocardial infarct, cardiomyopathy, myocarditis, hypertrophic cardiomyopathy, dilated hypertrophic cardiomyopathy, and dilated cardiomyopathy);
20 blood vessels in a pericardium patch, infarcted myocardium lower and upper limbs; and the like.

 Tissues targeted by the present invention may be any organ of an organism and may be derived from any organism.
25 Examples of organisms targeted by the present invention include vertebrates and invertebrates. Preferably, organisms targeted by the present invention are mammals (e.g., primates, rodents, etc.). More preferably, organisms targeted by the present invention are primates. Most
30 preferably, organisms targeted by the present invention are humans.

 When a prosthetic tissue, three-dimensional

- 51 -

structure, or the like of the present invention is used as a valve, techniques well known in the art for general use of prosthetic valves can be used to implant the prosthetic tissue or the like. For example, stentless heterologous tissue valves are well known in the art. For example, 5 stentless heterologous tissue valves are known. In heterologous tissue valves, the presence of a stent reduces the effective area of the valve port, leading to calcification or degeneration of valve leaflets. Recently, by utilizing 10 the morphology of the base portion of the porcine aorta, a stentless heterologous tissue valve stent without a stent has attracted attention as a prosthetic valve for the aortic valve (Gross C., et al., Ann. Thorac. Surg., 68:919, 1999). It is considered that the absence of a stent results in a 15 small pressure difference across the valve even when a small-size valve is unavoidably used and is also effective for postoperative enlargement of the left ventricle. Further, the elasticity of the base portion of the aorta is maintained, stress to the cusp is small, and the durability 20 can be expected to be improved as compared to a tissue valve with a stent. Further, stentless heterologous tissue valves can be used in the case of endocarditis due to infection or prosthetic valve infection. At present, substantially satisfactory intermediate-term postoperative results of 25 stentless heterologous tissue valves have been reported in the USA and Europe, and long-term results can be expected to be satisfactory (Gross C., et al., Ann. Thorac. Surg., 68:919, 1999).

30 As used herein, the term "large size" in relation to a prosthetic tissue refers to the size of a portion thereof which has no pore. Representatively, the term "large size" means that the length in a longitudinal direction of a portion

having no pore is at least 1 cm, preferably at least 1.5 cm, and even more preferably at least 2 cm. In this case, the length in a transverse direction thereof is also at least 1 cm, preferably at least 1.5 cm, and even more preferably at least 2 cm. The present invention is not limited to this. When a "large size" is represented by the area of a prosthetic tissue, the area of an inscribed circle in a portion having no pore is typically at least 1 cm², preferably at least 2 cm², more preferably at least 3 cm², even more preferably at least 4 cm², still even more preferably at least 5 cm², and most preferably at least 6 cm².

As used herein, the term "flexibility" in relation to a prosthetic tissue refers to an ability to resist physical stimuli from external environments (e.g., pressure). A prosthetic tissue having flexibility is preferable when the implantation site moves or deforms autonomously or by external effects. Therefore, such a prosthetic tissue having flexibility preferably retains flexibility after implantation.

As used herein, the term "extendibility and contractibility" in relation to a prosthetic tissue refers to an ability to resist extending or contracting stimuli from external environments (e.g., pulsation). A prosthetic tissue having extendibility and contractibility is preferable when the implantation site is subjected to extending or contracting stimuli. Examples of implantation sites, which are subjected to extending or contracting stimuli, include, but are not limited to, heart, muscle, joint, cartilage, tendon, and the like. In one embodiment, extendibility and contractibility capable of withstanding the pulsation motion of the heart may be required.

As used herein, the term "part other than the myocardium of an adult" refers to any part, tissue, cell, or organ other than the myocardium of the terminally differentiated heart. Examples of such parts, tissues, cells, and organs include, but are not limited to, skeletal myoblasts, fibroblasts, synovial cells, stem cells, and the like. These cells have no marker characteristic to cells derived from the myocardium of the adult heart. Such a marker (hereinafter referred to as an "adult myocardial marker") may be in the form of a nucleic acid molecule (expression of mRNA), a protein, an extracellular matrix, a specific phenotype, a specific shape of a cell, or the like. Therefore, adult myocardial markers which are not specified herein may be used to identify a prosthetic tissue of the present invention as long as these markers can indicate cells derived from the myocardium of an adult. Representative examples of parts other than the myocardium of an adult include, but are not limited to, portions of the heart other than the adult myocardium, portions containing mesenchymal stem cells or cells derived therefrom, other tissues, other organs, myoblasts (e.g., skeletal myoblasts), fibroblasts, synovial cells, and the like. Therefore, by identifying a specific marker characteristic to parts other than the myocardium of an adult, the parts other than myocardium can be confirmed.

As used herein, the term "part other than the heart of an adult" refers to any part, tissue, cell, or organ other than the terminally differentiated heart. Examples of such parts, tissues, cells, and organs include, but are not limited to, skeletal myoblasts, fibroblasts, synovial cells, stem cells, and the like. These cells have no marker characteristic to cells derived from the adult heart. Such

a marker may be in the form of a nucleic acid molecule (expression of mRNA), a protein, an extracellular matrix, a specific phenotype, a specific shape of cell, or the like. Therefore, adult heart markers which are not specified herein
5 may be used to identify a prosthetic tissue of the present invention as long as these markers can indicate cells derived from adult heart. Representative examples of parts other than the heart of an adult include, but are not limited to, parts containing mesenchymal stem cells or cells derived
10 therefrom, other tissues, other organs, myoblasts (e.g., skeletal myoblasts), fibroblasts, synovial cells, and the like. Therefore, by identifying a specific marker characteristic to parts other than the heart, the parts other than the heart of an adult can be confirmed.

15

A "part other than the myocardium of an adult" and a "part other than the heart of an adult" can be identified using markers characteristic to cells derived from the myocardium of an adult or the heart of an adult including
20 skeletal myoblasts, fibroblasts, synovial cells, stem cells, or the like (hereinafter referred to as a "non-adult myocardial marker" or a "non-adult heart marker", respectively). If the marker is expressed by less than about 100%, preferably less than about 80%, more preferably less
25 than about 50%, even more preferably less than about 25%, in some cases less than about 1%, the above-described parts can be identified. Examples of such markers include, but are not limited to, myosin heavy chain IIa, myosin heavy chain IIb, myosin heavy chain IIc (IIx), CD56, MyoD, Myf5,
30 myogenin, and the like. Therefore, non-adult myocardial markers which are not specified herein may be used to identify a prosthetic tissue of the present invention as long as these markers can indicate cells derived from parts other than

the myocardium of an adult. Also, non-adult heart markers which are not specified herein may be used to identify a prosthetic tissue of the present invention as long as these markers can indicate cells derived from parts other than the heart of an adult.

Myosin heavy chain IIa (human: Accession No. NM_017534; SEQ ID NOs. 1 and 2), myosin heavy chain IIb (human: Accession No. NM_017533; SEQ ID NOs. 3 and 4), and myosin heavy chain IIc (IIx) (human: Accession No. NM_005963; SEQ ID NOs. 5 and 6) are markers specific to myoblasts (Havenith M.G., Visser R., Schrijvers-van Schendel J.M., Bosman F.T., "Muscle Fiber Typing in Routinely Processed Skeletal Muscle With Monoclonal Antibodies", Histochemistry, 1990; 93(5):497-499). These markers can be confirmed mainly by observing the presence of proteins. An antibody against myosin heavy chain IIa, myosin heavy chain IIb, and myosin heavy chain IIc (IIx) is, for example, MY-32 available from Sigma. This antibody is specific to skeletal muscles and does not bind to myocardium (Webster C., Pavlath G.K., Parks D.R., Walsh F.S., Blau H.M., Exp. Cell. Res., 1988 Jan; 174(1):252-65; and Havenith M.G., Visser R., Schrijvers-van Schendel J.M., Bosman F.T., Muscle Fiber Typing in Routinely Processed Skeletal Muscle with Monoclonal Antibodies, Histochemistry, 1990, 93(5):497-499).

CD56 (human: Accession No. U63041; SEQ ID NOs. 7 and 8) is a marker specific to myoblasts. This marker can be confirmed mainly by observing the presence of mRNA.

MyoD (human: Accession No. X56677; SEQ ID NOs. 9 and 10) is a marker specific to myoblasts. This marker can be confirmed mainly by observing the presence of mRNA.

Myf5 (human: Accession No. NM_005593; SEQ ID NOs. 11 and 12) is a marker specific to myoblasts. This marker can be confirmed mainly by observing the presence of mRNA.

5

Myogenin (human: Accession No. BT007233; SEQ ID NOs. 13 and 14) is a marker specific to myoblasts. This marker can be confirmed mainly by observing the presence of mRNA.

10

In other embodiments, other markers specific to other tissues can be utilized. Examples of such markers include, but are not limited to, Oct-3/4, SSEA-1, Rex-1, Otx2, and the like for embryonic stem cells; VE-cadherin, Flk-1, Tie-1, PECAM1, vWF, c-kit, CD34, Thyl, Sca-1, and the like for endothelial cells; skeletal muscle α actin in addition to the above-described markers for skeletal muscles; Nestin, Glu receptor, NMDA receptor, GFAP, neuregulin-1, and the like for nerve cells; c-kit, CD34, Thyl, Sca-1, GATA-1, GATA-2, FOG, and the like for hematopoietic cells.

15
20

As used herein, the term "derived" in relation to cells means that the cells are separated, isolated, or extracted from a cell mass, tissue, or organ in which the cells have been originally present, or that the cells are induced from stem cells.

25

As used herein, the term "applicable to heart" means that the heart applied has an ability to pulsate. A tissue applicable to heart has strength such that the tissue can withstand dilation and contraction of the pulsating heart. Here, applicability to the heart includes applicability to the myocardium. Applicability to heart may be determined

30

by confirming that a recipient having an implanted graft survives.

As used herein, the term "three-dimensional structure" refers to an object which comprises cells having intracellular electrical connection and alignment and extends three-dimensionally. The term "three-dimensional structure" encompasses objects having any shape (e.g., sheet-shape, etc.). A sheet-shaped structure comprises a single layer or a plurality of layers.

As used herein, the term "cell sheet" refers to a structure comprising a monolayer of cells. Such a cell sheet has at least a two-dimensional biological connection. The sheet having biological connection is characterized in that after the sheet is produced, the connection between cells is not substantially destroyed even when the sheet is handled singly. Such biological connection includes intracellular connection via an extracellular matrix.

As used herein, the term "biological connection" in relation to the relationship between cells means that there is certain interaction between the cells. Examples of such interaction includes, but are not limited to, interaction via biological molecules (e.g., extracellular matrix), interaction via signal transduction, electrical interaction (electrical connection, such as synchronization of electrical signals or the like), and the like. In order to confirm interaction, an assay appropriate to a characteristic of the interaction is employed. In order to confirm physical interaction via biological molecules, the strength of a prosthetic tissue, a three-dimensional structure, or the like is measured (e.g., a tensile test). In order to confirm

interaction via signal transduction, gene expression or the like is investigated. In order to confirm electrical interaction, the electric potential of a prosthetic tissue, a three-dimensional structure, or the like is measured to
5 determine whether or not the electric potential is propagated with constant waves. Therefore, preferably, physical connection can be determined by observing whether or not the connection is established without a scaffold. In the present invention, it is typically sufficient that at least
10 a two-dimensional biological connection is provided. In a preferred embodiment, it is advantageous that a three-dimensional biological connection is provided. In this case, a three-dimensional structure may be formed. Preferably, there is biological connection substantially
15 uniformly in all directions in three-dimensional space. In another embodiment, the prosthetic tissue, a three-dimensional structure, and the like, which has substantially uniform two-dimensional biological connection and slightly weaker biological connection in the
20 third dimension, may be employed.

A prosthetic tissue, three-dimensional structure, or the like of the present invention may be provided using known preparation methods, as a pharmaceutical product, or
25 alternatively, as an animal drug, a quasi-drug, a marine drug, a cosmetic product, and the like.

Animals targeted by the present invention include any organism as long as it has organs (e.g., animals (e.g.,
30 vertebrates, invertebrate)). Preferably, the animal is a vertebrate (e.g., Myxiniiformes, Petronyzoniformes, Chondrichthyes, Osteichthyes, amphibian, reptilian, avian, mammalian, etc.), more preferably mammalian (e.g.,

monotremata, marsupialia, edentate, dermoptera, chiroptera, carnivore, insectivore, proboscidea, perissodactyla, artiodactyla, tubulidentata, pholidota, sirenia, cetacean, primates, rodentia, lagomorpha, etc.). Illustrative
5 examples of a subject include, but are not limited to, animals, such as cattle, pigs, horses, chickens, cats, dogs, and the like. More preferably, primates (e.g., chimpanzee, Japanese monkey, human, etc.) are used. Most preferably, a human is used. This is because there is limitation to
10 implantation therapies.

When the present invention is used as a pharmaceutical agent, it may further comprise a pharmaceutically acceptable carrier or the like. A pharmaceutically acceptable carrier
15 contained in a medicament of the present invention includes any material known in the art.

Examples of such a pharmaceutically acceptable carrier include, but are not limited to, antioxidants,
20 preservatives, colorants, flavoring agents, diluents, emulsifiers, suspending agents, solvents, fillers, bulking agents, buffers, delivery vehicles, agricultural or pharmaceutical adjuvants, and the like.

25 The amount of a pharmaceutical agent (e.g., a prosthetic tissue, a pharmaceutical compound used in conjunction therewith, etc.) used in the treatment method of the present invention can be easily determined by those skilled in the art with reference to the purpose of use,
30 a target disease (type, severity, and the like), the patient's age, weight, sex, and case history, the form or type of the cell, and the like. The frequency of the treatment method of the present invention applied to a subject (or patient)

is also determined by those skilled in the art with respect to the purpose of use, target disease (type, severity, and the like), the patient's age, weight, sex, and case history, the progression of the therapy, and the like. Examples of the frequency include once per day to several months (e.g., once per week to once per month). Preferably, administration is performed once per week to month with reference to the progression.

As used herein, the term "administer" in relation to a prosthetic tissue, three-dimensional structure, or the like of the present invention or a pharmaceutical agent comprising it, means that they are administered singly or in combination with other therapeutic agents. A prosthetic tissue of the present invention may be introduced into therapy sites (e.g., impaired heart, etc.) by the following methods, in the following forms, and in the following amounts. Examples of the introduction methods include, but are not limited to, direct attachment, suture after attachment, insertion, and the like. For example, a prosthetic tissue and a three-dimensional structure of the present invention may be applied by the above-described methods to an impaired site of ischemic myocardial tissue caused by myocardial infarct, angina pectoris, or the like. Combinations may be administered either concomitantly (e.g., as an admixture), separately but simultaneously or concurrently; or sequentially. This includes presentations in which the combined agents are administered together as a therapeutic mixture, and also procedures in which the combined agents are administered separately but simultaneously (e.g., a prosthetic tissue or the like is directly provided by operation, while other pharmaceutical agents are provided by intravenous injection). "Combination" administration

further includes the separate administration of one of the compounds or agents given first, followed by the second.

As used herein, the term "reinforcement" means that
5 the function of a targeted part of an organism is improved.

As used herein, the term "instructions" describe a method of administering a medicament, a method for diagnosis, or the like of the present invention for persons who administer,
10 or are administered, the medicament or the like or persons who diagnose or are diagnosed (e.g., physicians, patients, and the like). The instructions describe a statement indicating an appropriate method for administering a diagnostic, a medicament, or the like of the present invention.
15 The instructions are prepared in accordance with a format defined by an authority of a country in which the present invention is practiced (e.g., Health, Labor and Welfare Ministry in Japan, Food and Drug Administration (FDA) in the U.S., and the like), explicitly describing that the
20 instructions are approved by the authority. The instructions are so-called package insert and are typically provided in paper media. The instructions are not so limited and may be provided in the form of electronic media (e.g., web sites, electronic mails, and the like provided on the
25 Internet).

As used herein, the term "stimulus responsive macromolecule" refers to a macromolecule which changes its shape and/or property in response to a stimulus, i.e., the
30 changes occur between before and after the stimulus. Examples of such a stimulus include, but are not limited to, exposure to light, application of electric field, a change in temperature, a change in pH, addition of a chemical

substance, and the like. Examples of stimulus responsive macromolecules include, but are not limited to, poly(N-isopropylacrylamide), poly(N-isopropylacrylamide-acrylic acid) copolymer, 5 poly(N-isopropylacrylamide-methylmethacrylate) copolymer, poly(N-isopropylacrylamide-sodium acrylate) copolymer, poly(N-isopropylacrylamide-vinyl ferrocene) copolymer, γ ray-exposed poly(vinylmethylether) (PVME), poly(oxyethylene), a resin obtained by incorporating a 10 biological material (e.g., nucleic acid, etc.) into a macromolecule, and a gel obtained by cross-linking the above-described macromolecules with a cross-linking agent, and the like.

15 As used herein, the term "temperature responsive macromolecule" refers to a macromolecule which changes its shape and/or property in response to temperature. Examples of temperature responsive macromolecules include, but are not limited to, poly(N-isopropylacrylamide), 20 poly(N-isopropylacrylamide-acrylic acid) copolymer, poly(N-isopropylacrylamide-methylmethacrylate) copolymer, poly(N-isopropylacrylamide-sodium acrylate) copolymer, poly(N-isopropylacrylamide-vinyl ferrocene) copolymer, γ ray-exposed poly(vinylmethylether) (PVME), 25 poly(oxyethylene), and a gel obtained by cross-linking the above-described macromolecules with a cross-linking agent, and the like. Preferable examples of temperature responsive macromolecules include, but are not limited to, poly(N-isopropylacrylamide), 30 poly(N-isopropylacrylamide-methylmethacrylate) copolymer, poly(N-isopropylacrylamide-sodium acrylate) copolymer, and a gel obtained by cross-linking the above-described macromolecules with a cross-linking agent, and the like.

For example, a temperature responsive macromolecule used herein has an upper or lower critical solution temperature to water of from 0°C to 80°C. The present invention is not limited to this. The term "critical solution temperature" refers to a temperature threshold which changes a shape and/or property. Preferably, poly(N-isopropylacrylamide) may be herein used.

For example, γ ray-exposed polyvinylmethylether forms a hydrate at room temperature in aqueous solution which in turn swells. It is known that as the temperature is increased, the substance is dehydrated, so that the solution is contracted and turned into a heat-sensitive macromolecule gel. The PVME gel, which is uniform and transparent like a jelly, is turned cloudy (i.e., its transparency is changed) if it is heated. If the gel is provided with a porous structure or formed into fibers or particles, the gel can extend or contract at high speed. It is believed that a porous and fiber-like PVME gel can extend or contract for less than one second (see <http://www.aist.go.jp/NIMC/overview/v27-j.html>, Japanese Laid-Open Publication No. 2001-213992, and Japanese Laid-Open Publication No. 2001-131249). N-isopropylacrylamide gel (i.e., poly(N-isopropylacrylamide) is also known as a temperature responsive gel. If poly(N-isopropylacrylamide) is copolymerized with a hydrophobic monomer, the temperature which allows it to change its shape and/or property can be lowered. If poly(N-isopropylacrylamide) is copolymerized with a hydrophilic monomer, the temperature which allows it to change its shape and/or property can be raised. By utilizing this character, it is possible to prepare a filler responsive to a desired stimulus. Such a technique can be

applied to other temperature responsive macromolecules.

As used herein, the term "protein degrading enzyme" has the same meaning as commonly used in the art and refers to an enzyme which catalyzes the degradation of proteins. This enzyme is also referred to as "protease".

As used herein, the term "regular array film" refers to a film which has a structure in which elements are arrayed under a certain rule. Examples of the structure of such a film include, but are not limited to, honeycomb structure, line structure, dot structure, and the like. A prosthetic tissue of the present invention is preferably produced with such a regular array. The film can be made of a biodegradable material (e.g., poly-L-lactic acid (PLLA), etc.). In order to produce a stretchable film, poly(ϵ -caprolactone) (PCL) or the like can be used.

In cell engineering, tissue engineering, or the like, cell culture often requires base material for scaffolding cells. It is known that cell-to-cell interaction is affected by not only the chemical properties of cell surfaces but also the minute shape of cells. For the purpose of control of cellular functions, it is important to design both the chemical properties of material surfaces contacting cells and the minute structure of cells. It has been revealed that in porous films having honeycomb structure, the honeycomb pattern provides a cell adhesion surface and the porous structure provides access of cell supporting bases and supply routes of nutrients. Therefore, it is preferable to utilize honeycomb structure for the present invention.

The honeycomb structure film may be used as a base

to organize cells into a prosthetic organ or a prosthetic tissue, for example. Such a prosthetic organ or tissue or the like may be desired to be absorbed into the body. Therefore, the base is desirably absorbed into the body after
5 a certain period of time. Conventional materials, which have honeycomb structure, stably maintain the structure for a period of time required for cell culture, and thereafter degrade, are described in, for example, Japanese Laid-Open Publication No. 2001-157574, Japanese Laid-Open
10 Publication No. 2002-335949, and the like.

Japanese Laid-Open Publication No. 2001-157574 discloses a honeycomb structure and a film consisting of the honeycomb structure. The honeycomb structure is
15 obtained as follows. A hydrophobic organic solvent solution of a polymer consisting of 50 to 99 w/w% of a biodegradable polymer and 50 to 1 w/w% of an amphipatic polymer is cast on a substrate in atmosphere having a relative humidity of 50 to 95%, followed by gradual evaporation of the organic
20 solvent and concurrent dew condensation on the surface of the cast solution. Small dew drops caused by condensation are evaporated. As a result, a honeycomb structure is obtained. Japanese Laid-Open Publication No. 2002-335949 describes that the above-described film having a honeycomb
25 structure can be used to form a three-dimensional aggregation of orderly organized cells which is similar to biological tissue.

A film for use in the present invention is produced
30 as follows. A hydrophobic organic solvent solution of a single biodegradable and amphipatic polymer or a polymer mixture containing a biodegradable polymer and an amphipatic polymer is cast on a substrate, followed by evaporation of

the organic solvent and concurrent dew condensation on the surface of the cast solution. Small dew drops caused by condensation are evaporated.

5 In the present invention, a single biodegradable and amphipatic polymer may be used, or alternatively, a polymer mixture containing a plurality of polymers including biodegradable polymer(s) and amphipatic polymer(s) may be used.

10

As biodegradable polymers which can be used in the present invention, biodegradable aliphatic polyesters (e.g., poly(lactic acid), poly(hydroxybutyric acid), polycaprolactone, poly(ethylene adipate), poly(butylenes adipate), etc.), aliphatic polycarbonate (polybutylene carbonate, polyethylene carbonate, etc.), and the like are preferable in view of solubility to organic solvents. Particularly, poly(lactic acid) and polycaprolactone are desirable in view of availability, price, and the like.

20

Amphipatic polymers which can be used in the present invention are preferably nontoxic in view of use of them as a base material for cell culture. Examples of such amphipatic polymers include, but are not limited to, polyethylene glycol/polypropylene glycol block copolymer; an amphipatic polymer having an acrylamide polymer as a main chain (backbone structure), a dodecy group as a hydrophobic side chain, and a lactose group or a carboxyl group as a hydrophilic side chain; an ionic complex of an anionic macromolecule (e.g., heparin, dextran sulfate, nucleic acid (e.g., DNA, RNA, etc.), etc.) and a long chain alkylammonium salt; an amphipatic polymer having a water-soluble protein (e.g., gelatin, collagen, albumin, etc.) as a hydrophilic

30

group; and the like. Examples of a single biodegradable and amphipatic polymer include, but are not limited to, polylactic acid/polyethylene glycol block copolymer, poly(ϵ -caprolactone)/polyethylene glycol block copolymer, 5 poly(malic acid)/(an alkyl ester of polymalic acid) block copolymer, and the like.

As used herein, the term "impaired heart" and "impaired myocardium" refer to a heart and a myocardium, 10 respectively, having an impairment including, but being limited to, ischemic impairments and the like. Examples of ischemic impairments include, but are not limited to, myocardial infarct, angina pectoris, and the like.

15 As used herein, the term "three-dimensional promoting agent" refers to an agent which promotes biological connection in a third dimension after a group of cells are prepared. Examples of such an agent representatively include agents capable of promoting the secretion of a 20 cellularmatrix. Examples of a three-dimensional promoting agent include, but are not limited to, ascorbic acid or a derivative thereof (e.g., ascorbic acid 2-phosphate, ascorbic acid 1-phosphate, sodium L-ascorbate, etc.), and the like. Preferably, a three-dimensional promoting agent 25 may be preferably a component of an extracellular matrix of a part targeted by application and/or a component(s) capable of promoting the secretion of an extracellularmatrix in an amount similar thereto. When a three-dimensional promoting agent comprises a plurality of components, the 30 components may be components of an extracellular matrix of a part targeted by application and/or components capable of promoting the secretion of an extracellular matrix in an amount similar thereto.

As used herein, the term "ascorbic acid or a derivative thereof" includes ascorbic acid and an analog thereto (e.g., ascorbic acid 2-phosphate, ascorbic acid 1-phosphate, etc.), and a salt thereof (e.g., sodium salt, magnesium salt, etc.).

(Description of the Preferred Embodiments)

Hereinafter, preferred embodiments of the present invention will be described. The following embodiments are provided for a better understanding of the present invention and the scope of the present invention should not be limited to the following description. It will be clearly appreciated by those skilled in the art that variations and modifications can be made without departing from the scope of the present invention with reference to the specification.

According to one aspect of the present invention, a three-dimensional structure applicable to heart, which comprises a cell derived from a part other than the myocardium of an adult, is provided. Conventional three-dimensional structures applicable to heart comprise a cell derived from the myocardium of an adult, and have a small size and poor performance. The present invention is the first in the world to provide a three-dimensional structure applicable to heart, which comprises a cell derived from a part other than the myocardium of an adult (i.e., non-embryo), by culturing the cell derived from the part other than the myocardium of an adult under specific conditions (e.g., in the presence of a three-dimensional promoting agent, etc.). The three-dimensional structure comprises a cell, preferably substantially a cell and a component derived from the cell (e.g., an extracellular matrix, etc.). Thus, in a preferred

embodiment, the three-dimensional structure of the present invention comprises a biological material, and therefore, advantageously overcomes drawbacks due to a scaffold (e.g., poor biocompatibility, immunogenicity, etc.) as compared to conventional structures having a scaffold.

In one preferred embodiment, a cell contained in the three-dimensional structure of the present invention may include both a stem cell and a differentiated cell. In a preferred embodiment, a cell contained in the three-dimensional structure of the present invention is a mesenchymal cell. Though not wishing to be bound by any theory, the reason a mesenchymal cell is preferable is that the mesenchymal cell itself is excellently compatible to the heart, and may have an ability to differentiate into the heart tissue.

The above-described mesenchymal cell may be a mesenchymal stem cell or a differentiated mesenchymal cell.

Examples of a mesenchymal cell for use in the present invention include, but are not limited to, bone marrow, fat cells, synovial cells, and the like.

In a more preferred embodiment, a cell used in the present invention is preferably derived from a myoblast. Conventionally, it was not possible to expect that a three-dimensional structure comprising a myoblast is applicable to heart. This finding is an astonishing effect. The reason myoblasts are preferable is that, for example, the supply source thereof is abundant. The reason is not limited to this.

In a more preferred embodiment, a cell used in the present invention is a skeletal myoblast. Skeletal myoblasts are abundant, and therefore, are preferable as an easily available supply source. In addition, the present invention revealed for the first time the possibility that skeletal myoblasts can be implanted into a heart. Thus, skeletal myoblasts can be used in actual medical practice.

Thus, by appropriately culturing cells derived from parts other than the autologous myocardium, a defective heart can be repaired without implantation surgery.

In another embodiment, a cell used in the present invention may be a fibroblast. This is because fibroblasts can provide biological connection three-dimensionally in a three-dimensional structure. A three-dimensional structure comprising a fibroblast can be used in heart applications. Alternatively, such a three-dimensional structure comprising a fibroblast can be used for reinforcement in addition to heart applications.

In another embodiment, a cell used in the present invention may be a synovial cell. This is because synovial cells can provide biological connection three-dimensionally in a three-dimensional structure. A three-dimensional structure comprising a synovial cell can be used in heart applications. Alternatively, such a three-dimensional structure comprising a synovial cell can be used for reinforcement in addition to heart applications.

In another embodiment, a cell used in the present invention is derived from a stem cell. This is because a three-dimensional structure comprising a cell derived from

a stem cell can utilize a cell which is differentiated in a desired direction. Therefore, when the structure is applied to a heart, a stem cell which has been differentiated into a heart cell may be preferable. An exemplary method
5 for differentiation may employ LIF. The present invention is not limited to this.

In a preferred embodiment, a cell used in the present invention is advantageously a cell derived from a subject
10 to which a three-dimensional structure is applied. In this case, a cell used herein is also referred to as an autologous cell. By using autologous cells, immune rejection reactions can be prevented or reduced.

15 In another embodiment, a cell used in the present invention may be a cell not derived from a subject to which a three-dimensional structure is applied. In this case, a measure for preventing immune rejection reactions is preferably taken.

20 In another embodiment, a cell used in the three-dimensional structure of the present invention expresses at least one non-adult heart marker selected from the group consisting of myosin heavy chain IIa, myosin heavy
25 chain IIb, myosin heavy chain IIc(IIX), CD56, MyoD, Myf5, and myogenin. By utilizing such a non-adult heart marker, it is possible to confirm that the cell used in the three-dimensional structure is a non-adult heart-derived cell. The three-dimensional structure of the present
30 invention can avoid the use of the heart of an adult to significantly increase the potential of heart therapies.

The above-described non-adult heart marker is

expressed at a level which is typically possessed by a non-adult heart or a tissue thereof. For example, such a level may be at least about 50% of the naturally-occurring level of a non-adult heart or a tissue thereof, preferably at least about 60%, more preferably at least about 70%, more preferably at least about 80%, even more preferably at least about 90%, and still even more preferably at least about 100%. Examples of a technique for determining the level include, but are not limited to, PCR, blotting for determining the expression level of mRNA (e.g., Northern blotting, etc.), blotting for determining the expression level of a protein (e.g., Western blotting, etc.), and the like. PCR is utilized as follows. A specific primer is selected and designed from the above-described non-adult heart markers by using a method well known in the art (e.g., a commercially available PCR primer design device is used). Samples containing mRNA are extracted from a tissue or cell of interest. cDNA is prepared from mRNA using techniques well known in the art. cDNA is subjected to PCR cycles which allow detection of specific expression. The amplified products are subjected to, for example, electrophoresis, followed by staining. As a result, the expression level can be determined. Northern blotting is utilized as follows. The whole or a part of the nucleic acid sequence of the above-described non-adult heart marker is prepared as a probe (particularly, a sequence capable of specific detection). Samples containing mRNA are extracted from a tissue or cell of interest, followed by separation using electrophoresis. The above-described probe is used to detect expression. When a marker is involved in protein expression, antibodies specific to the protein are prepared. These antibodies are used in Western blotting to detect expression by utilizing antigen-antibody reactions.

In another embodiment, a cell used in the three-dimensional structure of the present invention contains substantially no adult heart marker. Based on the
5 fact that the cell contains substantially no adult heart marker, it is possible to confirm that the three-dimensional structure uses a non-adult heart-derived cell. The three-dimensional structure of the present invention can avoid the use of the heart of an adult to significantly increase
10 the potential of heart therapies.

The above-described adult heart marker is expressed at less than a level which is typically possessed by an adult heart or a tissue thereof. For example, such a level may
15 be less than about 100% of the naturally-occurring level of an adult heart or a tissue thereof, preferably less than about 80%, more preferably less than about 50%, even more preferably less than about 20%, still more preferably less than about 10%, and still even more preferably less than
20 about 5%.

In a preferred embodiment, a cell used in the three-dimensional structure of the present invention contains substantially no adult heart markers. By
25 confirming the absence of all adult heart markers, it is possible to more reliably confirm that the structure is not an adult heart. Note that not all adult heart markers are always checked.

30 Preferably, a cell used in the three-dimensional structure of the present invention is preferably a cell other than heart cells. Cells other than cardiomyocytes can be used in the present invention. However, cells derived from

a heart have a limited supply source, and cells derived from an autologous heart are substantially not available. Therefore, the use of cells not derived from a heart is preferable.

5

The three-dimensional structure of the present invention is typically applicable to heart, and may be applied to other organs. Preferably, the three-dimensional structure of the present invention may be applied to a myocardium.

10

In one embodiment, the three-dimensional structure of the present invention comprises a cell sheet having at least one layer. In a certain embodiment, the three-dimensional structure of the present invention comprises a cell sheet having only one layer. By providing a cell sheet, the intact or nonporous nature of the three-dimensional structure of the present invention is secured. Therefore, the three-dimensional structure of the present invention comprising a cell sheet having at least one layer is useful in applications in which an injured site is covered.

15

20

In a preferred embodiment, the three-dimensional structure of the present invention comprises a cell sheet having a plurality of layers. Preferably, it is advantageous that a plurality of layers in the cell sheet advantageously biologically connect one another. In this case, biological connection is preferably physical connection via an extracellular matrix, or electrical connection (e.g., pulsation, etc.). The connection varies depending on the desired site. When the three-dimensional structure of the present invention is intended to be implanted into a heart,

25

30

the biological connection typically includes electrical connection. Alternatively, the biological connection may be connection without a scaffold.

5 The three-dimensional structure of the present invention may be provided as a pharmaceutical agent. Alternatively, the three-dimensional structure of the present invention may be prepared by a medical practitioner or the like at an actual site. Alternatively, after a medical
10 practitioner prepares cells, a third party may culture the cells and prepare a three-dimensional structure comprising the cells, and employ it for surgery. In this case, cell culture can be carried out by those skilled in the art as well as medical practitioners. Therefore, those skilled in
15 the art can determine culture conditions depending on the type of cells and the target implantation site in accordance with the disclosure of the present specification.

 In another aspect of the present invention, a method
20 is provided for producing a three-dimensional structure applicable to adult heart, which comprises a cell derived from a part other than the heart. The method comprises the steps of: a) culturing a cell derived from a part other than the myocardium of an adult on a support comprising a
25 temperature responsive macromolecule; b) setting a culture temperature outside a critical solution temperature range of the temperature responsive macromolecule (above the upper limit, if any; or below the lower limit, if any); and
30 c) detaching the cultured cell as a three-dimensional structure. In this case, the cell derived from a part other than a myocardium may be a cell derived from a part other than a heart, including, for example, mesenchymal cells (e.g., myoblasts, skeletal myoblasts, synovial cells, fibroblasts,

etc.), and the like. Preferably, the upper limit or lower critical solution temperature to water is from 0°C to 80°C. A temperature responsive macromolecule having the above-described critical solution temperature is preferably grafted in the support.

In a preferred embodiment of the present invention, in the method for producing a three-dimensional structure, it is preferable that the structure is not treated with a protein degrading enzyme in or before the detaching step. In conventional methods for preparing cell sheets or the like, treatment using a protein degrading enzyme is performed so as to facilitate detachment. In this case, however, the cell sheet is injured, and therefore, cannot be used as a three-dimensional structure. In the method of the present invention, treatment using a protein degrading enzyme can be omitted, whereby an intact three-dimensional structure can be achieved.

In a preferred embodiment, the temperature responsive macromolecule is poly(N-isopropylacrylamide). Poly(N-isopropylacrylamide) has a lower limit critical solution temperature of a little more than 20°C. In this case, therefore, by changing culture medium from a typical culture temperature (e.g., about 37°C) to about 20°C, it is possible to easily prepare a three-dimensional structure. Thereby, a three-dimensional structure applicable to implantation surgery, which comprises a cell not derived from the myocardium of an adult, can be provided. As a result, a technique substantially other than organ transplantation can be provided to a number of diseases which can be treated only by conventional heart transplantation (e.g., dilated cardiomyopathy, etc.). That is, a therapy which cannot be

achieved by conventional techniques can be provided by the present invention.

5 In a more preferred embodiment, the three-dimensional structure of the present invention preferably comprises a three-dimensional organization promoting agent when cell culture is conducted. Such a three-dimensional organization promoting agent may be ascorbic acid or a derivative thereof.

10

In another aspect, the prosthetic tissue and three-dimensional structure of the present invention is free from injury caused by a protein degrading enzyme, such as, representatively, dispase, trypsin, or the like, during culture. Therefore, the prosthetic tissue and three-dimensional structure, which is detached from the base material, can be recovered as a cell mass holding proteins between cells (e.g., an extracellular matrix) and having a certain level of strength. The prosthetic tissue and three-dimensional structure also retain intact functions, such as a contraction/relaxation function, intracellular electrical connection, alignment, and the like which are specific to cardiomyocytes. In addition, the three-dimensional structure may have several characteristic, biological tissue-like, cell alignments (e.g., formation of a membrane consisting of connective tissue, formation of a lumen consisting of blood vessel endothelial cells, etc.). When typical protein degrading enzymes (e.g., trypsin, etc.) are used to detach the three-dimensional structure or prosthetic tissue, substantially no desmosome structure between cells, basement membrane-like proteins between cells and base materials, or the like are retained, so that cells are individually separated. Among these

15
20
25
30

protein degrading enzymes, dispase destroys basement membrane-like proteins between cells and base materials substantially completely, but not necessarily desmosome structure. The desmosome structure can be retained if the temperature is from 10°C to 60°C. In this case, however, the resultant three-dimensional structure or prosthetic tissue has weak strength. In contrast, the three-dimensional structure or prosthetic tissue of the present invention can retain 80% or more of each of the desmosome structure and the basement membrane-like protein, resulting in the above-described various effects. In the cell culture support, a temperature responsive polymer for use in coating the base material has an upper or lower limit critical solution temperature of from 0°C to 80°C in aqueous solution, and preferably from 20°C to 50°C. If the upper or lower limit critical solution temperature exceeds 80°C, cells are likely to be killed. If the upper or lower limit critical solution temperature is lower than 0°C, the cell growth rate is extremely low or cells are killed.

20

The temperature responsive polymer used in the present invention may be either a homopolymer or a copolymer. An example of such a polymer is a polymer described in, for example, Japanese Laid-Open Publication No. 2-211865, in addition to those described above. Specifically, for example, such a temperature responsive polymer is obtained by homo- or co-polymerization of the following monomers. Examples of usable monomers include, but are not limited to, (meth)acrylamide compounds, N-(or N,N-di)alkyl substituted (meth)acrylamide derivatives, or vinyl ether derivatives. In the case of copolymers, any two or more of these monomers can be used. Further, copolymers comprising monomers other than the above-described monomers, copolymers

30

obtained by graft- or co-polymerization of polymers, or a mixture of homopolymers and copolymers may be employed. Furthermore, polymers may be cross-linked to an extent such that the inherent properties of the polymer are not impaired.

5 Examples of the base material to be coated include, but are not limited to, materials typically used in cell culture (e.g., glass, modified glass, polystyrene, polymethylmethacrylate, etc.), substantially all materials capable of being generally shaped (e.g., macromolecule

10 compounds in addition to those described above, ceramics, etc.).

A method for coating a support with a temperature responsive polymer is not particularly limited and may be

15 performed in accordance with, for example, Japanese Laid-Open Publication No. 2-211865. Specifically, coating may be performed by subjecting a base material and the above-described monomer or polymer to electron beam irradiation (EB), γ ray irradiation, ultraviolet irradiation,

20 plasma treatment, corona treatment, or organic polymerization reaction, or physical adsorption or the like (e.g., application, crossing, etc.).

In the present invention, cell culture is conducted

25 on the above-described cell culture support (e.g., a cell culture dish, etc.). When the above-described polymer covering the surface of the base material has an upper limit critical solution temperature, the temperature of the medium is set to be equal to or lower than the upper limit critical

30 solution temperature. When the above-described polymer covering the surface of the base material has a lower limit critical solution temperature, the temperature of the medium is set to be equal to or higher than the lower limit critical

solution temperature. However, a low temperature range such that cultured cells cannot grow and a high temperature range such that cultured cells are killed is inappropriate. Culture conditions other than temperature may be those well
5 known in the art and are not particularly limited. For example, the medium may be supplemented with known fetal calf serum (FCS) or the like, or alternatively, serum-free medium without supplement of such a serum may be employed.

10 In the method of the present invention, the period of time required for culture may be determined depending on the application of the prosthetic tissue or three-dimensional structure. In order to detach and recover the cultured prosthetic tissue or three-dimensional
15 structure from the support material, the temperature of the support material having attached cells is increased on or above the upper limit critical solution temperature of a polymer covering the support base material, or is decreased on or below the lower limit critical solution temperature.
20 In this case, the cultured prosthetic tissue or three-dimensional structure is detached directly, or optionally with macromolecular membrane being attached thereto. Note that the prosthetic tissue or three-dimensional structure may be detached in culture medium
25 in which cells have been cultured, or alternatively, in other isotonic solutions. Such solutions may be selected depending on the purpose. Examples of the macromolecular membrane, which is optionally attached to the cell sheet or three-dimensional structure, include, but are not limited to, hydrophilized polyvinylidene difluoride (PVDF),
30 polypropylene, polyethylene, cellulose and derivatives thereof, chitin, chitosan, collagen, paper (e.g., Japan paper, etc.), urethane, net-like or stockinette -like

macromolecular materials (e.g., spandex, etc.), and the like. When a net-like or stockinette-like macromolecular material is employed, the prosthetic tissue or three-dimensional structure has a higher degree of freedom, so that the contraction/relaxation function thereof can be increased. A method for producing the prosthetic tissue or three-dimensional structure comprising cells of the present invention is not particularly limited. For example, the prosthetic tissue or three-dimensional structure of the present invention can be produced by utilizing the above-described cultured cell sheet attached to a macromolecular membrane.

In order to detach and recover the prosthetic tissue or three-dimensional structure with a high yield from the cell culture support, the cell culture support is tapped or shaken, or the medium is stirred with a pipette. These procedures may be performed singly or in combination. In addition, the prosthetic tissue or three-dimensional structure may be optionally rinsed with isotonic solution or the like before detaching and recovering. By stretching the prosthetic tissue or three-dimensional structure in a specific direction after being detached from the base material, the cell sheet or three-dimensional structure is provided with alignment. Stretching may be performed by using a tensile device (e.g., Tensilon, etc.), or simply forceps, or the like. A stretching method is not particularly limited. By providing alignment, it is possible to confer directionality to the motion of the cell sheet or three-dimensional structure itself. Therefore, for example, it is possible to allow the prosthetic tissue or three-dimensional structure to move in accordance with the motion of a specific organ. The prosthetic tissue or

three-dimensional structure can be efficiently applied to organs.

The thus-obtained prosthetic tissue or
5 three-dimensional structure cannot be obtained by
conventional techniques. The prosthetic tissue or
three-dimensional structure retains the basement membrane
which in conventional techniques is ruptured. Therefore,
the prosthetic tissue or three-dimensional structure can
10 be satisfactorily accepted by the surrounding tissue and
can pulsate *in situ* when it is buried in any part of an organism
(e.g., heart, bone, muscle, arm, shoulder, foot, and other
organs). Though not wishing to be bound by any theory, the
reason is believed to be as follows. The prosthetic tissue
15 or three-dimensional structure buried within an organism
is accepted by a biological tissue, and is contracted or
relaxed. In this case, the prosthetic tissue or
three-dimensional structure is in the low oxygen state. To
compensate the state, blood vessel endothelial cells
20 aggressively enter the prosthetic tissue or
three-dimensional structure from the surrounding biological
tissue. As a result, blood vessels are formed, so that
sufficient oxygen and nutrients can be supplied via blood.
Thus, the prosthetic tissue or three-dimensional structure
25 buried within an organism can form a functional tissue within
the organism. Such a prosthetic tissue or three-dimensional
structure is strongly expected to be used in clinical
applications, such as implantation and the like.
Specifically, the prosthetic tissue or three-dimensional
30 structure of the present invention can be used as a therapeutic
instrument for heart diseases (e.g., myocardial infarct,
etc.). In this case, for example, the prosthetic tissue or
three-dimensional structure is implanted to a site of a heart

which has a weak contraction force. Alternatively, the prosthetic tissue or three-dimensional structure may be applied around a blood vessel to improve circulation. For example, the prosthetic tissue or three-dimensional structure is useful as a therapeutic instrument for severe Raynaud's disease, a severe stiff shoulder, the dysfunction of the aorta, and the like. Note that a cell culture support for use in the present invention can be repeatedly used.

10 (Preparation of prosthetic tissue using three-dimensional promoting agent)

In another aspect, the present invention provides a method for producing a prosthetic tissue. The method for producing a prosthetic tissue comprises the steps of:
15 A) providing a cell; B) placing the cell in a container containing a cell culture medium including a three-dimensional promoting agent, wherein the container has a base with an area sufficient to accommodate a desired size of the prosthetic tissue; and C) culturing the cell
20 in the container for a period of time sufficient to form the prosthetic tissue having the desired size.

The above-described cell may be any cell. A method for providing a cell is well known in the art. For example, a tissue is extracted and cells are isolated from the tissue. Alternatively, cells are isolated from body fluid containing blood cells or the like. Alternatively, a cell line is prepared in an artificial culture. The present invention is not limited to this.

30

The method for producing a prosthetic tissue of the present invention employs a cell culture medium containing a three-dimensional promoting agent. Examples of such a

three-dimensional promoting agent include, but are not limited to, ascorbic acid or a derivative thereof, ascorbic acid 1-phosphate, ascorbic acid 2-phosphate, L-ascorbic acid, and the like.

5

The cell culture medium used in the present invention may be any medium which allows a cell of interest to grow. Examples of such a medium include, but are not limited to, DMEM, MEM, F12, DME, RPMI1640, MCDB104, 199, MCDB153, L15, SkBM, Basal medium, and the like which are supplemented with glucose, FCS (fetal calf serum), antibiotics (penicillin, streptomycin, etc.) as appropriate.

The container used in the present invention may be any container typically used in the art which has a base with an area sufficient to accommodate a desired size of the prosthetic tissue. Examples of such a container include, but are not limited to, petri dishes, flasks, mold containers, and the like, and preferably containers having a large area of the base (e.g., at least 1 cm²). The material of the container may be any material and include, but are not limited to, glass, plastic (e.g., polystyrene, polycarbonate, etc.), silicone, and the like.

In a preferred embodiment, the three-dimensional promoting agent used in the method for producing a prosthetic tissue of the present invention includes ascorbic acid 2-phosphate. Conventionally, it is known that ascorbic acid is used for cell culture. However, there was no report that ascorbic acid 2-phosphate is intentionally used for formation of tissue. In the present invention, by adding a certain amount of ascorbic acid 2-phosphate, it is possible to prevent an extracellular matrix from being produced in an excessively

30

large amount, the composition has an implantable level of extracellular matrices, and therefore, the ratio of the cell to the extracellular matrix results in an implantable level of strength and the like. These effects are unexpected.

5

In a preferred embodiment, ascorbic acid 2-phosphate used in the present invention typically has a concentration of at least 0.01 mM, preferably at least 0.05 mM, more preferably at least 0.1 mM, even more preferably at least 10 0.2 mM, still more preferably at least 0.5 mM, and still even more preferably 1.0 mM.

Alternatively, ascorbic acid 2-phosphate used in the present invention may be used in conjunction with ascorbic 15 acid 1-phosphate. In this case, ascorbic acid 1-phosphate and ascorbic acid 2-phosphate may be preferably used at a specific ratio. Such a preferable ratio is, for example, in the range of from 1:10 to 10:1. Alternatively, the preferable ratio is such that the molar amount of ascorbic 20 acid 1-phosphate is smaller than the molar amount of ascorbic acid 2-phosphate.

In another embodiment, the three-dimensional promoting agent used in the present invention includes 25 ascorbic acid 2-phosphate. However, there was no report that ascorbic acid 2-phosphate is explicitly used for formation of a tissue. In the present invention, by adding a certain amount of ascorbic acid 2-phosphate, it is possible to prevent an extracellular matrix from being produced in an excessively 30 large amount, the composition has an implantable level of extracellular matrices, and therefore, the ratio of cells to the extracellular matrix results in an implantable level of strength and the like. These effects are unexpected.

In a preferred embodiment, when the molar amount of ascorbic acid 1-phosphate is smaller than the molar amount of ascorbic acid 2-phosphate, ascorbic acid 2-phosphate used
5 in the present invention is typically present at a concentration of at least 0.01 mM, preferably at least 0.05 mM, more preferably at least 0.1 mM, even more preferably at least 0.2 mM, and still more preferably at least 0.5 mM, and still even more preferably 1.0 mM.

10

In a certain preferred embodiment, the three-dimensional promoting agent of the present invention includes ascorbic acid 1-phosphate or a salt thereof, ascorbic acid 2-phosphate or a salt thereof, and L-ascorbic
15 acid or a salt thereof.

The container used in a prosthetic tissue production method of the present invention is preferably coated with a temperature responsive macromolecule. In another
20 preferred embodiment, the container is preferably provided with a scaffold having a honeycomb structure. The present invention is not limited to this. Use of a honeycomb structure is described in, for example, Tanaka K. et al, "Atarashii Baiomedikaru Intafesu [New Biomedical
25 Interface]", Kagaku Kogyo [Chemical Industry], December 2002, 901-906, Kagaku Kogyo Sha.

The temperature responsive macromolecule which may be used in the prosthetic tissue production method of the
30 present invention, includes poly(N-isopropylacrylamide).

In a preferred embodiment, after the culturing step, the prosthetic tissue production method of the present

invention further comprises, D) detaching the prosthetic tissue and allowing the prosthetic tissue to perform self contraction. The detachment can be accelerated by applying a physical stimulus (e.g., applying a physical stimulus to a corner of the container, etc.). When a temperature responsive macromolecule is used, the detachment can be accelerated by changing the environment to a temperature higher or lower than the critical solution temperature of the temperature responsive macromolecule. Self-contraction naturally takes place after the detachment. By self-contraction, biological connection is accelerated particularly in the third dimension (the direction perpendicular to the two-dimensional directions in the case of tissue on a sheet). Therefore, a prosthetic tissue of the present invention may have a three-dimensional structure.

In a prosthetic tissue production method of the present invention, the sufficient time preferably means at least 3 days and may be more than or less than 3 days, though it varies depending on the application of a prosthetic tissue of interest. By 3-day culture, it is possible to prepare a graft which can be applied at least to the reinforcement of a heart.

In another aspect, the present invention provides a functional prosthetic tissue. The functional prosthetic tissue of the present invention is herein an implantable prosthetic tissue. Attempts have been heretofore made to produce prosthetic tissues by cell culture. However, there were no prosthetic tissues suitable for implantation in terms of size, strength, physical injuries when it is detached, or the like. The present invention provides a tissue culture method in which cells are cultured in the presence of a

three-dimensional promoting agent as described above, so that there is no problem in terms of size, strength, and the like and there is no difficulty in detaching tissues. An implantable prosthetic tissue is provided only after such
5 a tissue culture method is achieved. For diseases which are conventionally treated only by organ transplantation (e.g., refractory heart diseases (myocarditis, hypertrophic cardiomyopathy, dilated phase hypertrophic cardiomyopathy, dilated cardiomyopathy, etc.)), an alternative therapy
10 having general versatility is provided, which is of immeasurable usefulness.

A "disease" targeted by the present invention may be any heart disease in which tissue is injured. Examples
15 of such a heart disease include, but are not limited to, heart failure, myocardial infarct, cardiomyopathy, and the like. A combined therapy of the present invention may be applied to organs in addition to the heart as long as it aims the regeneration of injured tissues. In a specific
20 embodiment, a disease targeted by a method of the present invention is refractory heart failure.

The term "heart failure" refers to the inability of the heart to circulate blood in a required quantity and quality
25 to organs in the entire body due to an impairment of the heart itself, such as failure of cardiac functions, failure of circulatory functions, a reduction in contractile power, or the like. Heart failure is a terminal symptom of heart diseases, such as myocardial infarct, cardiomyopathy, and
30 the like. Severe heart failure means that the state of the heart is severe and is also referred to as terminal heart failure.

The term "refractory heart failure" refers to heart failure which is resistant to therapy and is difficult to ameliorate by medical therapy and drug therapy. The term "refractory heart failure" is substantially synonymically referred to as chronic heart failure or terminal heart failure. Refractory heart failure cannot be controlled by triple therapy using a typical Digitalis drug, diuretic, ACE inhibitor, and the like, or a drug therapy supplemented with a β -blocker. These therapies require a mechanical aid for circulation, such as IABP (intra-aortic balloon pumping), PCPS (percutaneous cardiopulmonary support), or the like, or alternatively, heart transplantation. Therefore, there was a demand for the development of a simple and radical therapy. Particularly, heart transplantation has a serious donor shortage problem. When heart transplantation cannot be used (e.g., elderly, patients in need of dialysis, etc.), refractory heart failure poses serious problems. Therefore, there is a keen demand for an alternative to heart transplantation therapy.

20

The term "myocardial infarct" refers to a disease in which ischemic necrosis occurs in a perfusion area associated with highly developed constriction or occlusion caused by various lesions of the coronary artery. The severity of myocardial infarct is divided into classes in various manners. Classification may be based on, for example, progress over time; morphology (e.g., the range, site, necrosis size, or the like within the myocardium); the necrosis form of a myocardium; the reconstruction of a ventricle after infarction; the dynamics of blood circulation (associated with therapy, prognosis, etc.); clinical severity; and the like. Myocardial infarct having a high level of severity is particularly called severe myocardial

30

infarct.

The term "cardiomyopathy" is a generic term for diseases caused by organic and functional abnormality in
5 amyocardium, which are divided into secondary cardiomyopathy following a basic disease (e.g., hypertension, dysbolism, ischemia, etc.), and spontaneous cardiomyopathy which develops without an apparent basic disease. As a
10 pathological change, myocardial hypertrophy, formation of fibrous tissue, degeneration, or the like is observed.

The term "dilated cardiomyopathy" refers to a functional failure of the left ventricle associated with the deflation thereof, and is also referred to as "congestive
15 cardiomyopathy". The term "dilated cardiomyopathy" may be abbreviated as "DCM". Dilated cardiomyopathy is associated with contraction failure, leading to chronic heart failure. Examples of a cause of dilated cardiomyopathy include various things, such as viral infection, gene mutation, and the like.
20 Generally, dilated cardiomyopathy does not include specific myocardial diseases (conventionally referred to as secondary myocardial diseases), such as ischemic cardiomyopathy caused by an unambiguous other cause, myocardial diseases associated with dysbolism or the like. However, these specific
25 myocardial diseases are also included within the scope of the present invention as long as the present invention has a therapeutic effect thereon. Most patients have a reduction in contractile power in the entire myocardium. It is also said that abnormality may occur in the motion of an isolated
30 portion of a wall. Typically, dilated cardiomyopathy has heart failure symptoms associated with congestion and sometimes has malaise due to low cardiac output. Dilated cardiomyopathy has no known cause and is an idiopathic

myocardial disease. The pathology of dilated cardiomyopathy mainly includes a reduction in contractile power of a myocardium, which leads to the dilation of the left ventricular cavity. The pathology also includes a
5 reduction in blood amount, an increase in left ventricular diastolic pressure, and the like. Dilated cardiomyopathy has acute or insidious onset and refractory heart failure at its end stage. Pathologically or histologically, the degeneration, formation of fibrous tissue, or atrophy of
10 myocardial tissue is diffusely or locally observed. Residual cardiomyocytes often cause hypertrophy. In addition to heart failure, severe arrhythmia or thromboembolism occurs, resulting in a very poor prognosis. Echocardiogram is particularly useful for diagnosis of
15 dilated cardiomyopathy, which demonstrates a diffuse reduction in wall motion, the thinning of a ventricular wall, and the dilation of a ventricular cavity. In addition, coronary angiography (coronary arterial lesion) and myocardial biopsy can be conducted to achieve a more reliable
20 diagnosis. Therefore, in the present invention, a test technique well known in the art, such as heart ultrasonography, a heart catheter test method, a nuclear medical test method (myocardial scintigraphy), myocardial biopsy, or the like, can be used to confirm an amelioration in dilated
25 cardiomyopathy.

Conventionally, for dilated cardiomyopathy, a drug therapy using an ACE inhibitor, a diuretic, a β -blocker, a cardiotonic drug, or the like; guidance in regulating the
30 intake of salt and water and exercise; and the like, are conducted. However, none of them cure the disease itself. For arrhythmia, an antiarrhythmic agent, such as amiodarone or the like, may be administered, which is however only a

symptomatic treatment. For thrombi and emboli, an anticoagulant, such as warfarin or the like, is used, which is however only a symptomatic treatment. As a surgical treatment, a pacemaker, a buried defibrillator, an assisted
5 circulation device (bypass), heart transplantation, or the like is used. However, these treatments other than heart transplantation cannot be said to eradicate the disease. At present, serious donor shortage limits heart transplantation. A therapeutic technique of the present
10 invention is effective for dilated cardiomyopathy and the like and provides an advantageous therapeutic effect.

The term "hypertrophic cardiomyopathy" (HCM) refers to a type of cardiomyopathy whose main symptom is a reduction
15 in diastolic compliance due to an abnormal enlargement of a myocardium and left ventricle hypertrophy. The contractile function of the heart is typically retained. The 5-year and 10-year survival rates are satisfactorily about 90% and about 80%, respectively. However,
20 hypertrophic cardiomyopathy is believed to be a cause of sudden death, which poses a clinical problem. Therefore, there is a demand for a radical therapy for the disease. A therapeutic technique of the present invention is also effective to hypertrophic cardiomyopathy and provides an
25 advantageous therapeutic effect.

The term "dilated phase hypertrophic cardiomyopathy" refers to a type of hypertrophic cardiomyopathy in which the formation of fibrous tissue is
30 developed in a myocardium in the course of the disease, leading to the thinning of a ventricular wall and a reduction in contractile power, and as a result, a ventricular cavity is enlarged, so that a symptom of dilated cardiomyopathy

appears. Dilated phase hypertrophic cardiomyopathy is said as having a very poor prognosis. There are a number of subclinical cases, posing a clinical problem. Therefore, there is also a demand for a radical therapy for dilated
5 phase hypertrophic cardiomyopathy. A therapeutic technique of the present invention is effective for dilated phase hypertrophic cardiomyopathy and the like and provides an advantageous therapeutic effect.

10 Conventional therapies and diagnostic techniques for refractory heart failure or the like as described above are described in, for example, "Junkanki Shikkan Saishin no Tiryo [Latest Therapy for Circulatory Diseases] 2002-2003, Shigetake Sasayama and Yoshio Yazaki editors, Nankodo, 2002,
15 and the like. As described in "Junkanki Shikkan Saishin no Tiryo [Latest Therapy for Circulatory Diseases] 2002-2003, Shigetake Sasayama and Yoshio Yazaki editors, Nankodo, 2002, which was most recently published, there was no radical therapy for refractory heart failure. The present invention
20 is the first to provide a therapy for the above-described heart diseases, particularly refractory heart failure.

As used herein, the term "prophylaxis" or "prevention" in relation to a certain disease or disorder
25 refers to a treatment which keeps such a condition from happening before the condition is caused, or causes the condition to occur at a reduced level or to be delayed.

As used herein, the term "therapy" in relation to
30 a certain disease or disorder means that when such a condition occurs, such a disease or disorder is prevented from deteriorating, preferably is retained as it is, more preferably is diminished, and even more preferably

extinguished. As used herein, the term "radical therapy" refers to a therapy which eradicates the root or cause of a pathological process. Therefore, when a radical therapy is made for a disease, there in principle is no recurrence
5 of the disease.

As used herein, the term "prognosis" is also referred to as "prognostic treatment". The term "prognosis" in relation to a certain disease or disorder refers to a diagnosis
10 or treatment of such a condition after a therapy.

In a preferred embodiment, the prosthetic tissue of the present invention has a three-dimensional, biological connection. As described in other portions of the
15 specification, examples of biological connection include, but are not limited to, physical connection via extracellular matrices, electrical connection, and the like. In the present invention, physical connection via extracellular matrices is particularly important in view of the strength
20 of tissue.

In one embodiment, the prosthetic tissue of the present invention is different from conventional prosthetic tissues in that the former comprises a cell.
25

Preferably, a prosthetic tissue of the present invention consists substantially of a cell or a material derived from the cell. Since the prosthetic tissue is composed substantially of only a cell and a cell-derived
30 material (e.g., extracellular matrix, etc.), the prosthetic tissue can have an increased level of biocompatibility and affinity. The cell-derived material representatively includes extracellular matrices. Particularly, the

prosthetic tissue preferably comprises a cell and an extracellular matrix at an appropriate ratio thereof. Such an appropriate ratio of a cell and an extracellular matrix is from about 1:9 to about 9:1, preferably about 3:7 to about 7:3, and more preferably about 3:7 to about 5:5. A preferable ratio varies depending on the purpose. Such variations may be prepared by those skilled in the art. An appropriate ratio can be estimated by investigating the ratio of a cell and an extracellular matrix in an organ of interest.

10

In another embodiment, the prosthetic tissue of the present invention is preferably isolated. In this case, the term "isolate" means that the prosthetic tissue is separated from a scaffold, a support, and a culture medium used in culture. If a prosthetic tissue of the present invention is substantially free from materials, such as a scaffold and the like, it is possible to suppress adverse reactions after implantation, such as immune rejection reactions, inflammation reactions, and the like.

20

In another embodiment, the prosthetic tissue of the present invention is preferably intact. An intact prosthetic tissue can be provided substantially only after the prosthetic tissue production method of the present invention using a three-dimensional promoting agent is provided. Conventionally, when a prosthetic tissue is detached from the culture environment, a physical stimulus is necessarily applied to the tissue, so that the tissue is unavoidably hurt. Therefore, an attempt has been made to compile a plurality of cell sheets prepared by conventional methods. However, such a multilayer of cell sheets cannot be easily used for actual implantation. Therefore, such a problem is overcome by the intactness of the prosthetic tissue

30

of the present invention.

In a preferred embodiment, the prosthetic tissue of the present invention has a large size. The term "large size" in relation to a prosthetic tissue typically means that the prosthetic tissue has an area sufficient to cover a site to which the prosthetic tissue is implanted. Such an area is, for example, at least 1 cm², more preferably at least 2 cm², at least 3 cm², at least 4 cm², even more preferably at least 5 cm², and still even more preferably at least 6 cm².

In a preferred embodiment, the prosthetic tissue of the present invention is thick. The term "thick" in relation to a prosthetic tissue typically means that the prosthetic tissue has a thickness which provides a strength sufficient to cover a site to which the prosthetic tissue is implanted. Such a thickness is, for example, at least about 50 μm, more preferably at least about 100 μm, at least about 200 μm, at least about 300 μm, even more preferably at least about 400 μm, still more preferably at least about 500 μm, and still even more preferably about 1 mm.

A prosthetic tissue of the present invention is preferably imperforate. The imperforate prosthetic tissue is suitable for implantation. The imperforate prosthetic tissue is particularly preferable for reinforcement of a defective site of a bag-shaped tissue which needs to be covered.

In another embodiment, the prosthetic tissue of the present invention is flexible. Due to the flexibility, the prosthetic tissue is particularly suitable for reinforcement of motile organs. Examples of motile organs include, but

are not limited to, hearts, blood vessels, muscles, and the like.

In another embodiment, the prosthetic tissue of the present invention has dilation/contraction ability. Due to the dilation/contraction ability, the prosthetic tissue is suitable for organs which expand and contract, including, for example, hearts, muscles, and the like. The dilation/contraction ability cannot be achieved by cell sheet or the like prepared by conventional methods. Preferably, a prosthetic tissue of the present invention has a sufficient strength to withstand the pulsation motion of a heart. The strength sufficient to withstand pulsation motion is, but is not limited to, at least about 50% of the strength of naturally-occurring myocardium, preferably at least about 75%, and more preferably at least about 100%.

In a preferred embodiment, the prosthetic tissue of the present invention has biological connection in all three dimensions. There are some prosthetic tissues prepared by conventional methods, which have biological connection in two dimensions to some degree. However, no tissue having biological connection in all three dimensions can be prepared by conventional methods. Therefore, since the prosthetic tissue of the present invention has biological connection in all three dimensions, the prosthetic tissue is substantially implantable in any application.

Examples of biological connection which is an indicator of a prosthetic tissue of the present invention, include, but are not limited to, interconnection of extracellular matrices, electrical connection, the presence of intracellular signal transduction, and the like. The

interaction of extracellular matrices can be observed with a microscope by staining intracellular adhesion as appropriate. Electrical connection can be observed by measuring electric potential.

5

In a preferred embodiment, the prosthetic tissue of the present invention has a sufficient tissue strength for clinical applications. The sufficient tissue strength for clinical applications varies depending on a site to which the prosthetic tissue is applied. Such a strength can be determined by those skilled in the art with reference to the disclosure of the specification and techniques well known in the art. For example, in a preferred embodiment, a strength required by the present invention is at least 80% of the tissue strength of a portion targeted by a clinical application.

10

15

20

In a specific embodiment, the above-described portion targeted by a clinical application includes the heart, and in some cases, portions other than the heart.

25

30

In another aspect, the present invention provides a cell culture composition for producing prosthetic tissue from a cell. The cell culture composition contains an ingredient (e.g., commercially available medium, etc.) for maintaining or growing the cell, and a three-dimensional promoting agent. The three-dimensional promoting agent has been described in detail in the above description of the prosthetic tissue production method. Therefore, the three-dimensional promoting agent includes ascorbic acid or a derivative thereof (e.g., ascorbic acid 1-phosphate or a salt thereof, ascorbic acid 2-phosphate or a salt thereof, L-ascorbic acid or a salt thereof, etc.). The culture

composition of the present invention contains ascorbic acid 2-phosphate or a salt thereof at a concentration of at least 0.1 mM. Alternatively, in the case of a condensed culture composition, the condensed culture composition contains
5 ascorbic acid 2-phosphate or a salt thereof at a concentration which becomes at least 0.1 mM after preparation. Alternatively, the lower limit concentration of ascorbic acid 2-phosphate or a salt thereof may be 0.01 mM, 0.05 mM, 0.2 mM, or 0.3 mM, even more preferably 0.5 mM, or
10 alternatively 1.0 mM.

In a preferred embodiment, the three-dimensional promoting agent contained in the cell culture composition of the present invention includes ascorbic acid 1-phosphate
15 or a salt thereof and ascorbic acid 2-phosphate or a salt thereof.

Ascorbic acid 2-phosphate used in the present invention is used concomitantly with ascorbic acid
20 1-phosphate. In this case, ascorbic acid 1-phosphate and ascorbic acid 2-phosphate may be preferably present at a specific ratio. Such a preferable ratio is, for example, in the range of from 1:10 to 10:1. Alternatively, the preferable ratio is such that the molar amount of ascorbic
25 acid 1-phosphate is smaller than the molar amount of ascorbic acid 2-phosphate.

In another embodiment, the three-dimensional promoting agent used in the present invention includes
30 ascorbic acid 2-phosphate. However, there was no report that ascorbic acid 2-phosphate is explicitly used for formation of a tissue. In the present invention, by adding a certain amount of ascorbic acid 2-phosphate, it is possible to prevent

an extracellular matrix from being produced in an excessively large amount, the composition has an implantable level of extracellular matrices, and therefore, the ratio of the cell to the extracellular matrix results in an implantable level of strength and the like. These effects are unexpected.

In a preferred embodiment, ascorbic acid 2-phosphate used in the present invention is typically present at a concentration of at least 0.01 mM, preferably at least 0.05 mM, more preferably at least 0.1 mM, even more preferably at least 0.2 mM, and still more preferably at least 0.5 mM, and still even more preferably 1.0 mM.

In a certain preferred embodiment, the three-dimensional promoting agent of the present invention includes ascorbic acid 1-phosphate or a salt thereof, ascorbic acid 2-phosphate or a salt thereof, and L-ascorbic acid or a salt thereof.

(Prosthetic tissue for "wrapping")

In another aspect, the present invention provides a prosthetic tissue for reinforcement of a portion of an animal organism. The prosthetic tissue capable of such reinforcement is a technique achieved only after the prosthetic tissue production method of the present invention is provided.

In a preferred embodiment, the above-described portion includes bag-shaped organs. For bag-shaped organs, it is important for the prosthetic tissue to possess intactness and/or nonporousness. A prosthetic tissue having such a property and a certain size cannot be provided by conventional techniques. Therefore, it can be said that

a substantial therapy for bag-shaped organs can be achieved only after the above-described prosthetic tissue of the present invention is provided. Therefore, for bag-shaped organs which have specific diseases (e.g., refractory diseases (e.g., dilated cardiomyopathy, etc.), etc.), a
5 therapy can be first provided other than organ transplantation.

In a specific embodiment, examples of the
10 above-described bag-shaped organ include, but are not limited to, hearts, livers, kidneys, and the like.

In a specific embodiment of the present invention, the above-described reinforcement may be achieved by
15 disposing a prosthetic tissue of the present invention to cover the above-described portion. It is not possible to use a prosthetic tissue provided by conventional methods to perform treatment by covering the above-described portion (i.e., "wrapping" application). Thus, the prosthetic
20 tissue of the present invention can provide applications which cannot be achieved by conventional techniques.

Therefore, in the above-described specific embodiment, the prosthetic tissue of the present invention
25 is resistant to dilation/contraction of the above-described portion.

In a preferred embodiment, the prosthetic tissue of the present invention advantageously has biological
30 connection.

In another preferred embodiment, the biological connection includes at least one of interconnection of

extracellular matrices, electrical connection, and intracellular signal transduction.

5 In another preferred embodiment, the prosthetic tissue for reinforcement of the present invention is formed by culturing a cell in the presence of a three-dimensional promoting agent.

10 In another embodiment, the prosthetic tissue for reinforcement of the present invention comprises a cell (autologous cell) derived from an animal to be treated (e.g., a human). More preferably, a prosthetic tissue for reinforcement of the present invention comprises only a cell(s) (autologous cell) derived from an animal to be treated
15 (e.g., a human).

("Wrapping" therapy)

In another aspect, the present invention provides a method for reinforcement of a portion of an animal organism.
20 The method comprises the steps of: A) disposing a prosthetic tissue to cover the portion; and B) holding the prosthetic tissue for a time sufficient to connect to the portion. The step of disposing the prosthetic tissue to cover the portion can be carried out using a technique well known in the art.
25 The sufficient time varies depending on a combination of the portion and the prosthetic tissue, and can be easily determined as appropriate by those skilled in the art depending on the combination. Examples of such a time include, but are not limited to, 1 week, 2 weeks, 1 month, 2 months,
30 3 months, 6 months, 1 year, and the like. In the present invention, a prosthetic tissue preferably comprises substantially only cell(s) and material(s) derived from the cell. Therefore, there is no particular material which needs

to be extracted after operation. The lower limit of the sufficient time is not particularly important. In this case, it can be said that the longer the time, the more preferable the prosthetic tissue. If the time is sufficiently extremely long, it can be said that reinforcement is substantially completed. Therefore, the time is not particularly limited.

In another embodiment, in a reinforcement method of the present invention, the above-described portion preferably includes bag-shaped organs (e.g., hearts, livers, kidneys, etc.). In order to reinforce such a bag-shaped tissue, it is necessary to wrap the organ (e.g., cover an injured portion. A prosthetic tissue resistant to wrapping applications is first provided by the present invention. Therefore, the reinforcement method of the present invention is advantageous over conventional techniques.

Particularly, in the reinforcement method of the present invention, a prosthetic tissue of the present invention is resistant to dilation/contraction of the above-described portion. Examples of such dilation/contraction include, but are not limited to, the pulsation motion of a heart, the contraction of a muscle, and the like.

In another preferred embodiment, in the reinforcement method of the present invention, a prosthetic tissue of the present invention has biological connection (e.g., interconnection of extracellular matrices, electrical connection, intracellular signal transduction, etc.). The biological connection is preferably provided in all three dimensions.

In another preferred embodiment, the reinforcement method of the present invention further comprises culturing a cell in the presence of a three-dimensional promoting agent to form a prosthetic tissue of the present invention. An
5 implantation/regeneration technique using the method which comprises the step of culturing a cell in the presence of a three-dimensional promoting agent cannot be provided by conventional techniques. The method provides a therapy for diseases (e.g., refractory heart diseases (e.g., dilated
10 cardiomyopathy, etc.), etc.), which cannot be achieved by conventional therapies.

In a preferred embodiment, in the reinforcement method of the present invention, the cell used in the
15 prosthetic tissue of the present invention is derived from an animal to which the prosthetic tissue is to be implanted (i.e., an autologous cell). By using an autologous cell, adverse side effects, such as immune rejection reactions or the like, can be avoided.

20 In another preferred embodiment, the portion is a heart. The heart has a disease or disorder, such as heart failure, ischemic heart disease, myocardial infarct, cardiomyopathy, myocarditis, hypertrophic cardiomyopathy,
25 dilated phase hypertrophic cardiomyopathy, dilated cardiomyopathy, or the like.

For some organs, it is said that it is difficult to radically treat a specific disease, disorder, or condition
30 thereof (e.g., refractory heart diseases). However, the present invention provides the above-described effect, thereby making possible a treatment which cannot be achieved by conventional techniques. It has been clarified that the

present invention can be applied to radical therapy. Therefore, the present invention has usefulness which cannot be achieved by conventional medicaments.

5 (Combined therapy)

In another aspect, the present invention provides a regeneration therapy which uses a cytokine, such as HGF or the like, in combination with a prosthetic tissue.

10 Cytokines used in the present invention are already commercially available (e.g., HGF-101 from Toyo Boseki, etc.). However, these cytokines can be prepared by various methods and can be used in the present invention if they are purified to an extent which allows them to be used as a medicament.

15 HGF can be obtained as follows: primary cultured cells or an established cell line capable of producing HGF is cultured; and HGF is separated from the culture supernatant or the like, followed by purification. Alternatively, a gene encoding HGF is incorporated into an appropriate vector by

20 a genetic engineering technique; the vector is inserted into an appropriate host to transform the host; recombinant HGF of interest can be obtained from the supernatant of the transformed host culture (e.g., Nature, 342, 440(1989); Japanese Laid-Open Publication No. 5-111383;

25 Biochem-Biophys. Res. Commun., 163, 967 (1989), etc.). The above-described host cell is not particularly limited and can be various host cells conventionally used in genetic engineering techniques, including, for example, *Escherichia coli*, yeast, animal cells, and the like. The thus-obtained

30 HGF may have one or more amino acid substitutions, deletions and/or additions in the amino acid sequence as long as it has substantially the same action as that of naturally-occurring HGF. Examples of a method for

introducing HGF into patients in the present invention include, but are not limited to, a Sendai virus (HVJ) liposome method with high safety and efficiency (Molecular Medicine, 30, 1440-1448(1993); Jikken Igaku (Experimental Medicine), 5 12, 1822-1826 (1994)), an electrical gene introduction method, a shotgun gene introduction method, and the like. Preferably, the HVJ liposome method is used.

Hereinafter, the present invention will be described
10 by way of examples. Examples described below are provided only for illustrative purposes. Accordingly, the scope of the present invention is not limited except as by the appended claims.

15 EXAMPLES

In the examples below, animals were treated in accordance with rules defined by Osaka University (Japan) and were cared for in the spirit of animal protection.

20 (Example 1: Production and utilization of prosthetic tissue and three-dimensional structure made of cardiomyocyte sheet - tissue engineered contractile cardiomyocyte sheet regenerates impaired myocardium -)

25 (Bioengineered contractile cardiomyocyte sheet regenerates infarcted myocardium)

In Example 1, the present inventors investigated
30 (1) whether or not a cardiomyocyte sheet (prosthetic tissue) survives after implantation and shows histological electrical connection with impaired myocardium; (2) whether or not the implanted cardiomyocyte sheet (prosthetic tissue) can induce an improvement in a cardiac function. As a result,

it was demonstrated that the present invention provides the electrical connection and the improvement of cardiac function.

5 The present inventors introduced the concept of
bioengineered tissue implantation into the treatment of
impaired myocardium. It was demonstrated that a tissue
engineered contractile cardiomyocyte sheet without a
scaffold provides histological electrical connection with
10 impaired myocardium and regeneration of an infarcted
myocardium.

(Materials and methods)

(Myocardial infarct model)

15 30 male Lewis rats (300 g, 8 weeks old; Seac Yoshitomi
Ltd, Fukuoka, Japan) were used in this study. Humane animal
care complied with "Principles of Laboratory Animal Care"
prepared by the National Society for Medical Research and
"Guide for the Care and Use of Laboratory Animals" (NIH
20 Publication, No. 86-23, 1985, revised) prepared by the
Institute of Laboratory Animal Resource and published by
the National Institute of Health. Acute myocardial infarct
was induced as described in Weisman H.F., Bush D.E., Mannisi
J.A., et al., Cellular Mechanism of Myocardial Infarct
25 Expansion, Circulation, 1988; 78: 186-201. Briefly, the
rats were anesthetized with sodium pentobarbital, followed
by positive pressure breathing through an endotracheal tube.
A left 4th intercostal space thoracotomy was used and the
left anterior descending coronary artery (LAD) was
30 completely ligated with an 8-0 polypropylene thread at a
distance of 3 mm from the root of the LAD.

(Preparation of rectangle-designed PIPAAm grafted

polystyrene cell culture dishes)

A rectangle-designed PIPAAm grafted cell culture dish was prepared with a specific procedure as described in, for example, Okano T., Yamada N., Sakai H., Sakurai Y., J. Biomed. Mater. Res., 1993; 27:1243-1251. Briefly, an
5 IPAAm monomer solution in 2-propanol (kindly provided by Kohjin, Tokyo, Japan) was spread onto tissue culture polystyrene (TCPS) dishes (Falcon 3002, Becton Dickinson). Thereafter, these dishes were subject to irradiation
10 (electron beam dose: 0.25 MGy) using an Area Beam Electron Processing System (Nisshin High Voltage), resulting in polymerization of IPAAm and covalent bonding of IPAAm to the dish surface. The PIPAAm grafted dishes were rinsed with cold distilled water to remove non-grafting IPAAm, followed
15 by drying the dishes in nitrogen gas. In the second step, the PIPAAm grafted surface was masked with a rectangular coverglass (24×24 mm, Matsunami, Tokyo, Japan). Acrylamide (AAm) monomer solution of 2-propanol was spread onto the surface of the masked dish. Thereafter, the dish surface
20 was electron beam irradiated and washed. As a result, the rectangular region at the center of each dish was PIPAAm-grafted (temperature responsive), while the surrounding border was poly-AAm grafted (non-cell adhesive). The rectangle-designed PIPAAm grafted dish was sterilized
25 with ethylene oxide gas before use in culture.

(Primary culture of newborn rat ventricular muscle cells)

Primary newborn rat cardiomyocytes were prepared in
30 accordance with a procedure previously described in, for example, Shimizu T., Yamato M., Akutsu T. et al., Circ. Res., Feb 22, 2002; 90(3):e40. Briefly, 1 to 2 day old newborn rats were sacrificed while deeply anesthetized, and the

hearts were rapidly removed, followed by digestion with Hanks solution containing collagenase (class II, Worthington Biochemical) at 37°C. The isolated cells were suspended in culture medium containing 6% FCS, 40% Medium 199 (Gibco BRL),
5 0.2% penicillin-streptomycin solution, 2.7 mmol/L glucose, and 54% balanced salt solution (116 mmol/L NaCl, 1.0 mmol/L NaH₂PO₄, 0.8 mmol/L MgSO₄, 1.18 mmol/L KCl, 0.87 mmol/L CaCl₂, and 26.2 mmol/L NaHCO₃). The cell suspension was plated at a density of 8×10⁶ cells/dish, followed by incubation in a
10 humidified atmosphere containing 5%CO₂ at 37°C.

(Primary culture of fibroblasts)

Primary fibroblasts were prepared in accordance with a procedure previously published in, for example,
15 Yablonka-Reuveni Z., Nameroff M., Skeletal Muscle Cell Populations Separation and Partial Characterization of Fibroblast-Like Cells from Embryonic Tissue Using Density Centrifugation, Histochemistry, 1987; 87:27-38. Briefly, a suspension of cells derived from leg muscle of 8 week old
20 Lewis rats was separated into fibroblasts and muscle cells by Percoll™ density centrifugation (Amersham Biosciences Sweden). The isolated fibroblasts were used for a control fibroblast sheet.

25 (Production of cardiomyocyte sheet)

The isolated cardiomyocytes of the newborn rat were cultured on the rectangle-designed PIPAAm grafted polystyrene cell culture dish. By lowering the temperature to 20°C, the cells were detached as a rectangular cell sheet.
30 Two cardiomyocyte sheets were piled up to produce a thicker heart graft. Cross sectional observation of the double-layered cardiac sheet demonstrated intimate connection and homogenous heart-like tissue. Synchronous

motion of a four-layer cardiomyocyte sheet was detected by the naked eye (data not shown). In the case of the fibroblast sheet, isolated fibroblasts were cultured on the same dish for 2 days, and were detached as a rectangular cell sheet
5 by the same method.

(Implantation of cardiomyocyte sheet)

The cardiomyocyte sheet was implanted into Lewis rats 2 weeks after LAD ligation. Specifically, a left 4th
10 intercostal space thoracotomy was performed on the rat under general anesthetization. The infarct region was visually identified based on the surface scar and the abnormal wall motion. The cardiomyocyte sheet or the fibroblast sheet was implanted into an infarcted myocardium. A control group was
15 not treated.

The cardiac function was evaluated 2 weeks, 4 weeks, and 8 week after implantation. 8 weeks after implantation, the heart was collected and sectioned, and processed for
20 histological and immunohistological tests.

In order to identify the implanted cardiomyocyte sheet, EGFP newborn rat cardiomyocytes were isolated with the same protocol, and a cardiomyocyte sheet was prepared.
25 The present inventors implanted the EGFP newborn rat cardiomyocyte sheet into an infarcted myocardium of nude rats. The present inventors could detect EGFP positive cardiomyocytes in the infarcted myocardium (Figure 6, lower left portion and lower right portion).

30

(Measurement of cardiac function of rat heart)

Rats were anesthetized with sodium pentobarbital. Anesthetization was supplemented with ethanol to maintain

- 111 -

light anesthetization. The rats were lightly secured in a supine position and the precordia of the rats were shaved. Heart ultrasonography was performed using a commercially available echocardiograph SONOS 5500 (PHILIPS Medical Systems, USA). A 12-MHz annular array transducer was placed on an acoustic coupler gel layer applied onto the left hemithorax. The transducer was carefully made to have adequate contact with the thorax while avoiding an excessive level of pressure on the thorax. The rats were imaged in a shallow left lateral decubitus position. The heart was first imaged in a two-dimensional mode in a short axis cross section at a level of the greatest left ventricle (LV) diameter. The systolic left ventricle (LV) area and the diastolic left ventricle (LV) area were determined at the same time. The volume of the left ventricle (LV) was estimated based on a short axis area of the left ventricle (LV) (Gorcsan J. 3rd, Morita S., Mandarino W.A., Deneault L.G., Kawai A., Kormos R.L., Griffith B.P., Pinsky M.R., Two-dimensional Echocardiographic Automated Border Detection Accurately Reflects Changes in Left ventricular Volume, J. Am. Soc. Echocardiogr., 1993; 6: 482-9). The resultant image was used to locate an Mmode cursor perpendicular to the left ventricle (LV) anterior wall and the left ventricle (LV) posterior wall. All measurements are performed online using a monitor. Diastolic measurements were performed at the time of an apparent maximum left ventricle (LV) diastolic dimension. A left ventricle (LV) endsystolic dimension was measured at the time of the most anterior systolic excursion of the left ventricle (LV) posterior wall. The left ventricle (LV) dimension in diastole (LVDD) and the left ventricle (LV) dimension in systole were measured. Dimension data and area data were represented by an average of measured values of two or three selected beats. A left ventricle (LV) ejection

fraction (EF) was calculated by:

$$\text{LVEF(\%)} = [(\text{LVDD}^3 - \text{LVDS}^3)/\text{LVDD}^3] \times 100.$$

5 LV% fractional shortening (FS) was calculated by:

$$\text{LV\%FS} = [(\text{LVDD} - \text{LVDS})/\text{LVDD}] \times 100.$$

10 (Endocardiography quantification of regional left ventricular wall motion using color kinesis)

 Color kinesis is an extension of this technology, which compares tissue backscatter values between successive acoustic frames as a means of automatically tracking and displaying endocardial motion in real time. Color kinesis
15 was incorporated into a commercially available ultrasound system (SONOS 5500, PHILIPS Medical Systems, USA) (Auchincloss 1988, Transplantation 46:1; Robert M.L., Philippe V., Lynn W., James B., Claudia K., Joanne S., Rick K., David P., Victor M.A., et al., "Echocardiographic
20 quantification of regional left ventricular wall motion with color kinesis", Circulation, 1996, 93:1877-1885).

 In all study subjects, ultrasound imaging was performed with a 12-MHz annular array transducer.
25 Midpapillary parasternal short-axis was obtained during end expiration in the lateral decubitus position. After image quality was optimized, the acoustic quantification system for endocardial boundary detection was activated. Gain control (total and lateral gain, time gain compensation)
30 were adjusted to optimize tracking of the blood-endocardial interface within a predefined region of interest. Color kinesis then was activated for on-line color encoding of endocardial excursion throughout systole. Image sequences

containing color kinesis data were obtained throughout the cardiac cycle and stored in a digital format on optical disks for off-line analysis.

5 (Histopathology)

Left ventricular myocardium specimens were obtained at 2 and 8 weeks after cardiomyocyte sheet implantation. Each specimen was placed in 10% neutral formaldehyde and embedded in paraffin. A few serial sections were cut from
10 each specimen and stained with hematoxylin and eosin for light microscopic examination.

To label vascular endothelial cells, immunohistochemical staining of factor VIII-related antigen
15 was performed. Frozen sections were fixed with a 2% paraformaldehyde solution in PBS for 5 minutes at room temperature, immersed in methanol with 3% hydrogen peroxide for 15 minutes, then washed with PBS. The samples were covered with bovine serum albumin solution (DAKO LSAB Kit
20 DAKO CORPORATION, Denmark) for 10 minutes to block nonspecific reactions. The specimens were incubated overnight with an EPOS-conjugated antibody against factor VIII-related antigen coupled with HRP (DAKO EPOS Anti-Human Von Willebrand Factor/HRP, DAKO Denmark). After the samples
25 were washed with PBS, they were immersed in diaminobenzidine solution (0.3 mg/ml diaminobenzidine in PBS) to obtain positive staining.

To detect Connexin 43, immunohistochemical staining
30 of Connexin 43-related antigen was performed. Frozen sections were immersed in methanol with 3% hydrogen peroxide for 5 minutes, and then washed with PBS. The specimens were incubated for 20 minutes with a mouse monoclonal antibody

to Connexin 43 (CHEMICON International, Inc. USA). After the samples were washed with PBS, they were immersed in biotinylated anti-mouse immunoglobulins (DAKO Denmark) for 10 minutes, and then washed with PBS. The samples were
5 immersed in peroxidase-conjugated streptavidin (DAKO Denmark) for 10 minutes. After the samples were washed with PBS, they were immersed in diaminobenzidine solution (0.3 mg/ml diaminobenzidine in PBS) to obtain positive staining.

10 (Electrophysiological analysis)

One microelectrode (100 μ m in diameter, Unique Medical Co., Ltd., Tokyo) for capture of the electrical potentials was positioned over the cardiomyocyte sheets implanted scar, fibroblast sheets implanted scar, or no
15 treatment scar. The other two electrodes were put on left subcostal and right femoral region. For stimulation of the host myocardium, two microelectrodes were positioned over an atrium. For detection of host electrocardiogram, three electrodes were attached on right upper breast, left
20 subcostal, and right femoral regions. Both electrograms were amplified by bioelectric amplifiers (UA-102, Unique Medical Co., Ltd., Tokyo) and were recorded by a data acquisition system (UAS-108S, Unique Medical Co., Ltd., Tokyo). The atrium was stimulated at the rate of 300 bpm
25 by stimulator (NIHON KODEN Japan). Thereafter, the electrical potential was captured in the regions of interest.

Thereafter, in order to analyze the threshold, two microelectrodes for stimulation were positioned over the
30 no treatment scar, cardiomyocyte sheet implanted scar, or fibroblast sheets implanted scar. For detection of paced host electrocardiogram, one electrode was attached on a normal myocardium, and the other two electrodes were put

on left subcostal and right femoral regions. Thereafter, the present inventors stimulated the no treatment scar, cardiomyocyte sheet implanted scar, or fibroblast sheets implanted scar at the rate of 300 bpm by the same stimulator.

5

(Data analysis)

Data are expressed as means \pm standard deviation (SD). In order to assess the significance of the differences between individual groups, statistical evaluation was performed with the nonparametric Mann-Whitney two-sample test. Statistical significance was determined as a p-value less than 0.05.

10

(Results)

15

(Characteristics of Cardiac grafts)

20

Detached cardiomyocyte sheets shrank from 5.76 cm² to 1.11 \pm 0.05 cm² (n=3) in area due to cytoskeletal reorganization. On the other hand, the thickness increased from 20.1 \pm 0.9 μ m to 52.4 \pm 6.0 μ m (n=3). The cardiac sheets contracted spontaneously by macroscopic observation.

20

(Histological assessment)

The present inventors could detach a mono-layered cardiomyocyte sheet under low temperature (Figure 6, upper left portion). The cardiomyocyte sheet was attached on an infarcted myocardium immediately after implantation without ligature (Figure 6, upper right portion). 2 weeks after implantation, histological examination of Hematoxylin-Eosin (HE) stain of the implanted cardiomyocyte sheet showed good attachment in alignment on the infarcted myocardium without accumulation of inflammatory cells. The yellow arrow indicates a collagen sheet, which is necessary to deliver the cardiomyocyte sheet to the infarcted

25

30

myocardium (Figure 7). Visual inspection of the implanted cardiomyocyte sheet at eight weeks after implantation revealed the intimate attachment between the implanted cardiomyocyte sheet and a recipient heart. HE stain of the
5 implanted cardiomyocyte sheet after eight weeks of implantation demonstrated the integration of the cardiomyocyte sheet with the host myocardium in alignment in the center of the scar (Figure 7, lower right portion). Immunohistochemical staining showed randomly oriented
10 Connexin 43 in the implanted cardiomyocyte sheet and around a contact region between the implanted cardiomyocyte sheet and the recipient heart (Figure 7, lower middle portion). Factor VIII immunohistochemical staining demonstrated many Factor VIII positive cells in and around the implanted
15 cardiomyocyte sheet (Figure 7, lower left portion).

(Functional recovery of infarcted myocardium)

B-mode analysis showed that dilatation of the left ventricle was well suppressed and global wall motion was
20 well preserved in the T group compared with the C group (Figure 8). An ejection fraction (EF), a fractional shortening (FS), and a left ventricular endsystolic area (LVESA) at a baseline were not significantly different between the three groups.

25

2 and 4 weeks after implantation, 2D endocardiography showed a significant improvement of EF and FS in the T group compared with those in the other groups. LVESA was significantly smaller in the T group than that in the other
30 groups. These functional improvements were preserved 8 weeks after implantation (Figure 9).

(Electrophysiological experiments)

Electrophysiological experiments showed the one peak component of QRS wave of the treated scar area in the T group in spite of two peaks of QRS wave like branch blocks in the C group (Figure 11). An effect was observed in the F group, though the level of the effect was lower than that of the T group. Furthermore, electrophysiological experiments demonstrated an improvement of the amplitude (volts) of the QRS complex in the T group in spite of low amplitude in the F and C group (C group vs T group: 2.79 ± 0.9 V vs 0.83 ± 0.64 V, $P < 0.05$) (Figure 11).

In the T group, when an atrium was stimulated at the frequency of 300 bpm by a stimulator, synchronous electrical spikes were detected in the implanted area (Figure 10, lower left portion). Furthermore, a threshold for pacing of a recipient heart was lower in the T group than the F and C groups (C group vs F group vs T group: 4.9 ± 0.9 V vs 3.0 ± 0.7 V vs 1.7 ± 0.5 V, $P < 0.05$) (Figure 10, right portion).

(Results)

A temperature-responsive domain made of poly(N-isopropylacrylamide) was grafted on polystyrene cell culture surfaces. Newborn rat cardiomyocytes were cultured on these dishes and detached as a rectangular cell sheet below 20°C without trypsin. Two sheets were piled up to make thicker cardiac grafts. These cardiomyocyte sheets contracted spontaneously. Cross sectional observation of the two sheets demonstrated intimate connection and homogenous heart-like tissue.

Two weeks after left anterior descending (LAD) ligation, two different treatments were conducted: 1) cardiomyocyte sheet implantation (T group, $n=10$); and 2)

fibroblast sheet implantation (F group, n=10). The control group was not treated (C group, n =10). Endocardiography demonstrated that cardiac function was significantly ameliorated in the T group two, four, and 8 weeks after
5 implantation. Color kinesis showed that regional systolic wall motion was excellently recovered as compared with values before implantation. Cardiomyocyte sheets attached on the infarcted myocardium were in alignment and seemed to be homogeneous tissue in the myocardium. Immunohistochemical
10 staining demonstrated neoangiogenesis and randomly oriented Connexin 43 in the implanted cardiomyocyte sheets. Electrophysiological experiments showed the improvement of the R-wave and the one peak component of the QRS complex in the treated scar area in the T group in spite of the two
15 peak components of the QRS complex like branch block in the F and C group. Furthermore, a threshold for pacing of a recipient heart was lower in the T group than the F and C group (C group vs F group vs T group: 4.9 ± 0.9 V vs 3.0 ± 0.7 V vs 1.7 ± 0.5 V, $P < 0.05$).

20

(Discussion)

The recent development of cellular cardiomyopathy introduced by needle injection has provided a novel approach to restore impaired cardiac function (Taylor D.A., Atkins
25 B.Z., Hungspreugs P., Jones T.R., Reedy M.C., Hutcheson K.A., Glower D.D., Kraus W.E., Regeneration of Functional Myocardium: Improved Performance after Skeletal Myoblast Transplantation, Nature Med., 1998; 4:929-933). Additional potential advantages of the cardiomyocyte sheet implantation
30 method are better control of the tissue formation process (the shape, size, and consistency of a graft), an easy implantation technique, and implantation of a number of cells with minimum cell loss. In contrast, an injection method

provides a loss of a certain amount of cells or its surface protein (e.g., Connexin 43) by means of trypsin treatment. In addition to myocardial infarction, the cardiomyocyte sheet implantation method may be useful for repair of global myocardial dysfunction (e.g., dilated cardiomyopathy). To achieve clinical applications, total implanted myocardial tissue mass is critically important for the repair of impaired myocardium, and enhancement of angiogenesis may make it possible for cardiac sheets to be thicker and deliver more cells to impaired myocardium.

In this example, the present inventors have developed a contractile cardiomyocyte sheet without a scaffold and have analyzed cardiac function and histological assessment after implantation. The cardiomyocyte sheet has attached to an infarcted myocardium accompanied with angiogenesis. The cardiomyocyte sheet looked like homogeneous myocyte tissue expressing Connexin 43 and contracted synchronously *in vivo*. Cardiomyocytes in the cardiomyocyte sheet exhibited alignment and few inflammatory cells accumulated in the implanted cardiomyocyte sheet. The cardiomyocyte sheet implantation promised excellent improvement of systolic and diastolic cardiac performance. Electrophysiological experiments revealed that the cardiomyocyte sheet improves electrical conductivity in scar and reconstructs one peak component of the QRS complex in the treated scar area. These data proved the present inventors' hypothesis that contractile cardiomyocyte sheets exhibit histological and electrical integration with impaired myocardium accompanied with angiogenesis and expression of Connexin 43 and induces the significant improvement of cardiac performance. To the present inventors' best knowledge, this is the first report in which

myocardial regeneration therapy was successful in impaired myocardium using a tissue engineered cardiac sheet.

5 The main factors of integration in the regenerative therapy are dynamic integration, electrical integration, and histological integration.

Concerning dynamic integration, cardiomyocytes of the implanted cardiomyocyte sheet showed alignment and promoted significant improvement of regional and global systolic function in infarcted myocardium. Impaired remodeling is responsible for the cardiac structural deformation and cardiac function deterioration in an infarcted heart (Tyagi S.C., Extracellular Matrix Dynamics in Heart Failure: A Prospect for Gene Therapy, J. Cell. Biochem., 1998, 68:403-410). Kelley et al. showed that restraint of the dilation of a left ventricle (LV) with mesh placed over an infarcted myocardium preserves the left ventricle (LV) geometry and resting function in a sheep myocardial infarction model (Kelley S.T., Malekan R., Gorman J.H. et al., Restraining Infarct Expansion Preserves Left Ventricular Geometry and Function after Acute Anteroapical Infarction, Circulation, 1999, 99:135-142). Although both the preservation of the left ventricle (LV) geometry and the improvement of a regional systolic function in dysfunctions tissues may be essential for repair of systolic performance in an impaired heart, only the attenuation of left ventricular (LV) dilatation is not adequate treatment. The present inventors' data, in which non-contractile sheets failed to improve the systolic performance compared with contractile sheets, supports this finding. Moreover, the present inventors' data demonstrated significant angiogenesis in infarcted myocardium. One of the mechanisms

for the improvement of cardiac function may be angiogenesis induced by an implanted cardiomyocyte sheet. To sum up, the significant improvement of systolic function induced by an implanted cardiomyocyte sheet is responsible for the preservation of left ventricular (LV) geometry, the improvement of regional systolic function, and induction of angiogenesis.

Concerning electrical integration, the present inventors' study demonstrated that an electrical conductor (i.e., a cardiomyocyte sheet expressing Connexin 43) promoted conductivity in scar, leading to the improvement of the amplitude of the QRS complex and the repair of two peak components of the QRS complex like branch block in infarcted myocardium. Branch block patterns are likely to be related to fibrosis or necrosis in myocardium (Agarwal A.K., Venugopalan P., Right Bundle Branch Block: Varying Electrocardiogram Patterns., An Etiological Correlation, Mechanisms and Electrophysiology, International Journal of Cardiology, 1999, 71:33-39). The histological change was reflected to the amplitude of the QRS complex in electrocardiogram recording (Sakamoto A., Ono K., Abe M., Jasmin G., Eki T., Murakami Y., Masaki T., Toyo-oka T., Hanaoka F., Both Hypertrophic and Dilated Cardiomyopathies Are Caused by Mutation of the Same Gene, delta-sarcoglycan, in Hamster: An Animal Model of Disrupted Dystrophin-associated Glycoprotein Complex, Proc. Natl. Acad. Sci. USA, Dec 9, 1997, 94(25):13873-8). The facts of synchronous wall motion demonstrated in the US, repair of two peak components of the QRS complex like branch block, and decrease of a threshold in scar might reveal electrical connection between an implanted cardiomyocyte sheet and a host myocardium. For this reason, cell sheets kept good surface condition with

Connexin 43 when the present inventors used temperature-responsive dishes, and not trypsin, to detach the cell sheets from culture dishes.

5 Concerning histological integration, implanted
cardiomyocyte sheets showed good attachment with infarcted
myocardium with angiogenesis. Already, the present
inventors demonstrated that histological integration by the
enhancement of cell/cell and cell/ECM interaction by a growth
10 factor in blood is essential for myocardial regeneration
of infarcted myocardium (Miyagawa S., Sawa Y., Taketani S.,
Kawaguchi N., Nakamura T., Matsuura N., Matsuda H.,
Myocardial Regeneration Therapy for Heart Failure,
Hepatocyte Growth Factor Enhances the Effect of Cellular
15 Cardiomyoplasty, Circulation, 2002, 105: 2556-2561).
Kushida et al. reported that adhesive agents in cell sheets
were well preserved after detachment from
temperature-responsive dishes (Kushida A., Yamato M., Konno
C., Kikuchi A., Sakurai Y., Okano T., J. Biomed. Mater. Res.
20 45:355-362, 1999). Therefore, these sheets show good
attachment and integration with several organs with good
preservation of adhesive molecules in its surface (Shimizu
T., Yamato M., Kikuchi A., et al., Two-dimensional
Manipulation of Cardiac Myocyte Sheets Utilizing
25 Temperature-responsive Culture Dishes Augments the
Pulsatile Amplitude, Tissue Eng., 2001, 7(2):141-51, 24;
and von Recum H.A., Kim S.W., Kikuchi A., Okuhara M., Sakurai
Y., Okano T., Retinal Pigmented Epithelium Culture on
Thermally Responsive Polymer Porous Substrates, J. Biomater.
30 Sci. Polym. Ed 9: 1998, 1241-1254). Moreover, delivery of
cells with preservation of cellular community may be
important for cell survival and viability in contrast to
cell delivery through an injection method. These results

indicate that cardiomyocyte sheets without scaffolds make a syncytium with a host myocardium.

5 A cell source for sheets is a very important matter in clinical applications. Recently, myoblasts are most widely used for clinical applications of cell transplantation. Myoblasts have a potential of ischemic tolerance rather than cardiomyocytes. Therefore, myoblasts are one of the suitable cell sources for cell sheet implantation in clinical
10 applications at present.

In conclusion, the present inventors have demonstrated that contractile cardiomyocyte sheets integrated with impaired myocardium dynamically,
15 electrically, and histologically.

Cardiomyocyte sheet implantation may be a novel and promising strategy for repairing functional performance and cardiac structure in impaired myocardium.
20

Fibroblast sheets also provide a slight improvement which is less than that of heart cell sheets. Therefore, it was demonstrated that fibroblast sheets have a potential to be utilized at least for first aid.
25

(Conclusion)

A prosthetic tissue using newborn rat cardiomyocytes integrated with impaired myocardium and ameliorated cardiac function in an ischemic cardium model. Although the present
30 inventors herein used cardiomyocytes, a prosthetic tissue organized using a cell sheet technique introduces a novel concept of tissue implantation and is useful in the field of regenerative medicine. This technique is schematically

shown in Figures 1A and 1B.

(Example 2)

5 (Self-derived myoblast sheet regenerates impaired
myocardium: A way to clinical application - Demonstrating
examples using rats)

Recent progress in tissue engineering is likely to
provide implantable functional tissue comprising various
cells other than myocardial cells, and extracellular matrices.
10 The present inventors designed autologous myoblast sheets.
The present inventors considered that these sheets are
beneficial for clinical applications. In this example,
therefore, myoblasts were used as material to construct a
prosthetic tissue or three-dimensional structure and an
15 effect of the prosthetic tissue or three-dimensional
structure on clinical applications was demonstrated.

(Methods)

An impaired heart was created in 28 rats by ligating
20 the left anterior descending (LAD) for 2 weeks. A temperature
responsive domain made of a polymer (N-isopropylacrylamide)
was coated on culture dishes. Skeletal myoblasts (SMs)
isolated from leg muscle were cultured and detached from
the dishes as a single monolayer cell-sheet (tissue) at 20°C
25 (Figure 13). Two myoblast sheets were implanted in nine rats
(myoblast sheet (S) group = 10^7 cells). Myoblast cells were
injected into 9 rats (I group = 10^7 cells). Non-cellular
therapy was conducted in 10 rats (C group = only medium was
injected).

30

(Measurement of cardiac function)

Rats were operated on under anesthetization. The
cardiac function was monitored at Day 14 and 28 after operation.

An ultrasound device (SONOS 5500) with a 12-MHz annular array transducer was used to perform endocardiography (Figure 18). Parasternal short axis imaging and parasternal long axis imaging were performed in the B- and M-imaging modes. In addition to anterior wall pressure, global parameters (e.g., left ventricle end-diastolic diameter, left ventricle endsystolic diameter, fractional shortening, and ejection fraction) were measured (Figure 14).

10 (Histology)

2 and 4 weeks after, the rats were sacrificed with excessive pentobarbital, and the hearts were excised. The hearts were fixed with 10% formaldehyde and embedded in paraffin. Serial 5-mm thick sections were cut from the base to the apex of the heart along a longitudinal axis thereof using a low temperature bath. Thereafter, treatment was performed for standard histology (as shown in Figures 15 and 17, hematoxylin-eosin staining was performed for visualization of muscle, and Masson's Trichrome staining for evaluating collagen content was performed for evaluation of collagen content).

(Results)

25 (Effect of myoblast implantation on cardiac function)

According to the experiments, myocardial infarction resulted in acute mortality of less than 20% within 24 hours after operation. The cell implantation procedure did not cause additional animal death.

30

Ventricle remodeling characteristically caused global enlargement of heart cavity and pump failure. At 2, 4, and 8 weeks after operation, tissue (MS group) and the

MI group had a significant decrease in left ventricular diameter, and both the left ventricular end-diastolic area (LVEDA) and left ventricular endsystolic area (LVESA) were improved after the treatment. Further, the ejection
5 fraction (EF) value and fractional shortening (FS) value of the myoblast sheet group were also high compared with those of the MI group (Figure 19).

Hearts in the control group which were not subjected
10 to cell therapy showed further dilation of a ventricle, hypertrophy of an anterior wall, and clearly low ejection fraction (EF) and fractional shortening (FS) values.

(Histological findings)

15 Histology revealed that the impaired hearts of the MI group had a dilated wall having nonuniform thickness (Figure 20), and contained substantially no patches of implanted cells (Figure 21). In contrast, the infarcted heart with the implanted sheet had a wall which did not dilate
20 and was uniformly thick, and adequately cellularized, and did not have scarring. The survival of the implanted sheet was identified at 2, 4, and 8 weeks after implantation.

Technical loss of implantation cells was analyzed
25 by RT-PCR based on the presence of the Y chromosome. As a result, the loss was smaller at 15 minutes and 1 day after operation in the MS group than in the MI group ($3.7 \pm 0.5\%$ vs $1.7 \pm 0.5\%$ of the total number of heart cells).

30 (Sequential photographs)

By taking a motion picture, it was confirmed that the myoblast implantation of the present invention actually caused pulsation (Figures 22A-F to 29).

Figures 22A to 22F show a motion picture display of a result of an electrophysiological examination, presenting representative frames (still images). Figures 22A to 22C indicate the control, and Figure 22D to 22F indicate results of a myoblast sheet of the present invention.

Figures 23A to 23C show a motion picture display of expression of GFP, presenting representative frames (still images). It is observed that a myoblast sheet of the present invention was actually pulsating.

Figures 24A to 24C show a motion picture display of an ultraechogram of an infarcted heart treated according to the present invention, presenting representative frames (still images).

Figures 25A to 25C also show a motion picture display of an ultraechogram of an infarcted heart treated according to the present invention, presenting representative frames (still images). The left portion of the figure shows a control infarcted heart, while the right portion shows a result of a myoblast sheet of the present invention. As can be seen from the figure, the present invention substantially cured infarct, so that the heart pulsated substantially normally.

Figures 26A to 26C are photographs showing the same sample as in Figures 25A to 25C at different time points. As can be seen from these figures, the infarcted heart was substantially cured by the present invention.

Figures 27A to 27C show a motion picture display of

an ultraechogram of an infarcted heart treated according to the present invention, presenting representative frames (still images). As can be seen from the figure, the infarct was cured by the treatment of the present invention.

5

(RT-PCR)

Next, in order to show cell affinity, the number of implanted cells was quantified by RT-PCR. In this example, the number of gene copies was evaluated by TaqMan assay for SRY and IL2.

10

RT-PCR was performed using a primer which was a portion of a gene derived from the Y chromosome in the male cells. By measuring the amount of the gene in the chromosomes in a female host, affinity was confirmed.

15

The following primer was used.

As a reaction solution, the following PCR mixed reaction solution was used.

20

UniversalMix (provided by the manufacturer)	12.5 μ l
Primer (100 μ M) forward	0.05 μ l
Primer (100 μ M) reverse	0.05 μ l
Probe (50 μ M)	0.1 μ l
dH ₂ O	10.3 μ l
Template (DNA)	2.0 μ l

The primer and probe sequences are described below.

SRY (forward primer) GCC TCA GGA CAT ATT AAT CTC TGG AG
(SEQ ID NO. 15)

5 (reverse primer) GCT GAT CTC TGA ATT CTG CAT GC (SEQ
ID NO. 16)

(probe) AGG CGC AAG TTG GCT CAA CAG AAT CC (SEQ
ID NO. 17)

IL2 (forward primer) GCC TTG TGT GTT ATA AGT AGG AGG C (SEQ
10 ID NO. 18)

(reverse primer) AGT GCC AAT TCG ATG ATG AGC (SEQ ID
NO. 19)

(probe) TCT CCT CAG AAA TTC CAC CAC AGT TGC
TG (SEQ ID NO. 20)

15

100 ng of each genomic DNA was used to perform PCR.
The mixed reaction solution was placed in wells of MicroAmp
Optical 96-well reaction plates. The wells were capped with
MicroAmp Optical Caps. Air bubbles were briefly removed,
20 and the liquid present in the bottom of each well was collected.
Each gene was measured in triplicate. PCR was performed using
the ABI Prism 7700 Sequence Detection System.

Standard DNA was the following: (200 ng. 40 ng.
25 8 ng. 1.6 ng 0.32 ng 0.064 ng); (SRY 200 ng = 3×10^4
copies; IL2 200 ng = 6×10^4 copies).

Parameters for thermal cycling were described below.

Stage 1	Stage 2	Stage 3
50°C/2 min	95°C/10 min	95°C/15 sec-60°C/1 min 40 cycles

30

The index of male cells was obtained by the following expression:

$$(2 \times \text{SRY} / \text{IL2}) \times 100.$$

5

As a result, as shown in Figure 28, it was demonstrated that the sheet (three-dimensional tissue) implantation has a more satisfactory level of affinity than that of needle (cell itself) implantation.

10

(Demonstration of cellularity)

What kind of cell type cells contained in an implanted cardiomyocyte sheet were differentiated into, was examined.

15

Therefore, Masson's Trichrome staining, HE (hematoxylin-eosin) staining, MHC fast staining, and MHC slow staining were performed.

These procedures were performed as follows.

20

<Masson's Trichrome Staining>

Masson's Trichrome staining is performed as follows.

Masson's Trichrome staining stains nuclei with iron hematoxylin. Thereafter, small pigment molecules (acid fuchsin, xyloidine ponceau) having a high diffusion rate enter cell reticular channels, and next, large pigment molecules (aniline blue) having a low diffusion rate enter the rough structure of collagen fibers, thereby staining the cell with blue.

30

Masson's Trichrome staining uses the following reagents.

A) Dye mordant

aqueous 10% trichloroacetic acid solution 1 part
aqueous 10% potassium dichromate solution 1 part

5 B) Weigert's iron hematoxylin solution (equal amounts of solution 1 and solution 2 are mixed in use)

solution 1

hematoxylin 1 g
100% ethanol 100 ml

10

solution 2

ferric chloride 2.0 g
hydrochloric acid (25%) 1 ml
distilled water 95 ml

15

C) 1% hydrochloric acid 70% alcohol

D) I solution

1% Biebrich red 90 ml
1% acid fuchsin 10 ml
acetic acid 1 ml

20

E) II solution

phosphomolybdic acid 5 g
phosphotungstic acid 5 g
distilled water 200 ml

25

F) III solution

aniline blue 2.5 g
acetic acid 2 ml
distilled water 100 ml

30

G) 1% acetic acid water

Procedure for Masson's Trichrome Staining:

1. deparaffinization, washing with water, distilled water;
2. mordanting (10 to 15 min);
- 5 3. washing with water (5 min);
4. Weigert's iron hematoxylin solution (5 min);
5. light washing with water;
6. separation with 1% hydrochloric acid 70% alcohol;
7. color development, washing with water (10 min);
- 10 8. distilled water;
9. I solution (2 to 5 min);
10. light washing with water;
11. II solution (30 min or more);
12. light washing with water;
- 15 13. III solution (5 min);
14. light washing with water;
15. 1% acetic acid/water (5 min);
16. washing with water (quick); and
17. dehydration, clearing, mounting.

20

With Masson's Trichrome staining, collagen fiber, reticular fiber and glomerular basement membrane are stained vividly blue, nuclei are stained black-violet, plasma is stained pale-red, erythrocytes are stained orange-yellow
25 to deep-red, mucus is stained blue, basophilic granules are stained blue and eosinophilic granules are stained red, and fibrin is stained red. Therefore, a blue-stained area can be calculated as a fibrous site.

30

<Hematoxylin-Eosin (HE) Staining>

The acceptance or vanishment of cells in a sheet was observed by HE staining. The procedure is described as follows. A sample is optionally deparaffinized (e.g., with

pure ethanol), followed by washing with water. The sample is immersed in Omni's hematoxylin for 10 min. Thereafter, the sample is washed with running water, followed by color development with ammonia water for 30 sec. Thereafter, the sample is washed with running water for 5 min and is stained with eosin hydrochloride solution for 2 min, followed by dehydration, clearing, and mounting.

<MHC Fast Staining>

- 10 MONOCLONAL ANTI-SKELETAL MYOSIN (FAST)
MYOSIN HEAVY CHAIN: MY-32 (skeletal myoblasts)
Specific reactivity with rats and human
1. Make 5um thick sections from frozen block.
 - 15 2. Sections are fixed in acetone at -20°C for 5-10 mins.
(Paraffin blocks should be deparaffinized and rehydrated).
 3. Endogenous peroxide activity is blocked in 0.3% H₂O₂ in methanol for 20 mins at RT.
 - 20 (1 ml 30% H₂O₂ + 99 ml methanol)
 4. Wash with PBS (3 × 5 mins).
 5. Incubate with primary monoclonal antibody (MY-32) in the moist chamber at 4°C for overnight (1 µl antibody + 200 µl PBS per slide).
 - 25 6. Next day wash with PBS (3 × 5 mins).
 7. Apply anti mouse and anti rabbit no. 1 Biotynalated link for 30 mins -1 hrs at RT.
(apply about 3 drops directly on slide).
 8. Wash with PBS (3 × 5 mins).
 - 30 9. Apply about 3 drops directly Streptavidin HRP no. 2 for LSAB. 10-15 mins.
 10. Wash with PBS (3 × 5 mins).
 11. Apply DAB (5 ml DAB+5 µl H₂O₂).

- 134 -

12. Observe under microscope for brownish colour.
13. Dip in water for 5 mins.
14. Apply HE for 30 sec-1 min.
15. Wash few times.
- 5 16. Ion exchange water wash 1 time.
17. 80% ethanol wash for 1 min.
18. 90% ethanol wash for 1 min.
19. 100% ethanol wash for 1 min (3 times).
20. Xylene wash for 1 min (3 times), Coverslip.
- 10 21. Examine color development.

<MHC Slow Staining>

Monoclonal Anti Myosin: (skeletal slow)

Specific reactivity with dog, rats and human

15

1. Make 5 μ m thick sections from frozen block.
2. Sections are fixed in acetone at -20°C for 5-10 mins.
(Paraffin blocks should be deparaffinized and rehydrated).
- 20 3. Endogenous peroxide activity is blocked in 0.3% H_2O_2 in methanol for 20 mins at RT.
(1 ml 30% H_2O_2 + 99 ml methanol)
4. Wash with PBS (3 \times 5 mins).
5. Incubate with primary monoclonal antibody NOQ7 in the moist chamber at 4°C for overnight (1 μ l antibody + 200 μ l PBS per slide).
- 25 6. Next day wash with PBS (3 \times 5 mins).
7. Apply anti mouse and anti rabbit no.1 Biotynalated link for 30 mins -1 hrs at RT.
- 30 (apply about 3 drops directly on slide).
8. Wash with PBS (3 \times 5 mins).
9. Apply about 3 drops directly Streptavidin HRP no. 2 for LSAB. 10-15 mins.

- 135 -

10. Wash with PBS (3 × 5 mins).
11. Apply DAB (5 ml DAB + 5 μ l H₂O₂).
12. Observe under microscope for brownish colour.
13. Dip in water for 5 mins.
- 5 14. Apply HE for 30 sec-1 min.
15. Wash few times.
16. Ion exchange water wash 1 time.
17. 80% ethanol wash for 1 min.
18. 90% ethanol wash for 1 min.
- 10 19. 100% ethanol wash for 1 min (3 times).
20. Xylene wash for 1 min (3 times), Coverslip.
21. Examine color development.

As a result, as shown in Figure 29, it was demonstrated that the implanted myoblast sheet was differentiated from fast fiber to slow fiber. These markers can be used to identify a three-dimensional tissue structure of the present invention.

20 (Conclusion)

Skeletal myoblast implantation attenuated heart remodeling and regenerated impaired myocardium to ameliorate global cardiac function as compared with cell implantation. This finding suggests a promising strategy for regenerative therapy for myocardium.

Therefore, it was demonstrated that when a myoblast sheet was implanted as a three-dimensional structure, the cardiac function of impaired myocardium was ameliorated. In this example, by using direct injection, autologous skeletal myoblast (SM) implantation was clinically applied. Loss of implanted cells and implanted extracellular matrix (ECM) due to direct injection limits the number of skeletal

myoblasts and the ability of skeletal myoblasts.

Concerning clinical tests using an autologous cell source, autologous myoblasts are preferably used. It was
5 also demonstrated that tissue implantation is more advantageous to regenerate an injured heart than cell implantation.

(Example 3: Skeletal myoblast - Implantation of
10 tissue-engineered myoblast sheet improves cardiac function with attenuation of cardiac remodeling in cardiomyopathic hamsters)

Next, it was examined whether or not a prosthetic tissue or three-dimensional structure produced using
15 skeletal myoblasts ameliorates cardiomyopathy.

Cell therapy is a promising strategy for ischemic cardiomyopathy. However, direct injection methods seem to
have limitations for generalized cell delivery in dilated
20 cardiomyopathy (DCM). Given this body of evidence, the present inventors considered that a tissue-engineered myoblast sheet implantation might be a superior and promising method to ameliorate the cardiac function in DCM. Therefore, the present inventors carried out this example.

25

(Method)

Male 27-week old BIO TO-2 (dilated cardiomyopathy (DCM)) hamsters which showed moderate cardiac remodeling were used as recipients. Myoblasts isolated from BIO FIB
30 hamsters (FIB) were cultured on dishes grafted with a temperature-responsive polymer made of poly(N-isopropylacrylamide), and detached as a cell sheet at 20°C without enzymatic treatment.

Three different therapies were conducted: (1) myoblast sheet implantation group (S group, n=8); (2) myoblast (isolated from FIB) injection group (T group, n=10);
5 and (3) Sham operation group (C group, n=10). In the S group, a myoblast sheet was implanted on the left ventricular (LV) wall. In the T group, myoblasts were injected into the right ventricular (RV) wall and the left ventricular (LV) wall.

10 (Results)

(Functional recovery of infarcted myocardium)

B-mode analysis demonstrated that the dilation of a left ventricle was adequately suppressed and global wall motion was adequately preserved in the T group as compared
15 with the C group (Figure 18).

After the myoblast sheet was implanted, an ultrasound echogram demonstrated that dilated LV dimension was significantly reduced, whereas the hearts in T and C groups
20 showed a progression of left ventricular (LV) dilation (Figure 33A). Six weeks after operation, fractional shortening (FS) was significantly improved in the S and T groups compared with that in the C group. After seven weeks, FS in the S group was maintained at the preoperative level,
25 while FS in the other groups decreased gradually. Although the max velocity of the mitral valve E-wave in the S group dropped slightly one week after the sheet implantation, this was recovered to the preoperative level 2 weeks after operation. The averaged E-wave in the S and T groups was
30 significantly higher than that in the C group 4 weeks after operation and thereafter. Histological examinations in the S group demonstrated that the implanted sheet almost covered the whole heart and the left ventricle (LV) wall thickness

was increased with surviving myoblasts (Figures 30A to 30D). As can be seen from Figure 30B, the implanted myoblasts, which constituted a tissue structure, were intimately attached to and accepted by the heart to aid the cardiac function. Figures 30C and 30D clearly show that expression of α -sarcoglycan and β -sarcoglycan had a score of 2 to 3 and about 3, respectively, i.e., the heart was substantially moderately recovered, where normal expression has a score of 5 and DCM hamsters have a score of about 3. It is known that DCM hamsters have a symptom of partial dilated cardiomyopathy caused by a decrease in expression of sarcoglycan. It was demonstrated that a three-dimensional tissue structure of the present invention has an effect of supplementing such gene expression.

Figure 33B clearly shows that use of the three-dimensional tissue structure of the present invention allowed DCM hamsters to survive beyond 48 weeks. This is a significant and unexpected effect compared with injection (only cells) or control (in either case, all DCM hamsters died after 38 to 40 weeks). As shown in Figure 33C, the contractility of the left ventricle with dilated cardiomyopathy was significantly ameliorated. This result shows that the structure of the present invention can be applied to hearts. The result corresponds to about a 25-year extension of life span, demonstrating a significant effect of the three-dimensional tissue structure of the present invention. The average life-span of the DCM hamsters was about 40 weeks, while the longest life-span of the DCM hamsters having an implanted sheet was about 70 weeks. Assuming that the life-span of a normal hamster is about 2 years and the life-span of a human is 80 years, the life-span of the implanted hamster was prolonged by about 30 weeks which is equivalent

to about 25 years in a human. Thus, it was demonstrated that the three-dimensional structure of the present invention has a significant effect on cardiomyopathy.

5 (Conclusion)

Myoblast sheet implantation reduced the progression of heart hypertrophy with improvement of cardiac function in dilated cardiomyopathic (DCM) hearts. Myoblast sheet implantation may be a promising method to restore the cardiac
10 function with attenuation of cardiac remodeling in DCM hearts.

(Example 4: Therapy for infarct pig model)

In this example, aiming for more clinical findings, skeletal myoblast sheets were implanted into a larger animal
15 model of myocardial infarct to study amelioration of cardiac function.

(Method)

20 A thoracotomy was performed on 30 kg pigs under general anesthetization and the LAD was ligated to produce myocardial infarct models. Three different therapies were conducted: 1) skeletal myoblast sheet group; 2) skeletal myoblast injection group; and 3) control group. For these
25 groups, changes in cardiac function and myocardial tissue were examined (Figure 34). Skeletal myoblasts were collected from autologous thigh muscle. Collagenase, trypsin EDTA, gentamicin sulfate, and amphotericin B were prepared and filtered through a 0.22- μ m filter to formulate
30 a dissociating solution. SkBM Basal Medium, bovine fetal serum, EGF, sodium dexamethasone phosphate, gentamicin sulfate, and amphotericin B were prepared and filtered through a 0.22 μ m filter to formulate primary culture medium.

The dissociated cells were cultured on dishes grafted with a temperature responsive macromolecule made of poly(N-isopropylamide) and were detached as a cell sheet by changing temperature instead of enzymatic treatment.

5

(Results)

The group with cell sheet implantation had ameliorated cardiac functions, i.e., contractility and expansibility (Figures 35 and 36). In addition, it was confirmed that the implanted cells were accepted by the myocardial infarct portion.

10

(Conclusion)

In experiments using animals other than rodents, it was confirmed that a therapy using a myoblast sheet of the present invention had an effect of ameliorating cardiac function.

15

(Example 5: Synovial cells)

To demonstrate an effect of the present invention in the case of another type of cell, a sheet of synovial cells (cells containing tissue stem cells) was prepared and implanted into myocardial infarct models to examine an effect of ameliorating cardiac function.

20

25

(Methods)

Knee joints were removed from 8-week old rats. Synovial tissue was cut off the internal surface of the joint. The tissue was attached to culture medium containing 20% FCS and DMEM high glucose for cell culture. The resultant cells were cultured on dishes grafted with a temperature responsive macromolecule made of poly(N-isopropylamide) and were detached as a cell sheet by changing temperature instead

30

of enzymatic treatment. For myocardial infarct models prepared by LAD ligation, three different therapies were conducted: 1) cell sheet group; 2) cell injection group; and 3) control group. For these groups, changes in cardiac function and myocardial tissue were examined.

(Results)

The group with cell sheet implantation had ameliorated cardiac functions, i.e., contractility and expansibility. In addition, it was confirmed that the implanted cells were accepted by the myocardial infarct portion.

(Conclusion)

In the case of cells differentiated from cell obtained from synovial tissue, it was confirmed that a sheet of such cells had an effect of ameliorating cardiac function.

(Example 6: Stem cells)

As an example of undifferentiated cells, there is a mouse embryonic stem cell known to be capable of differentiating into a cardiomyocyte. In this example, a sheet of such cardiomyocytes was prepared and implanted into myocardial infarct models to study the effect on ameliorating cardiac function.

(Methods)

A resistance gene was introduced into a promoter site of a gene expressing MHC in mouse embryonic stem cells. The cells were cultured in a selective culture containing a high concentration of a drug in which differentiated cells other than cardiomyocytes are killed, so that cardiomyocytes were selected. The resultant cells were cultured on dishes

grafted with a temperature responsive macromolecule made of poly(N-isopropylamide) and were detached as a cell sheet by changing temperature instead of enzymatic treatment. For myocardial infarct models prepared by LAD ligation, three
5 different therapies were conducted: 1) cell sheet group; 2) cell injection group; and 3) control group. For these groups, changes in cardiac function and myocardial tissue were examined.

10 (Results)

The group with cell sheet implantation had ameliorated cardiac functions, i.e., contractility and expansibility. In addition, it was confirmed that the
15 implanted cells were accepted by the myocardial infarct portion.

(Conclusion)

In the case of cells differentiated from cells obtained from synovial tissue, it was confirmed that a sheet
20 of such cells had an effect of ameliorating cardiac function.

(Example 7: Preparation of prosthetic tissue using ascorbic acid)

Next, an influence of ascorbic acid or a derivative
25 thereof on production of a prosthetic tissue was studied.

After an adequate amount of myoblasts were produced, 5×10^6 cells were cultured on 10-cm temperature responsive culture dishes. For culture, SkBM Basal Medium (Clonetics
30 (Cambrex)) was used. Next, ascorbic acid 2-phosphate (0.5 mM), magnesium ascorbic acid 1-phosphate (0.1 mM), and sodium L-ascorbate (0.1 mM) were added to the medium. 4 days after culture start, the cells were detached at 20°C. As

a control, a prosthetic tissue was prepared in a culture system without ascorbic acids.

(Results)

5 When ascorbic acid was added, the prosthetic tissue was detached much more easily than that in the culture system without any ascorbic acids. In addition, tissue was not cultured to a size of several millimeters in the culture system without ascorbic acids. If the tissue exceeded such
10 a size, cracks occurred and the growth stopped. It was also substantially difficult to detach the tissue. Thus, implantable prosthetic tissue could not be provided. In contrast, a prosthetic tissue of the present invention, which was cultured in a medium supplemented with an ascorbic acid,
15 grown into an implantable size, and was easy to detach. In addition, the prosthetic tissue was isolated while substantially no hole or scar was generated. Inspection of biological connections demonstrated that extracellular matrix-mediated interaction was significant (Figures 37 to
20 39).

(Example 8: Effect of addition of ascorbic acid 2-phosphate)

25 Next, an influence of ascorbic acid 2-phosphate on production of a prosthetic tissue was studied.

30 After an adequate amount of synovial cells or myoblasts were produced, 5×10^6 cells were cultured on 10-cm temperature responsive culture dishes. For culture, SkBM Basal Medium (myoblasts) containing ascorbic acid 2-phosphate (1 mM) or DMEM (synovial cells) containing ascorbic acid 2-phosphate (1 mM) was used. As a control, a prosthetic tissue was prepared in a culture system having

the same medium without ascorbic acids or in another culture system having the same medium with ascorbic acid 1-phosphate (1 mM).

5 9 days after culture start, the tissue was detached and contracted. The tissue was contracted by a factor of about 3.

10 The contracted tissue was histologically analyzed by HE staining or the like (Figure 42, synovial cells). It was found that the cells constructed 10 or more layers and the matrix was in the form of collagen mesh or sponge. The matrix had rigidity such that the matrix could be easily pinched with forceps.

15

(Stress-distortion examination (tensile test))

20 To confirm strength, a tensile test was conducted to obtain a load-time (stress distortion) curve where a sample is stretched. According to this curve, the limit of proportionality, modulus of elasticity, yield point, maximum strength, rupture point, elastic energy, and tenacity are obtained.

(Creep characteristics (indentation test))

25 Indentation test, which measures creep characteristics, was carried out by determining viscoelasticity. It is possible to observe a phenomenon in which distortion is increased. An instrument, such as a rod or the like, is pushed into a gel material, and the deformation
30 of the material is monitored.

(Results)

A prosthetic tissue can be detached much more easily

when ascorbic acid 2-phosphate is added than in a culture system without ascorbic acids and in a culture system which contains commonly used ascorbic acid 1-phosphate. In addition, tissue was not cultured to a size of several millimeters in the culture system without ascorbic acids. If the tissue exceeded such a size, cracks occurred and the growth stopped. The size, strength, and the like are greater in the culture system with ascorbic acid 2-phosphate than in the culture system containing commonly used ascorbic acid 1-phosphate. In the system without ascorbic acids, it was also substantially difficult to detach the tissue. Thus, implantable prosthetic tissue could not be provided.

Particularly, the prosthetic tissue cultured in the system containing ascorbic acid 2-phosphate had rigidity such that it can be pinched with forceps. Prosthetic tissues cultured in other systems had less rigidity than that of the prosthetic tissue cultured in the ascorbic acid 2-phosphate-containing system. The prosthetic tissue cultured in ascorbic acid 2-phosphate-containing medium was grown to an implantable size and was easy to detach. In addition, the prosthetic tissue was isolated while substantially no hole or scar was generated. Inspection of biological connection demonstrated that extracellular matrix-mediated interaction was significant.

(Example 9: Effect of prosthetic tissue cultured in the presence of ascorbic acids)

The prosthetic tissue produced in the presence of ascorbic acids in Examples 7 and 8 was implanted into dilated cardiomyopathy hamsters. All the implanted mice were cured, and survived as long as ordinary hamsters do. Therefore, it was demonstrated that the present invention can cure

diseases, which are conventionally believed to be refractory, by providing a specific three-dimensional promoting agent.

(Example 10: Combined therapy)

5 A combined therapy of a sheet as prepared in the above-described examples, and gene therapy, was carried out. The combined therapy aims for promoting angiogenesis in sheet implanted sites, promoting acceptance of implanted sheets, and suppressing cell necrosis within sheets.

10

(Methods)

 A complex of Sendai virus (HVJ) and a liposome was prepared in accordance with the description of a document (Kaneda Y., Iwai K., Uchida T., Increased Expression of DNA
15 Co-introduced with Nuclear Protein in Adult Rat Liver, Science, 1989, 243:375-378). Hereinafter, this procedure will be briefly described. 200 μ l of DNA solution was prepared and shaken for 30 sec. The solution was allowed to stand in a 37°C constant temperature bath for 30 sec. This
20 procedure was performed 8 times. The solution was subjected to ultrasonic treatment for 5 sec, and shaken for 30 sec. 0.3 mL of BSS was added to the solution, followed by shaking in a 37°C constant temperature bath. Inactivated HVJ was added to the solution which was in turn placed on ice for
25 10 min. The solution was shaken in a 37°C constant temperature bath for 1 hour. 1 mL of 60% sucrose solution and 6 mL of 30% sucrose solution were layered in an ultracentrifugation tube. HVJ liposome solution was placed on the layered solution. BSS was added to the tube. The
30 tube was ultracentrifuged at 62,800 \times g 4 times for 1.5 hours. A layer immediately above the 30% sucrose solution layer was removed and preserved at 4°C. This liposome was used for gene introduction.

About 0.2 mL of Sendai virus liposome-plasmid complex (containing 15 µg of human HGF cDNA) was injected into a myocardial infarct region. In a control group, an empty vector was used for gene introduction into infarcted myocardium. The human HGF concentration of heart tissue was measured by enzyme-linked immunosolvent assay (ELISA) using an anti-human HGF monoclonal antibody (Institute of Immunology, Tokyo, Japan)) (Ueda H., Sawa Y., Matsumoto K. et al., Gene Transfection of Hepatocyte Growth Factor Attenuates Reperfusion Injury in the Heart, Ann. Thorac. Surg., 1999, 67:1726-1731). The resultant cells were cultured on dishes grafted with a temperature responsive macromolecule made of poly(N-isopropylamide) and were detached as a cell sheet by changing temperature instead of enzymatic treatment. For myocardial infarct models prepared by LAD ligation, three different therapies were conducted: 1) cell sheet group; 2) gene therapy group; 3) combined therapy group; and 4) control group. For these groups, changes in cardiac function and myocardial tissue were examined.

(Results)

The cell sheet implantation group and the combined therapy group have ameliorated cardiac functions, i.e., contractility and expansibility. In addition, it is confirmed that in the combined therapy group, angiogenesis is observed and the implanted cells are accepted by the myocardial infarct portion.

(Conclusion)

A combination of sheet tissue and gene therapy has an effect of amelioration of cardiac function, an effect

of angiogenesis, and an effect of cell protection. It is also confirmed that cardiac function is further ameliorated.

Although certain preferred embodiments have been
5 described herein, it is not intended that such embodiments be construed as limitations on the scope of the invention except as set forth in the appended claims. Various other modifications and equivalents will be apparent to and can be readily made by those skilled in the art, after reading
10 the description herein, without departing from the scope and spirit of this invention. All patents, published patent applications and publications cited herein are incorporated by reference as if set forth fully herein.

15 INDUSTRIAL APPLICABILITY

The present invention provides a radical therapeutic method, a technique, and a medicament for diseases which are difficult to treat by conventional therapies
20 (particularly, heart diseases exhibiting severe heart failure, etc.).

CLAIMS

1. A three-dimensional structure applicable to heart,
comprising a cell derived from a part other than myocardium
5 of an adult.
2. A structure according to claim 1, wherein the cell is
a stem cell or a differentiated cell.
- 10 3. A structure according to claim 1, wherein the cell is
a mesenchymal cell.
4. A structure according to claim 1, wherein the cell is
derived from a myoblast.
- 15 5. A structure according to claim 4, wherein the myoblast
is a skeletal myoblast.
6. A structure according to claim 1, wherein the cell is
20 a fibroblast.
7. A structure according to claim 1, wherein the cell is
a synovial cell.
- 25 8. A structure according to claim 1, wherein the cell is
derived from a stem cell.
9. A structure according to claim 1, wherein the cell is
derived from a subject, the structure being applied to the
30 subject.
10. A structure according to claim 1, wherein the cell is
not derived from a subject, the structure being applied to

the subject.

11. A structure according to claim 1, wherein the structure expresses at least one non-adult heart marker selected from the group consisting of myosin heavy chain IIa, myosin heavy chain IIb, myosin heavy chain IId(IIx), CD56, MyoD, Myf5, and myogenin.
12. A structure according to claim 11, wherein an expression level of the non-adult heart marker in the structure is at least 50% of an expression level of the non-adult heart marker in skeletal myoblasts.
13. A structure according to claim 1, wherein the three-dimensional structure expresses all of myosin heavy chain IIa, myosin heavy chain IIb, myosin heavy chain IId(IIx), CD56, MyoD, Myf5, and myogenin.
14. A structure according to claim 13, wherein an expression level of each of myosin heavy chain IIa, myosin heavy chain IIb, myosin heavy chain IId(IIx), CD56, MyoD, Myf5, and myogenin in the structure is at least about 50% of an expression level thereof in skeletal myoblasts.
15. A structure according to claim 13, wherein an expression level of each of myosin heavy chain IIa, myosin heavy chain IIb, myosin heavy chain IId(IIx), CD56, MyoD, Myf5, and myogenin in the structure is at least about 100% of an expression level thereof in skeletal myoblasts.
16. A structure according to claim 1, wherein the cell derived from a part other than myocardium is a cell not derived from heart.

17. A structure according to claim 1, wherein the applicability to heart includes applicability to myocardium.

5 18. A structure according to claim 1, comprising a monolayer cell sheet.

19. A structure according to claim 1, comprising a multilayer cell sheet.

10

20. A structure according to claim 19, wherein the multilayer cell sheet has biological connection.

15 21. A structure according to claim 20, wherein the biological connection is selected from the group consisting of connection via extracellular matrix, electrical connection, and connection without scaffold.

20 22. A medicament, comprising a three-dimensional structure according to any one of claims 1 to 21.

23. A medicament according to claim 22, wherein the heart has a disease or disorder selected from the group consisting of heart failure, ischemic heart disease, myocardial infarct, cardiomyopathy, myocarditis, hypertrophic cardiomyopathy, 25 dilated phase hypertrophic cardiomyopathy, and dilated cardiomyopathy.

24. A method for producing a three-dimensional structure applicable to heart comprising a cell derived from a part other than myocardium of an adult, the method comprising the steps of:

a) culturing the cell derived from the part other

than myocardium of an adult on a cell culture support grafted with a temperature responsive macromolecule having an upper limit critical solution temperature or lower limit critical solution temperature to water of from 0°C to 80°C;

5 b) setting a culture medium temperature to the upper limit critical solution temperature or more or the lower limit critical solution temperature or less; and

 c) detaching the cultured cell as a three-dimensional structure.

10

25. A method according to claim 24, wherein a treatment using a protein degrading enzyme is not performed in or before the detaching step.


15

26. A method according to claim 24, wherein the temperature responsive macromolecule is poly(N-isopropylacrylamide).

FIG. 1A


Cell Sheet Constructs

A




Hydrophobic PIPAAm
Remains attached: 37°C

B



Intermediate stage
Partial detachment: 20°C

C




Hydrophilic PIPAAm
Completely detached sheet

1 / 47

Temperature responsive polymer

Poly (N-isopropylacrylamide) (PIPAAm)



Poly (acrylamide) (PAAm)


Exemplary Dimensions:


$1.11 \pm 0.05 \text{ cm}^2$ in area


$50.2 \pm 6.0 \mu\text{m}$ thick

2 / 47

FIG. 1B


Temperature responsive culture dish





5 / 47

FIG.4 Regenerative therapy for cardiac
muscle by cell transplantation



6 / 47


FIG.5 Problems with tissue transplantation

Cardiac muscle graft with scaffold

Alignment and cell-to-cell adhesion of transplanted cells within scaffold

Changes in scaffold in organism: elicitation of inflammation

Acceptance of scaffold by recipient's heart



Development of high biocompatible cardiac muscle graft without scaffold

7 / 47

FIG. 6

Implantation of cardiomyocyte sheet into infarcted heart

Cardiomyocyte sheet



Implantation into rat infarct model

*In vitro*

Implantation of GFP rat newborn cardiomyocyte sheet


*In vivo*

FIG. 7

Tissue

2 weeks after implantation

**8 weeks after
implantation**







FIG.8 Evaluation of Cardiac function - 1

Control



Implantation of prosthetic tissue



10 / 47

FIG.9 Evaluation of cardiac function - 2





FIG.10


Electrophysiological Evaluation



Buried electrode at
sheet implanted site

12 / 47

FIG.11



ECG 1: ECG (Surface)
 ECG 2: Normal heart (anterior wall)
 Ligation model (injured)
 Prosthetic tissue implanted
 (prosthetic tissue injured)

Electrophysiological Evaluation






FIG.12

Isolation and culture of myoblast




Harvested Muscle




Collagenase 37°C, 30min

13 /47



Myoblasts in culture



Desmin stained Myoblasts



Methods: Myoblast Sheet Construction

FIG.13







FIG.14

Experimental Protocol



Preparation of myoblast sheet

Lewis rat skeletal muscle cell

Collagenase/trypsin treatment

Sheet



Control group (n=8)

Cell implantation sheet (n=5) 5×10^6 cells (6~10 score)

Sheet implantation group (n=9): 5×10^6 cells/sheet

15 / 47




FIG.15


Myoblast sheet: 4W post implantation

Implanted myoblasts



x1000

HE staining




x10

x200

17 / 47

FIG.16 Myoblast sheet Implantation procedure



18 / 47

FIG.17 HistologyMasson's Trichrome staining








FIG.18

CKA




M-mode analysis



20 / 47

FIG.19




#P< 0.05 for control; *P< 0.05 to for injection needle group

FIG.20

Anterior Wall Thickness Comparison

Myoblast prosthetic tissue




x40

Myoblast injection



x40

Anterior wall thickness




Control



x40


FIG.21

Myoblast sheet:
Desmin Staining




x100

Control group (GFP)



x100


Myoblast prosthetic
tissue group (GFP)



x100
22 /47


Factor VIII staining

Myoblast injection




x40

Control



x40

Myoblast prosthetic tissue



x40

23 /47

FIG.22A




FIG.22B




FIG.22C



FIG.22D

24 /47




FIG.22E




FIG.22F



25 /47

FIG.23A



FIG.23B




FIG.23C



26 /47

FIG.24A




FIG.24B





FIG.24C



27 / 47

FIG.25A





FIG.25B



FIG.25C



28/47

FIG.26A




FIG.26B





FIG.26C



29 / 47

FIG.27A




FIG.27B





FIG.27C



30 /47

FIG.28





FIG.29


HE staining x400




Masson's Trichrome staining x400



MHC slow x400



MHC fast x400




32 / 47

FIG.30A Tissue (Masson's Trichrome staining)


Myoblast sheet
4W post implantation

x10




Myoblast implantation
(needle injection)

4W post implantation x10



Control

x10



x40




x40



x40

33 /47

FIG.30B






FIG.30C




FIG.30D

36 /47

Survival rate of implanted cell

FIG.31




FIG.32
MED system

Electronical properties of myoblast sheet

Cardiomyocyte sheet

Myoblast sheet









FIG.33A Myoblast sheet implantation to dilated
cardiomyopathic hamster



HE staining



38 /47



Masson's Trichrome staining



FIG.33B

Left ventricular end-systolic diameter


Left ventricular end-diastolic diameter




40 /47

FIG.33C

Control group



Myoblast sheet implantation group



41 /47

FIG.34 Myoblast sheet implantation into pig infarction model




FIG.35

Evaluation of cardiac function (systolic function) of
pig infarction model by CKI method

Before operation After operation





FIG.36

Evaluation of cardiac function (diastolic function) of
pig infarction model by CKI method

Before operation After operation



44 /47

FIG.37

Without ascorbic acid




FIG.38

With ascorbic acid





FIG.39



45 /47

FIG.40





FIG.41



Rigidity $H = \frac{F}{A} = \frac{F}{k_1 h_p^2}$

Young's modulus $E = \left[\frac{dF}{dh}\right]_{F_{max}} \frac{1 - \nu^2}{2 \cdot k_2 \cdot h_{pmax}}$

Contact depth $h_p = h_r + 0.25(h_{max} - h_r)$

F : Load

A : Contact projection area

h_p : Contact depth

$k_1 k_2$: Shape coefficient

F_{max} : Maximum load

h_{max} : Max. displacement


h_r : Point at which tangential line cross weight 0

dF/dh : Gradient of tangential line of the removal of load curve

ν : Poisson's ratio

47 /47

FIG.42



10/567728

SEQUENCE LISTING

IAP5 Rec'd PCT/PTO 31 JAN 2006

<110> Cardio, Inc.
 5 <120> three dimensional tissue construct
 <130> CD009PCT
 <150> JP2003-285476
 10 <151> 2003-08-01
 <160> 20
 <170> PatentIn version 3.1
 15 <210> 1
 <211> 5956
 <212> DNA
 <213> Homo sapiens
 20 <400> 1
 atgagttctg actcagaatt ggctgttttt ggggaggctg ctcttttcct ccgaaagtct 60
 gaaagggaac gcattgaggc ccagaatagg ccctttgatg ccaaaacatc tgtctttgtg 120
 25 gcggagccca aagaatcctt tgtcaaaggg accatccaga gcagagaagg aggaaaagtg 180
 acggtgaaga ctgagggagg agcgactctg acagtgaagg atgacaggt cttccccatg 240
 30 aaccctccca aatatgacaa gatcgaggat atggccatga tgactcatct gcatgagcct 300
 gctgtgctgt acaacctcaa agaacgttat gcagcctgga tgatctacac ctattcaggt 360
 ctctttctgt tcaactgtcaa cccctacaag tggctgcctg tgtataagcc cgagggtggtg 420
 35 acagcctacc gaggcaaaaa gcgccaggag gccccgcccc acatcttctc catctctgac 480
 aacgcctatc agttcatgct gactgaccga gagaatcagt caatcctgat cactggagaa 540
 40 tctggtgcag ggaagactgt gaacaccaag cgtgtcatcc agtactttgc aacaattgca 600
 gttactgggtg agaagaagaa ggaagaaatt acttctggca aaatacaggg gactctggaa 660
 gatcaaatca tcagtgccaa cccctactg gaggcctttg gcaacgcaa gaccgtgagg 720
 45 aatgacaact cctctcgctt tggtaaattc atcagaatcc actttggcac tactggaaaa 780
 ctggcatctg ctgatattga aacatatctg ctagagaagt ctagagttgt tttccagctt 840

aaggctgaga gaagttatca tattttttac cagattacat cgaataagaa accagaactt 900
attgaaatgc ttctgattac cacgaacca tatgattacc catttgtcag tcaaggggag 960
5 atcagtgtgg ccagcatoga tgatcaggaa gaactgatgg ccacagatag tgctattgat 1020
attttgggct ttactaatga agaaaaggtc tccattttaca agctcacggg ggctgtgatg 1080
10 cattatggga acctaaaatt taagcaaaag cagcgtgagg agcaagcaga gccagatggc 1140
acagaagttg ctgacaaggc ggctacctc cagagtctga actctgcaga tctgtcaaa 1200
gctctctgct accccagggt caaggctggc aatgagtatg tcaccaaagg ccagactgta 1260
15 gaacagggtgt ccaacgcagt aggtgctctg gccaaagccg tctacgagaa gatgttcctg 1320
tggtgggttg cccgcatcaa ccagcagctg gacaccaagc agcccaggca gtacttcac 1380
20 ggggtcttgg acattgctgg ttttgagatt ttgtatttca acagcctgga gcagctgtgc 1440
atcaatttca ccaatgagaa actgcaacag ttttcaacc accacatgtt cgtgctggag 1500
caggaggagt acaagaagga aggcacgag tggacgttca tcgacttcgg gatggacctg 1560
25 gctgcctgca tcgagctcat cgagaagcct atgggcatct tctccatcct ggaagaggag 1620
tgcatgttcc ctaaggcaac agacacctcc ttcaagaaca agctgtatga ccagcacctg 1680
30 ggcaagtctg ccaacttcca gaagcccaag gtgtcaaag gcaaggccga ggcccacttc 1740
gctctgattc actatgctgg tgtgtggac tacaacatta ctggctggct ggagaagaac 1800
aaggaccccc tgaatgagac cgtggttga ctgtaccaga agtctgcaat gaaaactcta 1860
35 gctcagctct tctctggggc tcaaactgct gaaggagagg gagctggtgg aggggccaag 1920
aaagggtgta agaagaaggg ctcttctttc cagacagtgt ctgccctttt cagagagaat 1980
40 ttgaacaagc tgatgaccaa cctcaggagt acccatcctc actttgtgag gtgtatcatc 2040
cccaatgaga caaaaactcc tggtgccatg gagcatgagc ttgtcctcca ccagctgagg 2100
tgtaacgggtg tgctggaagg catccgcac 1260
45 tatgcagact tcaaacagag atacaaggta ttaaatgcaa gtgcaatccc tgaagggcaa 2220
ttcattgata gcaagaaggc ctctgagaag ctccttgcac ccatcgacat tgaccacacc 2280

cagtataaat ttgggcacac caaggtcttt ttcaaagctg gtcttctggg gctoctagag 2340
gagatgogag atgacaagct ggcccagctg attaccgaa cccaggccag gtgcagaggg 2400
5 ttcttggcaa gagtggagta ccagaggatg gtggagagaa gggaggccat ctctgtatc 2460
cagtacaata tcagatcctt catgaatgtc aagcactggc cctggatgaa actcttcttc 2520
10 aagatcaagc ctctgttgaa gagtgcagaa actgagaagg agatggccac catgaaggaa 2580
gaatttcaga aaattaaaga cgaacttgcc aagtcagagg caaaaaggaa ggaactggaa 2640
gaaaagatgg tgacgctgtt gaaagaaaaa aatgacttgc agctccaagt tcaggctgaa 2700
15 gccgaaggct tggctgatgc agaggaaagg tgtgaccagc taatcaaaac caaatccag 2760
ctagaagcca aaatcaaaga ggtgactgag agagctgagg atgaggaaga gatcaatgct 2820
20 gagctgacag ccaagaagag gaaactggag gatgaatgtt cagaactcaa gaaagacatt 2880
gatgaccttg agctgacact ggccaagggt gagaaggaga aacatgccac agaaaacaag 2940
gtgaaaaacc tcacagaaga gatggcagggt ctggatgaaa ccattgctaa gctgaccaag 3000
25 gagaagaagg ctctccagga ggcccaccag cagaccctgg atgacctgca ggcagaggag 3060
gacaaaagtc acaccctgac caaagctaaa atcaaaacttg aacaacaagt ggatgatctt 3120
30 gaagggtcct tggagcaaga aaagaaactt cgcattggacc tagaaagggc taagaggaaa 3180
cttgagggtg acttgaagtt ggccaagaa tccataatgg acattgaaaa tgagaaacag 3240
caacttgatg aaaagctcaa aaagaaagag tttgaaatca gcaatctgca aagcaagatt 3300
35 gaagatgaac aggcaattgg cattcaattg cagaagaaaa ttaaagaatt gcaagcccgc 3360
attgaggagc tggaggagga aatcgaggcg gagcgggcct cccgggccaag agcagagaag 3420
40 cagcgtcttg acctctccg ggagctggag gagatcagcg agaggctgga agaagccggt 3480
ggggccactt cagcccagat tgagatgaac aagaagcggg aggctgagtt ccagaaaatg 3540
cgcagggacc tggaggaggc caccctacag catgaagcca cagcggccac cctgaggaag 3600
45 aagcatgcag atagtgtggc cgagcttggg gagcagattg acaacctgca gcgagtgaag 3660
cagaagctgg agaaggagaa gagtgagatg aagatggaga ttgatgacct tgctagtaat 3720

gtagaaacgg tctccaaagc caagggaaac ctagagaaaa tgtgccggac tctagaggac 3780
caactgagtg aactgaaatc aaaggaagag gagcagcagc ggctgatcaa tgacctgact 3840
5 ggcgagaggg ggcgcctgca gactgaatct ggtgagtttt cacgccagct tgatgaaaag 3900
gaagctctgg tgtctcagtt atcaagaggc aaacaagcct ttactcaaca gattgaagaa 3960
10 ttaaagaggc aacttgaaga ggagataaaa gccaagaacg ccctggcgca tgccctgcag 4020
tcttcccgcc acgactgtga cctgctgcgg gaacagtatg aggaggagca ggaatccaag 4080
gccgagctgc agagagcact gtccaaggcc aacaccgagg ttgccaatg gaggacaaaa 4140
15 tacgagacgg acgccatcca gcgcacagag gagctggagg aggccaagaa gaagctggcc 4200
cagcggctgc aggacagctga ggaacatgta gaagctgtga acgccaatg tgcttcctc 4260
20 gaaaagacga agcagoggct gcagaatgag gtcgaggacc tcatgcttga tgtggagagg 4320
acaaatgccg cctgtgccgc ccttgacaaa aagcaaagga acttcgataa gtcctggca 4380
gaatggaaac agaaatgtga ggaaacgcat gctgagcttg aggcctccca gaaggaggcc 4440
25 cgttcccttg gcactgagct gttcaagata aagaatgcct atgaggaatc tttggatcag 4500
ctagaaacc ctagaagcaga gaacaaaaac ttacagcagg agatttctga cctcacggaa 4560
30 cagattgcag aaggagggaa acgtatccat gaactggaga aaataaagaa acaagtggaa 4620
caagaaaagt gtgaacttca ggctgcttta gaagaagcag aggcattctt tgaacatgaa 4680
gagggaaaga tcctgcgcat ccagcttgag ttgaaccaag tcaagtctga ggttgatagg 4740
35 aaaattgctg aaaaagatga ggaaattgac cagctgaaga gaaaccacat tagaatcgtg 4800
gagtccatgc agagcacgct ggatgctgag atcaggagta ggaatgatgc cattaggctc 4860
40 aagaagaaga tggagggaga cctcaatgaa atggaaatcc agctgaacca tgccaaccgc 4920
atggctgctg aggccctgag gaactacagg aacaccaag gcatcctcaa ggatacccag 4980
atccacctgg atgatgctct ccggagccag gaggacctga aggaacagct ggccatggtg 5040
45 gagcgcagag ccaacctgct gcaggctgag atcgaggagc tgcgggccac tctggaacag 5100
acagagagga gcagaaaaat cgcagaacag gagctcctgg atgccagtga gcgtgttcag 5160

ctactgcaca cccagaacac cagcctgata aacaccaaga agaagctgga gacagatatt 5220
 tcccaaatgc aaggagagat ggaggacatt ctccaggaag ccgcaatgc agaagaaaag 5280
 5 gccagaagg ccatcactga tgccgccatg atggctgagg agctgaagaa ggagcaggac 5340
 accagcggcc acctggagcg gatgaagaag aacatggagc agaccgtgaa ggatctgcag 5400
 10 ctccgtctgg atgaggctga gcagctggcc ctgaagggtg ggaagaagca gatccagaaa 5460
 ctggaggcca ggttacggga gctggaagga gaggttgaga gtgagcaaaa gcgtaatgct 5520
 gaggtctgca aaggtctgcg caaacatgag aggcgagtga aggaactcac ttaccagacg 5580
 15 gaagaagata gaaagaatat tctcaggcct caagatttgg tagataaact tcaggcaaaa 5640
 gtgaaatctt ataagagaca agctgaggag gctgaggaac aatccaacac caatctagct 5700
 20 aaattccgca agctccagca tgagctggag gaggcgagg aacgggctga cattgctgag 5760
 tcccaggtga acaaaactgcg ggtgaagago cgggaggttc acacaaaagt cataagtga 5820
 gagtgatcat gtctgatgc catggaatga ctgaagacag gcacaaaatg tgacatcttt 5880
 25 ggtcatttcc ctctgtaatt attgtgtatt ctacctgtt gcaaaggaaa taaagcatag 5940
 ggtagtttgc aaacaa 5956

30

<210> 2
 <211> 1941
 <212> PRT
 <213> Homo sapiens

35

<400> 2

40

Met Ser Ser Asp Ser Glu Leu Ala Val Phe Gly Glu Ala Ala Pro Phe
 1 5 10 15

Leu Arg Lys Ser Glu Arg Glu Arg Ile Glu Ala Gln Asn Arg Pro Phe
 20 25 30

45

Asp Ala Lys Thr Ser Val Phe Val Ala Glu Pro Lys Glu Ser Phe Val
 35 40 45

Lys Gly Thr Ile Gln Ser Arg Glu Gly Gly Lys Val Thr Val Lys Thr
 50 55 60

5
 Glu Gly Gly Ala Thr Leu Thr Val Lys Asp Asp Gln Val Phe Pro Met
 65 70 75 80

10 Asn Pro Pro Lys Tyr Asp Lys Ile Glu Asp Met Ala Met Met Thr His
 85 90 95

15 Leu His Glu Pro Ala Val Leu Tyr Asn Leu Lys Glu Arg Tyr Ala Ala
 100 105 110

20 Trp Met Ile Tyr Thr Tyr Ser Gly Leu Phe Cys Val Thr Val Asn Pro
 115 120 125

Tyr Lys Trp Leu Pro Val Tyr Lys Pro Glu Val Val Thr Ala Tyr Arg
 130 135 140

25 Gly Lys Lys Arg Gln Glu Ala Pro Pro His Ile Phe Ser Ile Ser Asp
 145 150 155 160

30 Asn Ala Tyr Gln Phe Met Leu Thr Asp Arg Glu Asn Gln Ser Ile Leu
 165 170 175

35 Ile Thr Gly Glu Ser Gly Ala Gly Lys Thr Val Asn Thr Lys Arg Val
 180 185 190

40 Ile Gln Tyr Phe Ala Thr Ile Ala Val Thr Gly Glu Lys Lys Lys Glu
 195 200 205

Glu Ile Thr Ser Gly Lys Ile Gln Gly Thr Leu Glu Asp Gln Ile Ile
 210 215 220

45 Ser Ala Asn Pro Leu Leu Glu Ala Phe Gly Asn Ala Lys Thr Val Arg
 225 230 235 240

Asn Asp Asn Ser Ser Arg Phe Gly Lys Phe Ile Arg Ile His Phe Gly
245 250 255

5 Thr Thr Gly Lys Leu Ala Ser Ala Asp Ile Glu Thr Tyr Leu Leu Glu
260 265 270

10 Lys Ser Arg Val Val Phe Gln Leu Lys Ala Glu Arg Ser Tyr His Ile
275 280 285

15 Phe Tyr Gln Ile Thr Ser Asn Lys Lys Pro Glu Leu Ile Glu Met Leu
290 295 300

20 Leu Ile Thr Thr Asn Pro Tyr Asp Tyr Pro Phe Val Ser Gln Gly Glu
305 310 315 320

Ile Ser Val Ala Ser Ile Asp Asp Gln Glu Glu Leu Met Ala Thr Asp
325 330 335

25 Ser Ala Ile Asp Ile Leu Gly Phe Thr Asn Glu Glu Lys Val Ser Ile
340 345 350

30 Tyr Lys Leu Thr Gly Ala Val Met His Tyr Gly Asn Leu Lys Phe Lys
355 360 365

35 Gln Lys Gln Arg Glu Glu Gln Ala Glu Pro Asp Gly Thr Glu Val Ala
370 375 380

40 Asp Lys Ala Ala Tyr Leu Gln Ser Leu Asn Ser Ala Asp Leu Leu Lys
385 390 395 400

Ala Leu Cys Tyr Pro Arg Val Lys Val Gly Asn Glu Tyr Val Thr Lys
405 410 415

45 Gly Gln Thr Val Glu Gln Val Ser Asn Ala Val Gly Ala Leu Ala Lys
420 425 430

Ala Val Tyr Glu Lys Met Phe Leu Trp Met Val Ala Arg Ile Asn Gln
435 440 445

5
Gln Leu Asp Thr Lys Gln Pro Arg Gln Tyr Phe Ile Gly Val Leu Asp
450 455 460

10
Ile Ala Gly Phe Glu Ile Phe Asp Phe Asn Ser Leu Glu Gln Leu Cys
465 470 475 480

15
Ile Asn Phe Thr Asn Glu Lys Leu Gln Gln Phe Phe Asn His His Met
485 490 495

20
Phe Val Leu Glu Gln Glu Glu Tyr Lys Lys Glu Gly Ile Glu Trp Thr
500 505 510

25
Phe Ile Asp Phe Gly Met Asp Leu Ala Ala Cys Ile Glu Leu Ile Glu
515 520 525

30
Lys Pro Met Gly Ile Phe Ser Ile Leu Glu Glu Glu Cys Met Phe Pro
530 535 540

35
Gly Lys Ser Ala Asn Phe Gln Lys Pro Lys Val Val Lys Gly Lys Ala
565 570 575

40
Glu Ala His Phe Ala Leu Ile His Tyr Ala Gly Val Val Asp Tyr Asn
580 585 590

45
Ile Thr Gly Trp Leu Glu Lys Asn Lys Asp Pro Leu Asn Glu Thr Val
595 600 605

Val Gly Leu Tyr Gln Lys Ser Ala Met Lys Thr Leu Ala Gln Leu Phe
610 615 620

Ser Gly Ala Gln Thr Ala Glu Gly Glu Gly Ala Gly Gly Gly Ala Lys
625 630 635 640

5 Lys Gly Gly Lys Lys Lys Gly Ser Ser Phe Gln Thr Val Ser Ala Leu
645 650 655

10 Phe Arg Glu Asn Leu Asn Lys Leu Met Thr Asn Leu Arg Ser Thr His
660 665 670

15 Pro His Phe Val Arg Cys Ile Ile Pro Asn Glu Thr Lys Thr Pro Gly
675 680 685

20 Ala Met Glu His Glu Leu Val Leu His Gln Leu Arg Cys Asn Gly Val
690 695 700

25 Leu Glu Gly Ile Arg Ile Cys Arg Lys Gly Phe Pro Ser Arg Ile Leu
705 710 715 720

30 Tyr Ala Asp Phe Lys Gln Arg Tyr Lys Val Leu Asn Ala Ser Ala Ile
725 730 735

35 Pro Glu Gly Gln Phe Ile Asp Ser Lys Lys Ala Ser Glu Lys Leu Leu
740 745 750

40 Ala Ser Ile Asp Ile Asp His Thr Gln Tyr Lys Phe Gly His Thr Lys
755 760 765

45 Val Phe Phe Lys Ala Gly Leu Leu Gly Leu Leu Glu Glu Met Arg Asp
770 775 780

Asp Lys Leu Ala Gln Leu Ile Thr Arg Thr Gln Ala Arg Cys Arg Gly
785 790 795 800

Phe Leu Ala Arg Val Glu Tyr Gln Arg Met Val Glu Arg Arg Glu Ala
805 810 815

Ile Phe Cys Ile Gln Tyr Asn Ile Arg Ser Phe Met Asn Val Lys His
820 825 830

5 Trp Pro Trp Met Lys Leu Phe Phe Lys Ile Lys Pro Leu Leu Lys Ser
835 840 845

10 Ala Glu Thr Glu Lys Glu Met Ala Thr Met Lys Glu Glu Phe Gln Lys
850 855 860

15 Ile Lys Asp Glu Leu Ala Lys Ser Glu Ala Lys Arg Lys Glu Leu Glu
865 870 875 880

Glu Lys Met Val Thr Leu Leu Lys Glu Lys Asn Asp Leu Gln Leu Gln
885 890 895

20 Val Gln Ala Glu Ala Glu Gly Leu Ala Asp Ala Glu Glu Arg Cys Asp
900 905 910

25 Gln Leu Ile Lys Thr Lys Ile Gln Leu Glu Ala Lys Ile Lys Glu Val
915 920 925

30 Thr Glu Arg Ala Glu Asp Glu Glu Glu Ile Asn Ala Glu Leu Thr Ala
930 935 940

35 Lys Lys Arg Lys Leu Glu Asp Glu Cys Ser Glu Leu Lys Lys Asp Ile
945 950 955 960

40 Asp Asp Leu Glu Leu Thr Leu Ala Lys Val Glu Lys Glu Lys His Ala
965 970 975

Thr Glu Asn Lys Val Lys Asn Leu Thr Glu Glu Met Ala Gly Leu Asp
980 985 990

45 Glu Thr Ile Ala Lys Leu Thr Lys Glu Lys Lys Ala Leu Gln Glu Ala
995 1000 1005

	His	Gln	Gln	Thr	Leu	Asp	Asp	Leu	Gln	Ala	Glu	Glu	Asp	Lys	Val
	1010						1015					1020			
5	Asn	Thr	Leu	Thr	Lys	Ala	Lys	Ile	Lys	Leu	Glu	Gln	Gln	Val	Asp
	1025						1030					1035			
10	Asp	Leu	Glu	Gly	Ser	Leu	Glu	Gln	Glu	Lys	Lys	Leu	Arg	Met	Asp
	1040						1045					1050			
15	Leu	Glu	Arg	Ala	Lys	Arg	Lys	Leu	Glu	Gly	Asp	Leu	Lys	Leu	Ala
	1055						1060					1065			
20	Gln	Glu	Ser	Ile	Met	Asp	Ile	Glu	Asn	Glu	Lys	Gln	Gln	Leu	Asp
	1070						1075					1080			
25	Glu	Lys	Leu	Lys	Lys	Lys	Glu	Phe	Glu	Ile	Ser	Asn	Leu	Gln	Ser
	1085						1090					1095			
30	Lys	Ile	Glu	Asp	Glu	Gln	Ala	Leu	Gly	Ile	Gln	Leu	Gln	Lys	Lys
	1100						1105					1110			
35	Ile	Lys	Glu	Leu	Gln	Ala	Arg	Ile	Glu	Glu	Leu	Glu	Glu	Glu	Ile
	1115						1120					1125			
40	Glu	Ala	Glu	Arg	Ala	Ser	Arg	Ala	Lys	Ala	Glu	Lys	Gln	Arg	Ser
	1130						1135					1140			
45	Asp	Leu	Ser	Arg	Glu	Leu	Glu	Glu	Ile	Ser	Glu	Arg	Leu	Glu	Glu
	1145						1150					1155			
50	Ala	Gly	Gly	Ala	Thr	Ser	Ala	Gln	Ile	Glu	Met	Asn	Lys	Lys	Arg
	1160						1165					1170			
55	Glu	Ala	Glu	Phe	Gln	Lys	Met	Arg	Arg	Asp	Leu	Glu	Glu	Ala	Thr
	1175						1180					1185			

	Leu	Gln	His	Glu	Ala	Thr	Ala	Ala	Thr	Leu	Arg	Lys	Lys	His	Ala
	1190						1195					1200			
5	Asp	Ser	Val	Ala	Glu	Leu	Gly	Glu	Gln	Ile	Asp	Asn	Leu	Gln	Arg
	1205						1210					1215			
10	Val	Lys	Gln	Lys	Leu	Glu	Lys	Glu	Lys	Ser	Glu	Met	Lys	Met	Glu
	1220						1225					1230			
15	Ile	Asp	Asp	Leu	Ala	Ser	Asn	Val	Glu	Thr	Val	Ser	Lys	Ala	Lys
	1235						1240					1245			
20	Gly	Asn	Leu	Glu	Lys	Met	Cys	Arg	Thr	Leu	Glu	Asp	Gln	Leu	Ser
	1250						1255					1260			
25	Glu	Leu	Lys	Ser	Lys	Glu	Glu	Glu	Gln	Gln	Arg	Leu	Ile	Asn	Asp
	1265						1270					1275			
30	Leu	Thr	Ala	Gln	Arg	Gly	Arg	Leu	Gln	Thr	Glu	Ser	Gly	Glu	Phe
	1280						1285					1290			
35	Ser	Arg	Gln	Leu	Asp	Glu	Lys	Glu	Ala	Leu	Val	Ser	Gln	Leu	Ser
	1295						1300					1305			
40	Arg	Gly	Lys	Gln	Ala	Phe	Thr	Gln	Gln	Ile	Glu	Glu	Leu	Lys	Arg
	1310						1315					1320			
45	Gln	Leu	Glu	Glu	Glu	Ile	Lys	Ala	Lys	Asn	Ala	Leu	Ala	His	Ala
	1325						1330					1335			
50	Leu	Gln	Ser	Ser	Arg	His	Asp	Cys	Asp	Leu	Leu	Arg	Glu	Gln	Tyr
	1340						1345					1350			
55	Glu	Glu	Glu	Gln	Glu	Ser	Lys	Ala	Glu	Leu	Gln	Arg	Ala	Leu	Ser
	1355						1360					1365			

	Lys Ala Asn Thr Glu Val Ala Gln Trp Arg Thr Lys Tyr Glu Thr	
	1370	1375 1380
5	Asp Ala Ile Gln Arg Thr Glu Glu Leu Glu Glu Ala Lys Lys Lys	
	1385	1390 1395
10	Leu Ala Gln Arg Leu Gln Ala Ala Glu Glu His Val Glu Ala Val	
	1400	1405 1410
15	Asn Ala Lys Cys Ala Ser Leu Glu Lys Thr Lys Gln Arg Leu Gln	
	1415	1420 1425
20	Asn Glu Val Glu Asp Leu Met Leu Asp Val Glu Arg Thr Asn Ala	
	1430	1435 1440
	Ala Cys Ala Ala Leu Asp Lys Lys Gln Arg Asn Phe Asp Lys Ile	
	1445	1450 1455
25	Leu Ala Glu Trp Lys Gln Lys Cys Glu Glu Thr His Ala Glu Leu	
	1460	1465 1470
30	Glu Ala Ser Gln Lys Glu Ala Arg Ser Leu Gly Thr Glu Leu Phe	
	1475	1480 1485
35	Lys Ile Lys Asn Ala Tyr Glu Glu Ser Leu Asp Gln Leu Glu Thr	
	1490	1495 1500
40	Leu Lys Arg Glu Asn Lys Asn Leu Gln Gln Glu Ile Ser Asp Leu	
	1505	1510 1515
	Thr Glu Gln Ile Ala Glu Gly Gly Lys Arg Ile His Glu Leu Glu	
	1520	1525 1530
45	Lys Ile Lys Lys Gln Val Glu Gln Glu Lys Cys Glu Leu Gln Ala	
	1535	1540 1545

Ala Leu Glu Glu Ala Glu Ala Ser Leu Glu His Glu Glu Gly Lys
1550 1555 1560

5
Ile Leu Arg Ile Gln Leu Glu Leu Asn Gln Val Lys Ser Glu Val
1565 1570 1575

10
Asp Arg Lys Ile Ala Glu Lys Asp Glu Glu Ile Asp Gln Leu Lys
1580 1585 1590

15
Arg Asn His Ile Arg Ile Val Glu Ser Met Gln Ser Thr Leu Asp
1595 1600 1605

20
Ala Glu Ile Arg Ser Arg Asn Asp Ala Ile Arg Leu Lys Lys Lys
1610 1615 1620

25
Met Glu Gly Asp Leu Asn Glu Met Glu Ile Gln Leu Asn His Ala
1625 1630 1635

30
Asn Arg Met Ala Ala Glu Ala Leu Arg Asn Tyr Arg Asn Thr Gln
1640 1645 1650

35
Gly Ile Leu Lys Asp Thr Gln Ile His Leu Asp Asp Ala Leu Arg
1655 1660 1665

40
Ser Gln Glu Asp Leu Lys Glu Gln Leu Ala Met Val Glu Arg Arg
1670 1675 1680

45
Ala Asn Leu Leu Gln Ala Glu Ile Glu Glu Leu Arg Ala Thr Leu
1685 1690 1695

50
Glu Gln Thr Glu Arg Ser Arg Lys Ile Ala Glu Gln Glu Leu Leu
1700 1705 1710

55
Asp Ala Ser Glu Arg Val Gln Leu Leu His Thr Gln Asn Thr Ser
1715 1720 1725

	Leu Ile Asn Thr Lys Lys Lys	Leu Glu Thr Asp Ile Ser Gln Met
	1730	1740
5	Gln Gly Glu Met Glu Asp Ile	Leu Gln Glu Ala Arg Asn Ala Glu
	1745	1755
10	Glu Lys Ala Lys Lys Ala Ile	Thr Asp Ala Ala Met Met Ala Glu
	1760	1770
15	Glu Leu Lys Lys Glu Gln Asp	Thr Ser Ala His Leu Glu Arg Met
	1775	1785
20	Lys Lys Asn Met Glu Gln Thr	Val Lys Asp Leu Gln Leu Arg Leu
	1790	1800
	Asp Glu Ala Glu Gln Leu Ala	Leu Lys Gly Gly Lys Lys Gln Ile
	1805	1815
25	Gln Lys Leu Glu Ala Arg Val	Arg Glu Leu Glu Gly Glu Val Glu
	1820	1830
30	Ser Glu Gln Lys Arg Asn Ala	Glu Ala Val Lys Gly Leu Arg Lys
	1835	1845
35	His Glu Arg Arg Val Lys Glu	Leu Thr Tyr Gln Thr Glu Glu Asp
	1850	1860
40	Arg Lys Asn Ile Leu Arg Leu	Gln Asp Leu Val Asp Lys Leu Gln
	1865	1875
	Ala Lys Val Lys Ser Tyr Lys	Arg Gln Ala Glu Glu Ala Glu Glu
	1880	1890
45	Gln Ser Asn Thr Asn Leu Ala	Lys Phe Arg Lys Leu Gln His Glu
	1895	1905

Leu Glu Glu Ala Glu Glu Arg Ala Asp Ile Ala Glu Ser Gln Val
 1910 1915 1920

5

Asn Lys Leu Arg Val Lys Ser Arg Glu Val His Thr Lys Val Ile
 1925 1930 1935

10 Ser Glu Glu
 1940

15 <210> 3
 <211> 6016
 <212> DNA
 <213> Homo sapiens

<400> 3
 20 atccttcctc aaaattcttg aagtagttgt ctgctttgag cctgccacct tcttcatctg 60
 ataatacaag aggtatacct agtccagcac tgccatcaat aacctgcagc catgagttct 120
 gactctgaga tggccatttt tggggaggct gtccttttcc tccgaaagtc tgaagaggag 180
 25 cgaattgaag ctccagaaca gccttttgat gccaaagacat cagtctttgt ggtggaccct 240
 aaggagtcct acgtgaaagc aatagtgcag agcagggaag gggggaaggt gacagccaag 300
 30 accgaagctg gagctactgt aactgtgaaa gaagaccaag tcttctccat gaaccctccc 360
 aaatatgaca agatcgagga catggccatg atgactcacc tgcattgagc tgctgtgctg 420
 tataacctca aagagcgtaa cgcagcctgg atgatctaca cctactcggg cctcttctgt 480
 35 gtcaccgtca acccctacaa gtggctgccg gtgtacaacc ctgaggtggt gacagcctac 540
 cgaggcaaaa agcgcagga ggccccaccc catatcttct ccatctctga caatgcctat 600
 40 cagttcatgc taactgatcg tgaagaccag tcaatcttga ttactggaga atctggtgca 660
 gggaagactg tgaacacgaa gcgtgtcatc cagtactttg caacaattgc agttactgga 720
 gagaagaaaa aagaggaacc tgctctggc aaaatgcagg ggacccttga agatcaaac 780
 45 atcagtgcta accccctact ggaagccttc ggcaatgcc aagaccgtgag gaatgacaac 840
 tcctctcgct ttggtaaatt catcaggatc cattttggtg ccacaggcaa actggcttct 900

gcagatattg aaacatatct gctagagaag tcccagagta cttttcagct aaaggctgaa 960
agaagctacc acatatTTta tcaaatcctg tccaataaga aaccagagct cattgaaatg 1020
5 cttctgatca ccaccaaccc atatgacttc gcatttgtca gccaaagggga aattactgtg 1080
cccagcattg atgaccagga agagctgatg gccacagata gtgctgtgga catcctgggt 1140
10 ttcaactgctg atgaaaaggT ggccattttac aagctcactg gagccgtgat gcattatggg 1200
aacatgaaat tcaagcaaaa gcaaagggaa gagcaggcag agccagatgg cacggaagtt 1260
gctgacaaag ctgcttatct gacaagtctg aactctgctg acctgctcaa atctctctgc 1320
15 tatcccagag tcaaggctcg caatgagttc gtaaccaaag gccagactgt gcagcaggtg 1380
tacaacgcag tgggtgctct ggccaaagcc atctacgaga agatgttctt gtggatggtc 1440
20 acccgcatca accagcagct ggacaccaag cagcccaggc agtacttcat cggggtcttg 1500
gacattgctg gctttgagat ctttgatttc aacagcctgg agcagctgtg catcaacttc 1560
accaacgaga aactgcaaca gtttttcaac caccacatgt tcgtgctgga gcaggaagag 1620
25 tacaagaagg aaggcatcga gtgggagttc attgacttcg ggatggacct ggctgcctgc 1680
atcgagotca tcgagaagcc tatgggcata ttctccatcc tagaagagga gtgcatgttc 1740
30 cccaaggcaa cagacacctc ctccaagaac aagctgtatg aacaacatct tggaaaatcc 1800
aacaacttcc agaagcccaa gcctgccaaa ggcaagcctg aggctcactt ctactgggtg 1860
cactatgccg gcaccgtgga ctacaacatc gccggctggc tggacaaaaa caaggacccc 1920
35 ctgaatgaga ctgtgggtgg gctgtaccag aagtctgcaa tgaagactct ggctttcttc 1980
ttctctgggg cacaaactgc tgaagcagag ggtgggtggg gaaagaaagg tggcaaaaag 2040
40 aagggttctt ctttccagac agtgtcagct cttttcaggg agaatttgaa taagctgatg 2100
accaacttga ggagcactca cccccacttt gtgcggtgca tcatcccaa tgaaactaaa 2160
actcctgggtg ccatggagca tgagcttgtc ctgcatcagc tgagggtgaa cgggtgtgctg 2220
45 gaaggcatcc gcatctgcag gaaaggcttc ccaagcagaa tcctttatgc agacttcaaa 2280
cagagataca aggttctaaa tgcgagtgt atcccagagg gtcagttcat tgacagcaag 2340

aaggcttctg agaaacttct agggctctatt gaaattgacc acaccagta caaattcgggt 2400
cataccaagg ttttcttcaa agctggcctg ctgggaactc tagaagaaat gcgagatgaa 2460
5 aagctagctc aactcatcac gcgcactcaa gccatatgca gggggttcct gatgagagt 2520
gagttcagaa agatgatgga gaggagagag tccatcttct gcattcagta caacatccgt 2580
10 gctttcatga atgtgaagca ctggccctgg atgaagctgt atttcaagat caagcccctc 2640
ctcaagagtgc cagagacaga gaaggagatg gccaacatga aggaagaatt tgagaaaacc 2700
aaagaagagc tggctaagac agaggcaaaa aggaaagaac tagaagaaaa gatggtgacg 2760
15 ctaatgcaag agaaaaatga cttacaactc caagticaag ctgaagcaga tgccttggct 2820
gatgcagagg aaagatgtga tcagttgatt aaaacaaaa tccaacttga ggccaaaatc 2880
20 aaagaggtaa ctgaaagagc tgaggatgag gaagagatca atgctgagct gacagccaag 2940
aagaggaaac tggaggatga atgttcagag ctcaagaaag acattgatga ccttgagctg 3000
aacttgcca aggttgagaa ggagaaacat gccacagaga acaaggtgaa aaacctcaca 3060
25 gaagagatgg caggtctgga tgaaccatt gctaagctga ccaaggagaa gaaggctctc 3120
caggaggccc accagcagac cctggatgac ctgcagatgg aggaggacaa agtcaacacc 3180
30 ctgaccaaag ctaaaacca gctagaacag caagtggacg atcttgaagg atctctggaa 3240
caagaaaaga aactttgcat ggacttagaa agagccaaga gaaaactgga gggtagaccta 3300
aaattggccc aagaatccac aatggataca gaaaatgaca aacagcaact taatgagaaa 3360
35 ctcaaaaaga aagagtttga aatgagcaat ctgcaaggca agattgaaga tgaacaagcc 3420
cttgcaatgc agctacaaaa gaagatcaaa gaattacagg cccgcattga ggagctggag 3480
40 gaggaaatcg aggcagagcg ggcctcccgg gccaaagcag aaaagcagcg ctctgacctc 3540
tcccgggagc tggaggagat cagtgagagg ctggaagaag ccggtggggc cacttcagcc 3600
cagattgagt tgaacaagaa gcgggaggct gagttccaga aaatgcgcag ggacctggaa 3660
45 gagtccaccc tgcagcacga agccacggca gctgctcttc ggaagaagca cgcagatagt 3720
gtggctgagc ttgggaagca gatcgacagc cttcagcggg tcaagcagaa gctggagaag 3780

gaaaagagtg agctgaagat ggagatcaat gaccttgcta gtaacatgga gactgtctcc 3840
aaagccaagg caaactttga gaaaatgtgc cgcaccctag aggaccagct tagtgaaata 3900
5 aaaacaaagg aagaagagca gcaacgctta ataatgagt tgtcagccca gaaggcacgt 3960
ttacacacag aatcaggtga gttttcacga cagctagatg aaaaagatgc tatggtttct 4020
10 cagctatccc gaggcaaaca agcatttaca caacagattg aagaattaaa gaggcagcta 4080
gaagaggaga ctaaggccaa gagcactctg gcccatgccc tgcagtcagc cgcctatgac 4140
tgtgacctgc tgcgggaaca gtatgaggag gagcaggaag ccaaggctga gctgcagagg 4200
15 ggaatgtcca aggccaacag tgaggttgcc cagtggagga ccaagtacga gacggacgcc 4260
atccagcgca cagaggagct ggaggaggcc aagaagaagc tagcccagcg tctgcaggat 4320
20 gcagaagaac atgtagaagc tgtgaattcc aaatgtgctt ctcttgaaaa gacaaagcag 4380
aggctacaga atgaagtaga ggacctcatg attgatgtgg aacgatctaa tgctgcctgc 4440
atagctctcg ataagaagca aagaaacttt gacaaggttc tggcagaatg gaaacagaag 4500
25 tatgaggaaa ctgaggctga acttgaggcc tcccagaagg agtcgcgttc tctcagcact 4560
gagctgttca aggtgaagaa tgcctacgag gaatccctgg atcatcttga aactctaaag 4620
30 cgagagaata agaacttaca acaggagatt tctgacctga cagagcaaata tgcagagggt 4680
ggaaagcata tccatgaact ggagaaagta aagaacaac ttgatcatga gaagagtga 4740
ctacagactt ccctagagga agcagaggca tctcttgagc atgaagaagg caaaattctt 4800
35 cgcatccaac ttgagctaaa tcagggtgaaa tctgagattg accgaaaaat tgctgaaaaa 4860
gatgaagaac tcgatcagct aaagaggaac catctcagag ttgtggagtc aatgcagagt 4920
40 acactggatg ctgagatcag gagcagaaat gatgctctga ggatcaagaa gaagatggag 4980
ggagatctta atgaaatgga aatccagctg aacctgcca accgccaggc tgctgaggca 5040
ctaaggaatc ttagaaacac acaaggaata ctgaaggaca ctgagctaca tttggatgat 5100
45 gccatcagag gccaaagatga ccttaaggaa caattggcaa tggttgagcg cagagctaac 5160
ctgatgcagg ctgaagttga agagctcagg gcatccctgg aacggactga gagaggcagg 5220

5 aaaatggcag agcaagagct tctggatgcc agtgaacgtg tgcaacttct gcacactcag 5280
 aacaccagcc tgatcaacac caagaagaag ctggaaacag acatttccca aatccaggga 5340
 10 gagatggagg acatcgtcca ggaagcccg c aatgcagagg agaaggccaa gaaggccatc 5400
 actgatgctg ccatgatggc tgaggagctg aagaaggaac aggacaccag cgcccacctg 5460
 gagcggatga agaagaacat ggagcagacc gtgaaggatc tgcagctccg tctgggtgag 5520
 gctgagcagc tggcgctgaa ggggtgggaag aagcagatcc agaaactgga ggccagggtg 5580
 15 agagagcttg aaagtgaggt ggaaagtga cagaagcaca atgttgaggc tgtcaagggt 5640
 cttcgcaaac atgagagaag agtgaaggaa ctcaacttacc agactgagga ggaccgcaag 5700
 aatattotca ggctgcagga cttggtggac aaattgcaaa ccaaagtcaa agcttacaag 5760
 20 agacaagctg aagaggctga ggaacaatcc aatgtcaacc ttgccaagtt ccgcaagctc 5820
 cagcacgagc tggaggaggc cgaggaacgg gctgacattg ctgagtccca agtcaacaag 5880
 ctgagagtga agagtcggga ggttcacaca aaagtcataa gtgaagagta attcattcta 5940
 25 atgaaagaaa atgtgaccaa agaaatgcac gaaatgtgaa gttctttgtc actgtcctgt 6000
 atatcaagga aataaa 6016

30

<210> 4
 <211> 1939
 <212> PRT
 <213> Homo sapiens

35

<400> 4

40

Met Ser Ser Asp Ser Glu Met Ala Ile Phe Gly Glu Ala Ala Pro Phe
 1 5 10 15

Leu Arg Lys Ser Glu Lys Glu Arg Ile Glu Ala Gln Asn Lys Pro Phe
 20 25 30

45

Asp Ala Lys Thr Ser Val Phe Val Val Asp Pro Lys Glu Ser Tyr Val
 35 40 45

Lys Ala Ile Val Gln Ser Arg Glu Gly Gly Lys Val Thr Ala Lys Thr
50 55 60

5
Glu Ala Gly Ala Thr Val Thr Val Lys Glu Asp Gln Val Phe Ser Met
65 70 75 80

10
Asn Pro Pro Lys Tyr Asp Lys Ile Glu Asp Met Ala Met Met Thr His
85 90 95

15
Leu His Glu Pro Ala Val Leu Tyr Asn Leu Lys Glu Arg Tyr Ala Ala
100 105 110

20
Trp Met Ile Tyr Thr Tyr Ser Gly Leu Phe Cys Val Thr Val Asn Pro
115 120 125

25
Tyr Lys Trp Leu Pro Val Tyr Asn Pro Glu Val Val Thr Ala Tyr Arg
130 135 140

30
Asn Ala Tyr Gln Phe Met Leu Thr Asp Arg Glu Asn Gln Ser Ile Leu
165 170 175

35
Ile Thr Gly Glu Ser Gly Ala Gly Lys Thr Val Asn Thr Lys Arg Val
180 185 190

40
Ile Gln Tyr Phe Ala Thr Ile Ala Val Thr Gly Glu Lys Lys Lys Glu
195 200 205

45
Glu Pro Ala Ser Gly Lys Met Gln Gly Thr Leu Glu Asp Gln Ile Ile
210 215 220

50
Ser Ala Asn Pro Leu Leu Glu Ala Phe Gly Asn Ala Lys Thr Val Arg
225 230 235 240

Asn Asp Asn Ser Ser Arg Phe Gly Lys Phe Ile Arg Ile His Phe Gly
245 250 255

5
Ala Thr Gly Lys Leu Ala Ser Ala Asp Ile Glu Thr Tyr Leu Leu Glu
260 265 270

10
Lys Ser Arg Val Thr Phe Gln Leu Lys Ala Glu Arg Ser Tyr His Ile
275 280 285

15
Phe Tyr Gln Ile Leu Ser Asn Lys Lys Pro Glu Leu Ile Glu Met Leu
290 295 300

20
Leu Ile Thr Thr Asn Pro Tyr Asp Phe Ala Phe Val Ser Gln Gly Glu
305 310 315 320

Ile Thr Val Pro Ser Ile Asp Asp Gln Glu Glu Leu Met Ala Thr Asp
325 330 335

25
Ser Ala Val Asp Ile Leu Gly Phe Thr Ala Asp Glu Lys Val Ala Ile
340 345 350

30
Tyr Lys Leu Thr Gly Ala Val Met His Tyr Gly Asn Met Lys Phe Lys
355 360 365

35
Gln Lys Gln Arg Glu Glu Gln Ala Glu Pro Asp Gly Thr Glu Val Ala
370 375 380

40
Asp Lys Ala Ala Tyr Leu Thr Ser Leu Asn Ser Ala Asp Leu Leu Lys
385 390 395 400

Ser Leu Cys Tyr Pro Arg Val Lys Val Gly Asn Glu Phe Val Thr Lys
405 410 415

45
Gly Gln Thr Val Gln Gln Val Tyr Asn Ala Val Gly Ala Leu Ala Lys
420 425 430

Ala Ile Tyr Glu Lys Met Phe Leu Trp Met Val Thr Arg Ile Asn Gln
435 440 445

5
Gln Leu Asp Thr Lys Gln Pro Arg Gln Tyr Phe Ile Gly Val Leu Asp
450 455 460

10
Ile Ala Gly Phe Glu Ile Phe Asp Phe Asn Ser Leu Glu Gln Leu Cys
465 470 475 480

15
Ile Asn Phe Thr Asn Glu Lys Leu Gln Gln Phe Phe Asn His His Met
485 490 495

20
Phe Val Leu Glu Gln Glu Glu Tyr Lys Lys Glu Gly Ile Glu Trp Glu
500 505 510

25
Phe Ile Asp Phe Gly Met Asp Leu Ala Ala Cys Ile Glu Leu Ile Glu
515 520 525

30
Lys Pro Met Gly Ile Phe Ser Ile Leu Glu Glu Glu Cys Met Phe Pro
530 535 540

35
Gly Lys Ser Asn Asn Phe Gln Lys Pro Lys Pro Ala Lys Gly Lys Pro
565 570 575

40
Glu Ala His Phe Ser Leu Val His Tyr Ala Gly Thr Val Asp Tyr Asn
580 585 590

45
Ile Ala Gly Trp Leu Asp Lys Asn Lys Asp Pro Leu Asn Glu Thr Val
595 600 605

Val Gly Leu Tyr Gln Lys Ser Ala Met Lys Thr Leu Ala Phe Leu Phe
610 615 620

Ser Gly Ala Gln Thr Ala Glu Ala Glu Gly Gly Gly Gly Lys Lys Gly
625 630 635 640

5 Gly Lys Lys Lys Gly Ser Ser Phe Gln Thr Val Ser Ala Leu Phe Arg
645 650 655

10 Glu Asn Leu Asn Lys Leu Met Thr Asn Leu Arg Ser Thr His Pro His
660 665 670

15 Phe Val Arg Cys Ile Ile Pro Asn Glu Thr Lys Thr Pro Gly Ala Met
675 680 685

20 Glu His Glu Leu Val Leu His Gln Leu Arg Cys Asn Gly Val Leu Glu
690 695 700

Gly Ile Arg Ile Cys Arg Lys Gly Phe Pro Ser Arg Ile Leu Tyr Ala
705 710 715 720

25 Asp Phe Lys Gln Arg Tyr Lys Val Leu Asn Ala Ser Ala Ile Pro Glu
725 730 735

30 Gly Gln Phe Ile Asp Ser Lys Lys Ala Ser Glu Lys Leu Leu Gly Ser
740 745 750

35 Ile Glu Ile Asp His Thr Gln Tyr Lys Phe Gly His Thr Lys Val Phe
755 760 765

Phe Lys Ala Gly Leu Leu Gly Thr Leu Glu Glu Met Arg Asp Glu Lys
770 775 780

40 Leu Ala Gln Leu Ile Thr Arg Thr Gln Ala Ile Cys Arg Gly Phe Leu
785 790 795 800

45 Met Arg Val Glu Phe Arg Lys Met Met Glu Arg Arg Glu Ser Ile Phe
805 810 815

Cys Ile Gln Tyr Asn Ile Arg Ala Phe Met Asn Val Lys His Trp Pro
 820 825 830

5

Trp Met Lys Leu Tyr Phe Lys Ile Lys Pro Leu Leu Lys Ser Ala Glu
 835 840 845

10

Thr Glu Lys Glu Met Ala Asn Met Lys Glu Glu Phe Glu Lys Thr Lys
 850 855 860

15

Glu Glu Leu Ala Lys Thr Glu Ala Lys Arg Lys Glu Leu Glu Glu Lys
 865 870 875 880

20

Met Val Thr Leu Met Gln Glu Lys Asn Asp Leu Gln Leu Gln Val Gln
 885 890 895

25

Ala Glu Ala Asp Ala Leu Ala Asp Ala Glu Glu Arg Cys Asp Gln Leu
 900 905 910

30

Ile Lys Thr Lys Ile Gln Leu Glu Ala Lys Ile Lys Glu Val Thr Glu
 915 920 925

35

Arg Ala Glu Asp Glu Glu Glu Ile Asn Ala Glu Leu Thr Ala Lys Lys
 930 935 940

40

Arg Lys Leu Glu Asp Glu Cys Ser Glu Leu Lys Lys Asp Ile Asp Asp
 945 950 955 960

45

Leu Glu Leu Thr Leu Ala Lys Val Glu Lys Glu Lys His Ala Thr Glu
 965 970 975

Asn Lys Val Lys Asn Leu Thr Glu Glu Met Ala Gly Leu Asp Glu Thr
 980 985 990

Ile Ala Lys Leu Thr Lys Glu Lys Lys Ala Leu Gln Glu Ala His Gln
 995 1000 1005

	Gln Thr	Leu Asp Asp Leu Gln	Met Glu Glu Asp Lys	Val Asn Thr
	1010	1015	1020	
5	Leu Thr	Lys Ala Lys Thr Lys	Leu Glu Gln Gln Val	Asp Asp Leu
	1025	1030	1035	
10	Glu Gly	Ser Leu Glu Gln Glu	Lys Lys Leu Cys Met	Asp Leu Glu
	1040	1045	1050	
15	Arg Ala	Lys Arg Lys Leu Glu	Gly Asp Leu Lys Leu	Ala Gln Glu
	1055	1060	1065	
20	Ser Thr	Met Asp Thr Glu Asn	Asp Lys Gln Gln Leu	Asn Glu Lys
	1070	1075	1080	
25	Leu Lys	Lys Lys Glu Phe Glu	Met Ser Asn Leu Gln	Gly Lys Ile
	1085	1090	1095	
30	Glu Asp	Glu Gln Ala Leu Ala	Met Gln Leu Gln Lys	Lys Ile Lys
	1100	1105	1110	
35	Glu Leu	Gln Ala Arg Ile Glu	Glu Leu Glu Glu Glu	Ile Glu Ala
	1115	1120	1125	
40	Glu Arg	Ala Ser Arg Ala Lys	Ala Glu Lys Gln Arg	Ser Asp Leu
	1130	1135	1140	
45	Ser Arg	Glu Leu Glu Glu Ile	Ser Glu Arg Leu Glu	Glu Ala Gly
	1145	1150	1155	
50	Gly Ala	Thr Ser Ala Gln Ile	Glu Leu Asn Lys Lys	Arg Glu Ala
	1160	1165	1170	
55	Glu Phe	Gln Lys Met Arg Arg	Asp Leu Glu Glu Ser	Thr Leu Gln
	1175	1180	1185	

His Glu Ala Thr Ala Ala Ala Leu Arg Lys Lys His Ala Asp Ser
1190 1195 1200

5
Val Ala Glu Leu Gly Lys Gln Ile Asp Ser Leu Gln Arg Val Lys
1205 1210 1215

10
Gln Lys Leu Glu Lys Glu Lys Ser Glu Leu Lys Met Glu Ile Asn
1220 1225 1230

15
Asp Leu Ala Ser Asn Met Glu Thr Val Ser Lys Ala Lys Ala Asn
1235 1240 1245

20
Phe Glu Lys Met Cys Arg Thr Leu Glu Asp Gln Leu Ser Glu Ile
1250 1255 1260

25
Lys Thr Lys Glu Glu Glu Gln Gln Arg Leu Ile Asn Glu Leu Ser
1265 1270 1275

30
Ala Gln Lys Ala Arg Leu His Thr Glu Ser Gly Glu Phe Ser Arg
1280 1285 1290

35
Gln Leu Asp Glu Lys Asp Ala Met Val Ser Gln Leu Ser Arg Gly
1295 1300 1305

40
Lys Gln Ala Phe Thr Gln Gln Ile Glu Glu Leu Lys Arg Gln Leu
1310 1315 1320

45
Glu Glu Glu Thr Lys Ala Lys Ser Thr Leu Ala His Ala Leu Gln
1325 1330 1335

50
Ser Ala Arg His Asp Cys Asp Leu Leu Arg Glu Gln Tyr Glu Glu
1340 1345 1350

55
Glu Gln Glu Ala Lys Ala Glu Leu Gln Arg Gly Met Ser Lys Ala
1355 1360 1365

	Asn Ser Glu Val Ala Gln Trp Arg Thr Lys Tyr Glu Thr Asp Ala	
	1370	1375 1380
5	Ile Gln Arg Thr Glu Glu Leu Glu Glu Ala Lys Lys Lys Leu Ala	
	1385	1390 1395
10	Gln Arg Leu Gln Asp Ala Glu Glu His Val Glu Ala Val Asn Ser	
	1400	1405 1410
15	Lys Cys Ala Ser Leu Glu Lys Thr Lys Gln Arg Leu Gln Asn Glu	
	1415	1420 1425
20	Val Glu Asp Leu Met Ile Asp Val Glu Arg Ser Asn Ala Ala Cys	
	1430	1435 1440
	Ile Ala Leu Asp Lys Lys Gln Arg Asn Phe Asp Lys Val Leu Ala	
	1445	1450 1455
25	Glu Trp Lys Gln Lys Tyr Glu Glu Thr Gln Ala Glu Leu Glu Ala	
	1460	1465 1470
30	Ser Gln Lys Glu Ser Arg Ser Leu Ser Thr Glu Leu Phe Lys Val	
	1475	1480 1485
35	Lys Asn Ala Tyr Glu Glu Ser Leu Asp His Leu Glu Thr Leu Lys	
	1490	1495 1500
40	Arg Glu Asn Lys Asn Leu Gln Gln Glu Ile Ser Asp Leu Thr Glu	
	1505	1510 1515
	Gln Ile Ala Glu Gly Gly Lys His Ile His Glu Leu Glu Lys Val	
	1520	1525 1530
45	Lys Lys Gln Leu Asp His Glu Lys Ser Glu Leu Gln Thr Ser Leu	
	1535	1540 1545

Glu Glu Ala Glu Ala Ser Leu Glu His Glu Glu Gly Lys Ile Leu
1550 1555 1560

5 Arg Ile Gln Leu Glu Leu Asn Gln Val Lys Ser Glu Ile Asp Arg
1565 1570 1575

10 Lys Ile Ala Glu Lys Asp Glu Glu Leu Asp Gln Leu Lys Arg Asn
1580 1585 1590

15 His Leu Arg Val Val Glu Ser Met Gln Ser Thr Leu Asp Ala Glu
1595 1600 1605

20 Ile Arg Ser Arg Asn Asp Ala Leu Arg Ile Lys Lys Lys Met Glu
1610 1615 1620

Gly Asp Leu Asn Glu Met Glu Ile Gln Leu Asn His Ala Asn Arg
1625 1630 1635

25 Gln Ala Ala Glu Ala Leu Arg Asn Leu Arg Asn Thr Gln Gly Ile
1640 1645 1650

30 Leu Lys Asp Thr Gln Leu His Leu Asp Asp Ala Ile Arg Gly Gln
1655 1660 1665

35 Asp Asp Leu Lys Glu Gln Leu Ala Met Val Glu Arg Arg Ala Asn
1670 1675 1680

40 Leu Met Gln Ala Glu Val Glu Glu Leu Arg Ala Ser Leu Glu Arg
1685 1690 1695

Thr Glu Arg Gly Arg Lys Met Ala Glu Gln Glu Leu Leu Asp Ala
1700 1705 1710

45 Ser Glu Arg Val Gln Leu Leu His Thr Gln Asn Thr Ser Leu Ile
1715 1720 1725

	Asn Thr	Lys Lys Lys Leu Glu	Thr Asp Ile Ser Gln	Ile Gln Gly
	1730	1735	1740	
5	Glu Met	Glu Asp Ile Val Gln	Glu Ala Arg Asn Ala	Glu Glu Lys
	1745	1750	1755	
10	Ala Lys	Lys Ala Ile Thr Asp	Ala Ala Met Met Ala	Glu Glu Leu
	1760	1765	1770	
15	Lys Lys	Glu Gln Asp Thr Ser	Ala His Leu Glu Arg	Met Lys Lys
	1775	1780	1785	
20	Asn Met	Glu Gln Thr Val Lys	Asp Leu Gln Leu Arg	Leu Gly Glu
	1790	1795	1800	
	Ala Glu	Gln Leu Ala Leu Lys	Gly Gly Lys Lys Gln	Ile Gln Lys
	1805	1810	1815	
25	Leu Glu	Ala Arg Val Arg Glu	Leu Glu Ser Glu Val	Glu Ser Glu
	1820	1825	1830	
30	Gln Lys	His Asn Val Glu Ala	Val Lys Gly Leu Arg	Lys His Glu
	1835	1840	1845	
35	Arg Arg	Val Lys Glu Leu Thr	Tyr Gln Thr Glu Glu	Asp Arg Lys
	1850	1855	1860	
40	Asn Ile	Leu Arg Leu Gln Asp	Leu Val Asp Lys Leu	Gln Thr Lys
	1865	1870	1875	
	Val Lys	Ala Tyr Lys Arg Gln	Ala Glu Glu Ala Glu	Glu Gln Ser
	1880	1885	1890	
45	Asn Val	Asn Leu Ala Lys Phe	Arg Lys Leu Gln His	Glu Leu Glu
	1895	1900	1905	

Glu Ala Glu Glu Arg Ala Asp Ile Ala Glu Ser Gln Val Asn Lys
 1910 1915 1920

5

Leu Arg Val Lys Ser Arg Glu Val His Thr Lys Val Ile Ser Glu
 1925 1930 1935

10 Glu

15 <210> 5
 <211> 5925
 <212> DNA
 <213> Homo sapiens

<400> 5
 20 atgagttctg actctgagat ggccattttt ggggaggctg ctcctttcct ccgaaagtct 60
 gaaagggagc gaattgaagc ccagaacaag ccttttgatg ccaagacatc agtctttgtg 120
 gtggacccta aggagtcctt tgtgaaagca acagtgcaga gcagggaagg ggggaagggtg 180
 25 acagctaaga ccgaagctgg agctactgta acagtgaaag atgaccaagt cttcccatg 240
 aacctccca aatatgacaa gatcgaggac atggccatga tgactcatct acacgagcct 300
 30 gctgtgtgtg acaacctcaa agagcgctac gcagcctgga tgatctacac ctactcaggc 360
 ttgttctgtg tcaactgtcaa cccctacaag tggttgccag tgtataatgc agaagtgggtg 420
 acagcctacc gaggcaaaaa gcgccaggaa gccccacccc acatcttctc catctctgac 480
 35 aatgcctatc agttcatgct gactgatcgg gagaatcagt ctatcttgat caccggagaa 540
 tctggcgcag ggaagactgt gaacaccaag cgtgtcatcc agtactttgc aacaattgca 600
 40 gttactgggg agaagaagaa ggaagaagtt acttctggca aaatgcaggg gactctggaa 660
 gatcaaatca tcagtgccaa cccctactg gaggcctttg gcaacgcaa gaccgtgagg 720
 aatgacaact cctctcgctt tggtaaattc atcaggatcc acttcggtac cacagggaaa 780
 45 ctggcttctg ctgatattga aacatatott ctggagaagt ctagagttao tttccagcta 840
 aaggctgaaa gaagctatca tattttttat cagatcatgt ctaacaagaa gccagatcta 900

attgaaatgc tcctgatcac caccaaccca tacgattatg ccttcgtcag tcaaggggag 960
atcacagtgc ccagcattga tgaccaagaa gagttgatgg ctacagatag tgccattgaa 1020
5 attctgggct ttacttcaga tgaagagtg tccatctata agtcacagg ggcgtgatg 1080
cattatggga acatgaaatt caagcaaaag cagcgtgagg agcaagctga gccagatggc 1140
10 actgaagttg ctgacaaggc agcctatctc caaaatctga actctgcaga tctgctcaaa 1200
gccctctgct accctagggt caaggctggc aatgagtatg tcaccaaagg tcaaactgtg 1260
cagcagggtg acaatgcagt ggtgtctctg gccaaagctg tctacgataa gatgttcttg 1320
15 tggatgggtca cccgcatcaa ccagcagctg gacaccaagc agcccaggca gtacttcatt 1380
ggggtcttgg acattgctgg ctttgagatc tttgatttca acagcctgga gcagctgtgc 1440
20 atcaacttca ccaatgagaa actgcaacag ttttcaacc accacatgtt cgtgctggag 1500
caggaggagt acaagaagga aggcattgag tggacgttca ttgactttgg gatggacctg 1560
gctgcctgca tcgagctcat cgagaagcct atgggcatct tctccatcct ggaagaggag 1620
25 tgcatgttcc ccaaggcgac agacacctcc ttcaagaaca agctglatga acaacatctt 1680
ggaaaatcca ataacttcca gaagccaag cctgccaaag gcaagcctga ggcccacttc 1740
30 tctttgattc actatgctgg caccgtggac tacaacattg ccggctggct tgacaagaac 1800
aaggaccccc tgaatgagac tgtgtggggg ctgtaccaga agtctgcaat gaagactctg 1860
gctctcctct ttgttggggc aacgggagcg gaagcagagg ctggcgggtg aaagaaaggt 1920
35 ggtaagaaga aggtttcttc tttccagact gtgtcggctc tcttcaggga gaatttgaat 1980
aagctgatga ccaacttgag gagcactcac cccactttg tgcggtgcat catccccaat 2040
40 gaaactaaaa ctctggtgc catggagcat gagcttgtcc tgcatcagct gaggtgtaac 2100
ggtgtgctgg aaggcatccg catctgcagg aaaggcttcc caagcagaat cttttatgca 2160
gacttcaaac agagatacaa ggtgttaaata gcaagtgtc tccctgaagg acaattcatc 2220
45 gatagcaaga aggcttcaga gaagctcctg ggttcattg acattgacca caccagtat 2280
aaatttggtc acaccaaggt ctttttcaaa gctgggtcttc tggggctcct agaggagatg 2340

cgagatgaga agctggccca gctgattacc cgaaccagg ccatgtgcag agggttcttg 2400
gcaagagtgg agtaccagaa aatggtgaa agaagagagt ccatcttctg catccagtac 2460
5 aatgtccgtg ccttcatgaa tgtcaagcac tggccctgga tgaagctgta tttcaagatc 2520
aaacccctcc tcaaaagtgc agagacagag aaggagatgg ccaacatgaa ggaagaattt 2580
10 gagaaaacca aagaagagct ggctaagacc gaggcacaaa ggaaagagct ggaagaaaaa 2640
atggtgactc tgatgcaaga aaaaaatgac ttgcaactcc aggttcaagc tgaagctgac 2700
agcttggtg atgcagagga aagggtgac cagctaata aaaccaaata ccagctagaa 2760
15 gccaaaatca aagaggtgac tgagagagct gaggatgagg aagagatcaa tgctgagctg 2820
acagccaaga agaggaaact ggaggatgaa tggtcagaac tcaagaaaga cattgatgac 2880
20 cttgagctga cactggccaa ggttgagaag gagaaacatg ccacagaaaa caaggtgaaa 2940
aacctcacag aagagatggc ggttctggat gaaaccattg ctaagctgac caaggagaag 3000
aaggctctcc aggaggccca ccagcagacc ctggatgacc tgcaggcaga ggaggacaaa 3060
25 gtcaacaccc tgaccaaagc taaaatcaaa cttgaacaac aagtggatga tcttgaagga 3120
tctttggaac aagaaaagaa aatccggatg gatctagaaa gagcaaagag aaaactagag 3180
30 ggagacctaa aattggctca agaatccgca atggatatag aaaatgacaa acaacaactt 3240
gatgaaaagc ttaaaaagaa agagttttaa atgagcggtc tgcaaagcaa gattgaagat 3300
gaacaagccc ttggtatgca gctgcagaag aaaatcaagg agttacaagc ccgcattgag 3360
35 gagctggagg aggaaatcga ggcagagcgg gcctccggg ccaaagcaga gaagcagcgc 3420
tctgatctct cccgggagct ggaggagatc agtgagagc tggaagaagc cgggtggggcc 3480
40 acctcggccc agattgagat gaacaagaag cgggaagctg agttccagaa aatgcgcagg 3540
gacctggagg aggccacct acagcatgag gccacggcgg ccacctgag gaagaagcat 3600
gcagatagtg tggccgagct tggggagcag attgacaacc tgcagcgagt gaagcagaag 3660
45 ctggagaagg agaagagtga gatgaagatg gagatcgatg accttgctag taacatggag 3720
actgtctcca aagccaaggg aaaccttgaa aagatgtgcc gcgctctaga agatcaactg 3780

agtgaaatta agaccaagga agaggagcag cagcggctga tcaatgacct cacagcacag 3840
agagcgcgcc tgcaaacaga atcaggtgaa tattcacgcc agctagatga aaaggacaca 3900
5 ctagtttcac agctctcgag gggcaaacia gcctttactc aacagattga ggaactgaaa 3960
aggcaacttg aagaggagat aaaggccaag agtgccttg ccatgacct gcagtcctcc 4020
10 cgccatgact gtgacctgct gcgggaacag tatgaggagg agcaggaagc caaggccgag 4080
ctacagagag caatgtccaa ggccaacagt gaggttgccc agtggaggac caaatatgag 4140
acagatgcca tccagcgcac agaggagctg gaggaggcca agaagaagct ggctcagcgt 4200
15 ctgcaggatg ctgaggaaca tgtagaagct gtgaatgcca aatgtgcttc ccttgagaag 4260
acgaagcaga ggctccagaa tgaattgag gacctatga ttgatgtga gaggacaaat 4320
20 gctgcctgtg ccgccctgga caaaaagcaa aggaactttg ataagacct ggcaaatgg 4380
aaacagaagt gtgaagaaac tcatgtgaa cttgaagctt ctcaaaagga atcccgctca 4440
ctcagcacag aactatttaa gattaagaat gottatgagg aatctttaga ccaacttgaa 4500
25 accttgaaac gggaaaataa gaatctgcag caggagattt ctgatctcac tgaacagatt 4560
gcagaaggag gaaagcgcat ccatgaactg gaaaaataa agaagcaagt tgagcaagaa 4620
30 aagtctgaac ttcaggctgc cttagaggag gcagaggcat ctcttgaaca tgaagaggga 4680
aagatcctgc gcatccagct tgagttgaac caagtcaagt ctgaggtga taggaaaatt 4740
gtgaaaaag atgaggaaat tgaccagatg aagagaaacc acattagaat cgtggagtcc 4800
35 atgcagagca cactggatgc tgagatcagg agcaggaatg atgccattag gctcaagaag 4860
aagatggagg gagacctcaa tgaaatggaa atccagctga accatgcaa ccgcatggct 4920
40 gctgaggccc tgaggaacta taggaacacc caagccatcc tcaaggatac ccagctccac 4980
ctagatgatg ctctccggag ccaagaggac ctgaaggaa agctggctat ggtggagcgc 5040
agagccaacc tgctgcaggc tgagatcgag gaactacgag ccactctgga acagacggag 5100
45 aggagcagga aaatcgaga acaggagctc ctggatgcca gtgaacgtgt tcagctcctg 5160
cacaccaga acaccagcct gatcaacacc aagaagaagc tggagacaga catttccaa 5220

atccagggag agatggaaga catcatocag gaagcccgca atgcagaaga gaaggccaag 5280
 aaggccatca ctgatgctgc catgatggct gaggagctga agaaggaaca ggacaccagc 5340
 5 gcccatctgg agcggatgaa gaagaacttg gaacagacgg tgaaggacct gcagcatcgt 5400
 ctggatgagg ctgagcagct ggccctgaag ggtgggaaga agcagatcca gaaactggag 5460
 10 gccagggttc gtgaacttga aggtgaagtt gaaagtgaac agaagcgcaa tgttgaagct 5520
 gtcaagggtc tacgcaaaca tgagagaaaa gtgaaggaac tcacttacca aactgaggaa 5580
 gaccgcaaga atattctcag gctgcaggac ctggtggaca agctgcaagc aaaggtgaaa 5640
 15 tcctacaaga gacaagctga agaagcggag gaacaatcca acgtcaacct ctccaaattc 5700
 cggaggatcc agcacgagct ggaggaggcc gaggaaaggg ctgacattgc tgagtccag 5760
 20 gtcaacaagc tgagggtgaa gagcaggag gttcacacaa aaatcataag tgaagagtaa 5820
 tttatctaac tgctgaaagg tgaccaaaga aatgcacaaa atgtgaaaat ctttgtcact 5880
 ccattttgta cttatgaatt ttggagataa aaaatttato tgcca 5925
 25

<210> 6

<211> 1939

<212> PRT

30 <213> Homo sapiens

<400> 6

Met Ser Ser Asp Ser Glu Met Ala Ile Phe Gly Glu Ala Ala Pro Phe
 35 1 5 10 15

Leu Arg Lys Ser Glu Arg Glu Arg Ile Glu Ala Gln Asn Lys Pro Phe
 20 25 30

40

Asp Ala Lys Thr Ser Val Phe Val Val Asp Pro Lys Glu Ser Phe Val
 35 40 45

45

Lys Ala Thr Val Gln Ser Arg Glu Gly Gly Lys Val Thr Ala Lys Thr
 50 55 60

Glu Ala Gly Ala Thr Val Thr Val Lys Asp Asp Gln Val Phe Pro Met
 65 70 75 80

5
 Asn Pro Pro Lys Tyr Asp Lys Ile Glu Asp Met Ala Met Met Thr His
 85 90 95

10
 Leu His Glu Pro Ala Val Leu Tyr Asn Leu Lys Glu Arg Tyr Ala Ala
 100 105 110

15
 Trp Met Ile Tyr Thr Tyr Ser Gly Leu Phe Cys Val Thr Val Asn Pro
 115 120 125

Tyr Lys Trp Leu Pro Val Tyr Asn Ala Glu Val Val Thr Ala Tyr Arg
 130 135 140

20
 Gly Lys Lys Arg Gln Glu Ala Pro Pro His Ile Phe Ser Ile Ser Asp
 145 150 155 160

25
 Asn Ala Tyr Gln Phe Met Leu Thr Asp Arg Glu Asn Gln Ser Ile Leu
 165 170 175

30
 Ile Thr Gly Glu Ser Gly Ala Gly Lys Thr Val Asn Thr Lys Arg Val
 180 185 190

35
 Ile Gln Tyr Phe Ala Thr Ile Ala Val Thr Gly Glu Lys Lys Lys Glu
 195 200 205

Glu Val Thr Ser Gly Lys Met Gln Gly Thr Leu Glu Asp Gln Ile Ile
 210 215 220

40
 Ser Ala Asn Pro Leu Leu Glu Ala Phe Gly Asn Ala Lys Thr Val Arg
 225 230 235 240

45
 Asn Asp Asn Ser Ser Arg Phe Gly Lys Phe Ile Arg Ile His Phe Gly
 245 250 255

Thr Thr Gly Lys Leu Ala Ser Ala Asp Ile Glu Thr Tyr Leu Leu Glu
260 265 270

5
Lys Ser Arg Val Thr Phe Gln Leu Lys Ala Glu Arg Ser Tyr His Ile
275 280 285

10
Phe Tyr Gln Ile Met Ser Asn Lys Lys Pro Asp Leu Ile Glu Met Leu
290 295 300

15
Leu Ile Thr Thr Asn Pro Tyr Asp Tyr Ala Phe Val Ser Gln Gly Glu
305 310 315 320

20
Ile Thr Val Pro Ser Ile Asp Asp Gln Glu Glu Leu Met Ala Thr Asp
325 330 335

25
Ser Ala Ile Glu Ile Leu Gly Phe Thr Ser Asp Glu Arg Val Ser Ile
340 345 350

30
Tyr Lys Leu Thr Gly Ala Val Met His Tyr Gly Asn Met Lys Phe Lys
355 360 365

35
Gln Lys Gln Arg Glu Glu Gln Ala Glu Pro Asp Gly Thr Glu Val Ala
370 375 380

40
Asp Lys Ala Ala Tyr Leu Gln Asn Leu Asn Ser Ala Asp Leu Leu Lys
385 390 395 400

45
Ala Leu Cys Tyr Pro Arg Val Lys Val Gly Asn Glu Tyr Val Thr Lys
405 410 415

50
Gly Gln Thr Val Gln Gln Val Tyr Asn Ala Val Gly Ala Leu Ala Lys
420 425 430

55
Ala Val Tyr Asp Lys Met Phe Leu Trp Met Val Thr Arg Ile Asn Gln
435 440 445

Gln Leu Asp Thr Lys Gln Pro Arg Gln Tyr Phe Ile Gly Val Leu Asp
450 455 460

5
Ile Ala Gly Phe Glu Ile Phe Asp Phe Asn Ser Leu Glu Gln Leu Cys
465 470 475 480

10
Ile Asn Phe Thr Asn Glu Lys Leu Gln Gln Phe Phe Asn His His Met
485 490 495

15
Phe Val Leu Glu Gln Glu Tyr Lys Lys Glu Gly Ile Glu Trp Thr
500 505 510

Phe Ile Asp Phe Gly Met Asp Leu Ala Ala Cys Ile Glu Leu Ile Glu
515 520 525

20

Lys Pro Met Gly Ile Phe Ser Ile Leu Glu Glu Glu Cys Met Phe Pro
530 535 540

25
Lys Ala Thr Asp Thr Ser Phe Lys Asn Lys Leu Tyr Glu Gln His Leu
545 550 555 560

30
Gly Lys Ser Asn Asn Phe Gln Lys Pro Lys Pro Ala Lys Gly Lys Pro
565 570 575

Glu Ala His Phe Ser Leu Ile His Tyr Ala Gly Thr Val Asp Tyr Asn
580 585 590

35

Ile Ala Gly Trp Leu Asp Lys Asn Lys Asp Pro Leu Asn Glu Thr Val
595 600 605

40

Val Gly Leu Tyr Gln Lys Ser Ala Met Lys Thr Leu Ala Leu Leu Phe
610 615 620

45
Val Gly Ala Thr Gly Ala Glu Ala Glu Ala Gly Gly Gly Lys Lys Gly
625 630 635 640

Gly Lys Lys Lys Gly Ser Ser Phe Gln Thr Val Ser Ala Leu Phe Arg
645 650 655

5
Glu Asn Leu Asn Lys Leu Met Thr Asn Leu Arg Ser Thr His Pro His
660 665 670

10
Phe Val Arg Cys Ile Ile Pro Asn Glu Thr Lys Thr Pro Gly Ala Met
675 680 685

15
Glu His Glu Leu Val Leu His Gln Leu Arg Cys Asn Gly Val Leu Glu
690 695 700

20
Gly Ile Arg Ile Cys Arg Lys Gly Phe Pro Ser Arg Ile Leu Tyr Ala
705 710 715 720

25
Asp Phe Lys Gln Arg Tyr Lys Val Leu Asn Ala Ser Ala Ile Pro Glu
725 730 735

30
Ile Asp Ile Asp His Thr Gln Tyr Lys Phe Gly His Thr Lys Val Phe
755 760 765

35
Phe Lys Ala Gly Leu Leu Gly Leu Leu Glu Glu Met Arg Asp Glu Lys
770 775 780

40
Leu Ala Gln Leu Ile Thr Arg Thr Gln Ala Met Cys Arg Gly Phe Leu
785 790 795 800

45
Ala Arg Val Glu Tyr Gln Lys Met Val Glu Arg Arg Glu Ser Ile Phe
805 810 815

Cys Ile Gln Tyr Asn Val Arg Ala Phe Met Asn Val Lys His Trp Pro
820 825 830

Trp Met Lys Leu Tyr Phe Lys Ile Lys Pro Leu Leu Lys Ser Ala Glu
835 840 845

5 Thr Glu Lys Glu Met Ala Asn Met Lys Glu Glu Phe Glu Lys Thr Lys
850 855 860

10 Glu Glu Leu Ala Lys Thr Glu Ala Lys Arg Lys Glu Leu Glu Glu Lys
865 870 875 880

15 Met Val Thr Leu Met Gln Glu Lys Asn Asp Leu Gln Leu Gln Val Gln
885 890 895

20 Ala Glu Ala Asp Ser Leu Ala Asp Ala Glu Glu Arg Cys Asp Gln Leu
900 905 910

Ile Lys Thr Lys Ile Gln Leu Glu Ala Lys Ile Lys Glu Val Thr Glu
915 920 925

25 Arg Ala Glu Asp Glu Glu Glu Ile Asn Ala Glu Leu Thr Ala Lys Lys
930 935 940

30 Arg Lys Leu Glu Asp Glu Cys Ser Glu Leu Lys Lys Asp Ile Asp Asp
945 950 955 960

35 Leu Glu Leu Thr Leu Ala Lys Val Glu Lys Glu Lys His Ala Thr Glu
965 970 975

40 Asn Lys Val Lys Asn Leu Thr Glu Glu Met Ala Gly Leu Asp Glu Thr
980 985 990

Ile Ala Lys Leu Thr Lys Glu Lys Lys Ala Leu Gln Glu Ala His Gln
995 1000 1005

45 Gln Thr Leu Asp Asp Leu Gln Ala Glu Glu Asp Lys Val Asn Thr
1010 1015 1020

	Leu Thr	Lys Ala Lys Ile Lys	Leu Glu Gln Gln Val	Asp Asp Leu
	1025	1030	1035	
5	Glu Gly	Ser Leu Glu Gln Glu	Lys Lys Ile Arg Met	Asp Leu Glu
	1040	1045	1050	
10	Arg Ala	Lys Arg Lys Leu Glu	Gly Asp Leu Lys Leu	Ala Gln Glu
	1055	1060	1065	
15	Ser Ala	Met Asp Ile Glu Asn	Asp Lys Gln Gln Leu	Asp Glu Lys
	1070	1075	1080	
20	Leu Lys	Lys Lys Glu Phe Glu	Met Ser Gly Leu Gln	Ser Lys Ile
	1085	1090	1095	
25	Glu Asp	Glu Gln Ala Leu Gly	Met Gln Leu Gln Lys	Lys Ile Lys
	1100	1105	1110	
30	Glu Leu	Gln Ala Arg Ile Glu	Glu Leu Glu Glu Glu	Ile Glu Ala
	1115	1120	1125	
35	Glu Arg	Ala Ser Arg Ala Lys	Ala Glu Lys Gln Arg	Ser Asp Leu
	1130	1135	1140	
40	Ser Arg	Glu Leu Glu Glu Ile	Ser Glu Arg Leu Glu	Glu Ala Gly
	1145	1150	1155	
45	Gly Ala	Thr Ser Ala Gln Ile	Glu Met Asn Lys Lys	Arg Glu Ala
	1160	1165	1170	
50	Glu Phe	Gln Lys Met Arg Arg	Asp Leu Glu Glu Ala	Thr Leu Gln
	1175	1180	1185	
55	His Glu	Ala Thr Ala Ala Thr	Leu Arg Lys Lys His	Ala Asp Ser
	1190	1195	1200	

Val Ala Glu Leu Gly Glu Gln Ile Asp Asn Leu Gln Arg Val Lys
1205 1210 1215

5
Gln Lys Leu Glu Lys Glu Lys Ser Glu Met Lys Met Glu Ile Asp
1220 1225 1230

10
Asp Leu Ala Ser Asn Met Glu Thr Val Ser Lys Ala Lys Gly Asn
1235 1240 1245

15
Leu Glu Lys Met Cys Arg Ala Leu Glu Asp Gln Leu Ser Glu Ile
1250 1255 1260

20
Lys Thr Lys Glu Glu Glu Gln Gln Arg Leu Ile Asn Asp Leu Thr
1265 1270 1275

25
Ala Gln Arg Ala Arg Leu Gln Thr Glu Ser Gly Glu Tyr Ser Arg
1280 1285 1290

30
Gln Leu Asp Glu Lys Asp Thr Leu Val Ser Gln Leu Ser Arg Gly
1295 1300 1305

35
Lys Gln Ala Phe Thr Gln Gln Ile Glu Glu Leu Lys Arg Gln Leu
1310 1315 1320

40
Glu Glu Glu Ile Lys Ala Lys Ser Ala Leu Ala His Ala Leu Gln
1325 1330 1335

45
Ser Ser Arg His Asp Cys Asp Leu Leu Arg Glu Gln Tyr Glu Glu
1340 1345 1350

50
Glu Gln Glu Ala Lys Ala Glu Leu Gln Arg Ala Met Ser Lys Ala
1355 1360 1365

55
Asn Ser Glu Val Ala Gln Trp Arg Thr Lys Tyr Glu Thr Asp Ala
1370 1375 1380

Ile Gln Arg Thr Glu Glu Leu Glu Glu Ala Lys Lys Lys Leu Ala
1385 1390 1395

5
Gln Arg Leu Gln Asp Ala Glu Glu His Val Glu Ala Val Asn Ala
1400 1405 1410

10
Lys Cys Ala Ser Leu Glu Lys Thr Lys Gln Arg Leu Gln Asn Glu
1415 1420 1425

15
Val Glu Asp Leu Met Ile Asp Val Glu Arg Thr Asn Ala Ala Cys
1430 1435 1440

20
Ala Ala Leu Asp Lys Lys Gln Arg Asn Phe Asp Lys Ile Leu Ala
1445 1450 1455

25
Glu Trp Lys Gln Lys Cys Glu Glu Thr His Ala Glu Leu Glu Ala
1460 1465 1470

30
Ser Gln Lys Glu Ser Arg Ser Leu Ser Thr Glu Leu Phe Lys Ile
1475 1480 1485

35
Lys Asn Ala Tyr Glu Glu Ser Leu Asp Gln Leu Glu Thr Leu Lys
1490 1495 1500

40
Arg Glu Asn Lys Asn Leu Gln Gln Glu Ile Ser Asp Leu Thr Glu
1505 1510 1515

45
Gln Ile Ala Glu Gly Gly Lys Arg Ile His Glu Leu Glu Lys Ile
1520 1525 1530

Lys Lys Gln Val Glu Gln Glu Lys Ser Glu Leu Gln Ala Ala Leu
1535 1540 1545

50
Glu Glu Ala Glu Ala Ser Leu Glu His Glu Glu Gly Lys Ile Leu
1550 1555 1560

Arg Ile Gln Leu Glu Leu Asn Gln Val Lys Ser Glu Val Asp Arg
1565 1570 1575

5
Lys Ile Ala Glu Lys Asp Glu Glu Ile Asp Gln Met Lys Arg Asn
1580 1585 1590

10
His Ile Arg Ile Val Glu Ser Met Gln Ser Thr Leu Asp Ala Glu
1595 1600 1605

15
Ile Arg Ser Arg Asn Asp Ala Ile Arg Leu Lys Lys Lys Met Glu
1610 1615 1620

20
Gly Asp Leu Asn Glu Met Glu Ile Gln Leu Asn His Ala Asn Arg
1625 1630 1635

25
Met Ala Ala Glu Ala Leu Arg Asn Tyr Arg Asn Thr Gln Ala Ile
1640 1645 1650

30
Leu Lys Asp Thr Gln Leu His Leu Asp Asp Ala Leu Arg Ser Gln
1655 1660 1665

35
Glu Asp Leu Lys Glu Gln Leu Ala Met Val Glu Arg Arg Ala Asn
1670 1675 1680

40
Leu Leu Gln Ala Glu Ile Glu Glu Leu Arg Ala Thr Leu Glu Gln
1685 1690 1695

45
Thr Glu Arg Ser Arg Lys Ile Ala Glu Gln Glu Leu Leu Asp Ala
1700 1705 1710

Ser Glu Arg Val Gln Leu Leu His Thr Gln Asn Thr Ser Leu Ile
1715 1720 1725

50
Asn Thr Lys Lys Lys Leu Glu Thr Asp Ile Ser Gln Ile Gln Gly
1730 1735 1740

	Glu Met	Glu Asp	Ile Ile	Gln	Glu Ala	Arg Asn	Ala	Glu Glu	Lys
	1745			1750				1755	
5	Ala Lys	Lys Ala	Ile Thr	Asp	Ala Ala	Met Met	Ala	Glu Glu	Leu
	1760			1765				1770	
10	Lys Lys	Glu Gln	Asp Thr	Ser	Ala His	Leu Glu	Arg	Met Lys	Lys
	1775			1780				1785	
15	Asn Leu	Glu Gln	Thr Val	Lys	Asp Leu	Gln His	Arg	Leu Asp	Glu
	1790			1795				1800	
20	Ala Glu	Gln Leu	Ala Leu	Lys	Gly Gly	Lys Lys	Gln	Ile Gln	Lys
	1805			1810				1815	
	Leu Glu	Ala Arg	Val Arg	Glu	Leu Glu	Gly Glu	Val	Glu Ser	Glu
	1820			1825				1830	
25	Gln Lys	Arg Asn	Val Glu	Ala	Val Lys	Gly Leu	Arg	Lys His	Glu
	1835			1840				1845	
30	Arg Lys	Val Lys	Glu Leu	Thr	Tyr Gln	Thr Glu	Glu	Asp Arg	Lys
	1850			1855				1860	
35	Asn Ile	Leu Arg	Leu Gln	Asp	Leu Val	Asp Lys	Leu	Gln Ala	Lys
	1865			1870				1875	
40	Val Lys	Ser Tyr	Lys Arg	Gln	Ala Glu	Glu Ala	Glu	Glu Gln	Ser
	1880			1885				1890	
	Asn Val	Asn Leu	Ser Lys	Phe	Arg Arg	Ile Gln	His	Glu Leu	Glu
	1895			1900				1905	
45	Glu Ala	Glu Glu	Arg Ala	Asp	Ile Ala	Glu Ser	Gln	Val Asn	Lys
	1910			1915				1920	

Leu Arg Val Lys Ser Arg Glu Val His Thr Lys Ile Ile Ser Glu
 1925 1930 1935

5

Glu

10

<210> 7
 <211> 2633
 <212> DNA
 <213> Homo sapiens

15

<220>
 <221> CDS
 <222> (38).. (2584)
 <223>

20

<400> 7
 ccgcggaag aacatccctc ccagccagca gattaca atg ctg caa act aag gat 55
 Met Leu Gln Thr Lys Asp
 1 5

25

ctc atc tgg act ttg ttt ttc ctg gga act gca gtt tct ctg cag gtg 103
 Leu Ile Trp Thr Leu Phe Phe Leu Gly Thr Ala Val Ser Leu Gln Val
 10 15 20

30

gat att gtt ccc agc cag ggg gag atc agc gtt gga gag tcc aaa ttc 151
 Asp Ile Val Pro Ser Gln Gly Glu Ile Ser Val Gly Glu Ser Lys Phe
 25 30 35

35

ttc tta tgc caa gtg gca gga gat gcc aaa gat aaa gac atc tcc tgg 199
 Phe Leu Cys Gln Val Ala Gly Asp Ala Lys Asp Lys Asp Ile Ser Trp
 40 45 50

40

ttc tcc ccc aat gga gaa aag ctc acc cca aac cag cag cgg atc tca 247
 Phe Ser Pro Asn Gly Glu Lys Leu Thr Pro Asn Gln Gln Arg Ile Ser
 55 60 65 70

gtg gtg tgg aat gat gat tcc tcc tcc acc ctc acc atc tat aac gcc 295
 Val Val Trp Asn Asp Asp Ser Ser Ser Thr Leu Thr Ile Tyr Asn Ala
 75 80 85

45

aac atc gac gac gcc ggc att tac aag tgt gtg gtt aca ggc gag gat 343
 Asn Ile Asp Asp Ala Gly Ile Tyr Lys Cys Val Val Thr Gly Glu Asp
 90 95 100

	ggc agt gag tca gag gcc acc gtc aac gtg aag atc ttt cag aag ctc Gly Ser Glu Ser Glu Ala Thr Val Asn Val Lys Ile Phe Gln Lys Leu 105 110 115	391
5	atg ttc aag aat gcg cca acc cca cag gag ttc cgg gag ggg gaa gat Met Phe Lys Asn Ala Pro Thr Pro Gln Glu Phe Arg Glu Gly Glu Asp 120 125 130	439
10	gcc gtg att gtg tgt gat gtg gtc agc tcc ctc cca cca acc atc atc Ala Val Ile Val Cys Asp Val Val Ser Ser Leu Pro Pro Thr Ile Ile 135 140 145 150	487
15	tgg aaa cac aaa ggc cga gat gtc atc ctg aaa aaa gat gtc cga ttc Trp Lys His Lys Gly Arg Asp Val Ile Leu Lys Lys Asp Val Arg Phe 155 160 165	535
20	ata gtc ctg tcc aac aac tac ctg cag atc cgg ggc atc aag aaa aca Ile Val Leu Ser Asn Asn Tyr Leu Gln Ile Arg Gly Ile Lys Lys Thr 170 175 180	583
	gat gag ggc act tat cgc tgt gag ggc aga atc ctg gca cgg ggg gag Asp Glu Gly Thr Tyr Arg Cys Glu Gly Arg Ile Leu Ala Arg Gly Glu 185 190 195	631
25	atc aac ttc aag gac att cag gtc att gtg aat gtg cca cct acc atc Ile Asn Phe Lys Asp Ile Gln Val Ile Val Asn Val Pro Pro Thr Ile 200 205 210	679
30	cgg gcc agg cag aat att gtg aat gcc acc gcc aac ctc ggc cag tcc Arg Ala Arg Gln Asn Ile Val Asn Ala Thr Ala Asn Leu Gly Gln Ser 215 220 225 230	727
35	gtc acc ctg gtg tgc gat gcc gaa cgg ttc cca gag ccc acc atg agc Val Thr Leu Val Cys Asp Ala Glu Arg Phe Pro Glu Pro Thr Met Ser 235 240 245	775
40	tgg aca aag gat ggg gaa cag ata gag caa gag gaa gac gat gag aag Trp Thr Lys Asp Gly Glu Gln Ile Glu Gln Glu Glu Asp Asp Glu Lys 250 255 260	823
	tac atc ttc agc gac gat agt tcc cag ctg acc atc aaa aag gtg gat Tyr Ile Phe Ser Asp Asp Ser Ser Gln Leu Thr Ile Lys Lys Val Asp 265 270 275	871
45	aag aac gac gag gct gag tac atc tgc att gct gag aac aag gct ggc Lys Asn Asp Glu Ala Glu Tyr Ile Cys Ile Ala Glu Asn Lys Ala Gly 280 285 290	919

	gag cag gat gcg acc atc cac ctc aaa gtc ttt gca aaa ccc aaa atc	967
	Glu Gln Asp Ala Thr Ile His Leu Lys Val Phe Ala Lys Pro Lys Ile	
	295 300 305 310	
5	aca tat gta gag aac cag act gcc atg gaa tta gag gag cag gtc act	1015
	Thr Tyr Val Glu Asn Gln Thr Ala Met Glu Leu Glu Glu Gln Val Thr	
	315 320 325	
10	ctt acc tgt gaa gcc tcc gga gac ccc att ccc tcc atc acc tgg agg	1063
	Leu Thr Cys Glu Ala Ser Gly Asp Pro Ile Pro Ser Ile Thr Trp Arg	
	330 335 340	
15	act tct acc cgg aac atc agc agc gaa gaa aag act ctg gat ggg cac	1111
	Thr Ser Thr Arg Asn Ile Ser Ser Glu Glu Lys Thr Leu Asp Gly His	
	345 350 355	
20	atg gtg gtg cgt agc cat gcc cgt gtg tcg tcg ctg acc ctg aag agc	1159
	Met Val Val Arg Ser His Ala Arg Val Ser Ser Leu Thr Leu Lys Ser	
	360 365 370	
25	atc cag tac act gat gcc gga gag tac atc tgc acc gcc agc aac acc	1207
	Ile Gln Tyr Thr Asp Ala Gly Glu Tyr Ile Cys Thr Ala Ser Asn Thr	
	375 380 385 390	
30	atc ggc cag gac tcc cag tcc atg tac ctt gaa gtg caa tat gcc cca	1255
	Ile Gly Gln Asp Ser Gln Ser Met Tyr Leu Glu Val Gln Tyr Ala Pro	
	395 400 405	
35	aag cta cag ggc cct gtg gct gtg tac act tgg gag ggg aac cag gtg	1303
	Lys Leu Gln Gly Pro Val Ala Val Tyr Thr Trp Glu Gly Asn Gln Val	
	410 415 420	
40	aac atc acc tgc gag gta ttt gcc tat ccc agt gcc acg atc tca tgg	1351
	Asn Ile Thr Cys Glu Val Phe Ala Tyr Pro Ser Ala Thr Ile Ser Trp	
	425 430 435	
45	ttt cgg gat ggc cag ctg ctg cca agc tcc aat tac agc aat atc aag	1399
	Phe Arg Asp Gly Gln Leu Leu Pro Ser Ser Asn Tyr Ser Asn Ile Lys	
	440 445 450	
50	atc tac aac acc ccc tct gcc agc tat ctg gag gtg acc cca gac tct	1447
	Ile Tyr Asn Thr Pro Ser Ala Ser Tyr Leu Glu Val Thr Pro Asp Ser	
	455 460 465 470	
55	gag aat gat ttt ggg aac tac aac tgt act gca gtg aac cgc att ggg	1495
	Glu Asn Asp Phe Gly Asn Tyr Asn Cys Thr Ala Val Asn Arg Ile Gly	
	475 480 485	

	cag gag tcc ttc gaa ttc atc ctt gtt caa gca gac acc ccc tct tca	1543
	Gln Glu Ser Phe Glu Phe Ile Leu Val Gln Ala Asp Thr Pro Ser Ser	
	490 495 500	
5	cca tcc atc gac cag gtg gag cca tac tcc agc aca gcc cag gtg cag	1591
	Pro Ser Ile Asp Gln Val Glu Pro Tyr Ser Ser Thr Ala Gln Val Gln	
	505 510 515	
10	ttt gat gaa cca gag gcc aca ggt ggg gtg ccc atc ctc aaa tac aaa	1639
	Phe Asp Glu Pro Glu Ala Thr Gly Gly Val Pro Ile Leu Lys Tyr Lys	
	520 525 530	
15	gct gag tgg aga gca gtg ggt gaa gaa gta tgg cat tcc aag tgg tat	1687
	Ala Glu Trp Arg Ala Val Gly Glu Glu Val Trp His Ser Lys Trp Tyr	
	535 540 545 550	
20	gat gcc aag gaa gcc agc atg gag ggc atc gtc acc atc gtg ggc ctg	1735
	Asp Ala Lys Glu Ala Ser Met Glu Gly Ile Val Thr Ile Val Gly Leu	
	555 560 565	
	aag ccc gaa aca acg tac gcc gta agg ctg gcg gcg ctc aat ggc aaa	1783
	Lys Pro Glu Thr Thr Tyr Ala Val Arg Leu Ala Ala Leu Asn Gly Lys	
	570 575 580	
25	ggg ctg ggt gag atc agc gcg gcc tcc gag ttc aag acg cag cca gtc	1831
	Gly Leu Gly Glu Ile Ser Ala Ala Ser Glu Phe Lys Thr Gln Pro Val	
	585 590 595	
30	caa ggg gaa ccc agt gca cct aag ctc gaa ggg cag atg gga gag gat	1879
	Gln Gly Glu Pro Ser Ala Pro Lys Leu Glu Gly Gln Met Gly Glu Asp	
	600 605 610	
35	gga aac tct att aaa gtg aac ctg atc aag cag gat gac ggc ggc tcc	1927
	Gly Asn Ser Ile Lys Val Asn Leu Ile Lys Gln Asp Asp Gly Gly Ser	
	615 620 625 630	
40	ccc atc aga cac tat ctg gtc agg tac cga gcg ctc tcc tcc gag tgg	1975
	Pro Ile Arg His Tyr Leu Val Arg Tyr Arg Ala Leu Ser Ser Glu Trp	
	635 640 645	
	aaa cca gag atc agg ctc ccg tct ggc agt gac cac gtc atg ctg aag	2023
	Lys Pro Glu Ile Arg Leu Pro Ser Gly Ser Asp His Val Met Leu Lys	
	650 655 660	
45	tcc ctg gac tgg aat gct gag tat gag gtc tac gtg gtg gct gag aac	2071
	Ser Leu Asp Trp Asn Ala Glu Tyr Glu Val Tyr Val Val Ala Glu Asn	
	665 670 675	

	cag caa gga aaa tcc aag gcg gct cat ttt gtg ttc agg acc tcg gcc Gln Gln Gly Lys Ser Lys Ala Ala His Phe Val Phe Arg Thr Ser Ala 680 685 690	2119
5	cag ccc aca gcc atc cca gcc aac ggc agc ccc acc tca ggc ctg agc Gln Pro Thr Ala Ile Pro Ala Asn Gly Ser Pro Thr Ser Gly Leu Ser 695 700 705 710	2167
10	acc ggg gcc atc gtg ggc atc ctc atc gtc atc ttc gtc ctg ctc ctg Thr Gly Ala Ile Val Gly Ile Leu Ile Val Ile Phe Val Leu Leu Leu 715 720 725	2215
15	gtg gtt gtg gac atc acc tgc tac ttc ctg aac aag tgt ggc ctg ttc Val Val Val Asp Ile Thr Cys Tyr Phe Leu Asn Lys Cys Gly Leu Phe 730 735 740	2263
20	atg tgc att gcg gtc aac ctg tgt gga aaa gcc ggg ccc ggg gcc aag Met Cys Ile Ala Val Asn Leu Cys Gly Lys Ala Gly Pro Gly Ala Lys 745 750 755	2311
	ggc aag gac atg gag gag ggc aag gcc gcc ttc tcg aaa gat gag tcc Gly Lys Asp Met Glu Glu Gly Lys Ala Ala Phe Ser Lys Asp Glu Ser 760 765 770	2359
25	aag gag ccc atc gtg gag gtt cga acg gag gag gag agg acc cca aac Lys Glu Pro Ile Val Glu Val Arg Thr Glu Glu Glu Arg Thr Pro Asn 775 780 785 790	2407
30	cat gat gga ggg aaa cac aca gag ccc aac gag acc acg cca ctg acg His Asp Gly Gly Lys His Thr Glu Pro Asn Glu Thr Thr Pro Leu Thr 795 800 805	2455
35	gag ccc gag aag ggc ccc gta gaa gca aag cca gag tgc cag gag aca Glu Pro Glu Lys Gly Pro Val Glu Ala Lys Pro Glu Cys Gln Glu Thr 810 815 820	2503
40	gaa acg aag cca gcg cca gcc gaa gtc aag acg gtc ccc aat gac gcc Glu Thr Lys Pro Ala Pro Ala Glu Val Lys Thr Val Pro Asn Asp Ala 825 830 835	2551
	aca cag aca aag gag aac gag agc aaa gca tga tgggtgaaga gaaccgagca Thr Gln Thr Lys Glu Asn Glu Ser Lys Ala 840 845	2604
45	aagatcaaaa taaaaagtga cacagcagc	2633

<211> 848
 <212> PRT
 <213> Homo sapiens

5 <400> 8

Met	Leu	Gln	Thr	Lys	Asp	Leu	Ile	Trp	Thr	Leu	Phe	Phe	Leu	Gly	Thr
1				5					10					15	
10															
Ala	Val	Ser	Leu	Gln	Val	Asp	Ile	Val	Pro	Ser	Gln	Gly	Glu	Ile	Ser
			20					25					30		
15															
Val	Gly	Glu	Ser	Lys	Phe	Phe	Leu	Cys	Gln	Val	Ala	Gly	Asp	Ala	Lys
		35					40					45			
20															
Asp	Lys	Asp	Ile	Ser	Trp	Phe	Ser	Pro	Asn	Gly	Glu	Lys	Leu	Thr	Pro
	50					55					60				
25															
Asn	Gln	Gln	Arg	Ile	Ser	Val	Val	Trp	Asn	Asp	Asp	Ser	Ser	Ser	Thr
65				70					75						80
30															
Leu	Thr	Ile	Tyr	Asn	Ala	Asn	Ile	Asp	Asp	Ala	Gly	Ile	Tyr	Lys	Cys
				85				90						95	
35															
Val	Val	Thr	Gly	Glu	Asp	Gly	Ser	Glu	Ser	Glu	Ala	Thr	Val	Asn	Val
			100					105					110		
40															
Lys	Ile	Phe	Gln	Lys	Leu	Met	Phe	Lys	Asn	Ala	Pro	Thr	Pro	Gln	Glu
		115					120					125			
45															
Phe	Arg	Glu	Gly	Glu	Asp	Ala	Val	Ile	Val	Cys	Asp	Val	Val	Ser	Ser
	130					135					140				
50															
Leu	Pro	Pro	Thr	Ile	Ile	Trp	Lys	His	Lys	Gly	Arg	Asp	Val	Ile	Leu
145				150						155				160	
55															
Lys	Lys	Asp	Val	Arg	Phe	Ile	Val	Leu	Ser	Asn	Asn	Tyr	Leu	Gln	Ile
				165					170					175	

Arg Gly Ile Lys Lys Thr Asp Glu Gly Thr Tyr Arg Cys Glu Gly Arg
180 185 190

5

Ile Leu Ala Arg Gly Glu Ile Asn Phe Lys Asp Ile Gln Val Ile Val
195 200 205

10

Asn Val Pro Pro Thr Ile Arg Ala Arg Gln Asn Ile Val Asn Ala Thr
210 215 220

15

Ala Asn Leu Gly Gln Ser Val Thr Leu Val Cys Asp Ala Glu Arg Phe
225 230 235 240

20

Pro Glu Pro Thr Met Ser Trp Thr Lys Asp Gly Glu Gln Ile Glu Gln
245 250 255

25

Glu Glu Asp Asp Glu Lys Tyr Ile Phe Ser Asp Asp Ser Ser Gln Leu
260 265 270

30

Thr Ile Lys Lys Val Asp Lys Asn Asp Glu Ala Glu Tyr Ile Cys Ile
275 280 285

35

Ala Glu Asn Lys Ala Gly Glu Gln Asp Ala Thr Ile His Leu Lys Val
290 295 300

40

Phe Ala Lys Pro Lys Ile Thr Tyr Val Glu Asn Gln Thr Ala Met Glu
305 310 315 320

45

Leu Glu Glu Gln Val Thr Leu Thr Cys Glu Ala Ser Gly Asp Pro Ile
325 330 335

Pro Ser Ile Thr Trp Arg Thr Ser Thr Arg Asn Ile Ser Ser Glu Glu
340 345 350

Lys Thr Leu Asp Gly His Met Val Val Arg Ser His Ala Arg Val Ser
355 360 365

5 Ser Leu Thr Leu Lys Ser Ile Gln Tyr Thr Asp Ala Gly Glu Tyr Ile
370 375 380

10 Cys Thr Ala Ser Asn Thr Ile Gly Gln Asp Ser Gln Ser Met Tyr Leu
385 390 395 400

15 Glu Val Gln Tyr Ala Pro Lys Leu Gln Gly Pro Val Ala Val Tyr Thr
405 410 415

20 Trp Glu Gly Asn Gln Val Asn Ile Thr Cys Glu Val Phe Ala Tyr Pro
420 425 430

25 Ser Ala Thr Ile Ser Trp Phe Arg Asp Gly Gln Leu Leu Pro Ser Ser
435 440 445

30 Asn Tyr Ser Asn Ile Lys Ile Tyr Asn Thr Pro Ser Ala Ser Tyr Leu
450 455 460

35 Glu Val Thr Pro Asp Ser Glu Asn Asp Phe Gly Asn Tyr Asn Cys Thr
465 470 475 480

40 Ala Val Asn Arg Ile Gly Gln Glu Ser Phe Glu Phe Ile Leu Val Gln
485 490 495

45 Ala Asp Thr Pro Ser Ser Pro Ser Ile Asp Gln Val Glu Pro Tyr Ser
500 505 510

Ser Thr Ala Gln Val Gln Phe Asp Glu Pro Glu Ala Thr Gly Gly Val
515 520 525

Pro Ile Leu Lys Tyr Lys Ala Glu Trp Arg Ala Val Gly Glu Glu Val
530 535 540

Trp His Ser Lys Trp Tyr Asp Ala Lys Glu Ala Ser Met Glu Gly Ile
545 550 555 560

Val Thr Ile Val Gly Leu Lys Pro Glu Thr Thr Tyr Ala Val Arg Leu
565 570 575

5

Ala Ala Leu Asn Gly Lys Gly Leu Gly Glu Ile Ser Ala Ala Ser Glu
580 585 590

10

Phe Lys Thr Gln Pro Val Gln Gly Glu Pro Ser Ala Pro Lys Leu Glu
595 600 605

15

Gly Gln Met Gly Glu Asp Gly Asn Ser Ile Lys Val Asn Leu Ile Lys
610 615 620

20

Gln Asp Asp Gly Gly Ser Pro Ile Arg His Tyr Leu Val Arg Tyr Arg
625 630 635 640

25

Ala Leu Ser Ser Glu Trp Lys Pro Glu Ile Arg Leu Pro Ser Gly Ser
645 650 655

30

Asp His Val Met Leu Lys Ser Leu Asp Trp Asn Ala Glu Tyr Glu Val
660 665 670

35

Tyr Val Val Ala Glu Asn Gln Gln Gly Lys Ser Lys Ala Ala His Phe
675 680 685

40

Val Phe Arg Thr Ser Ala Gln Pro Thr Ala Ile Pro Ala Asn Gly Ser
690 695 700

45

Pro Thr Ser Gly Leu Ser Thr Gly Ala Ile Val Gly Ile Leu Ile Val
705 710 715 720

Ile Phe Val Leu Leu Leu Val Val Val Asp Ile Thr Cys Tyr Phe Leu
725 730 735

Asn Lys Cys Gly Leu Phe Met Cys Ile Ala Val Asn Leu Cys Gly Lys
740 745 750

Ala Gly Pro Gly Ala Lys Gly Lys Asp Met Glu Glu Gly Lys Ala Ala
755 760 765

5

Phe Ser Lys Asp Glu Ser Lys Glu Pro Ile Val Glu Val Arg Thr Glu
770 775 780

10

Glu Glu Arg Thr Pro Asn His Asp Gly Gly Lys His Thr Glu Pro Asn
785 790 795 800

15

Glu Thr Thr Pro Leu Thr Glu Pro Glu Lys Gly Pro Val Glu Ala Lys
805 810 815

20

Pro Glu Cys Gln Glu Thr Glu Thr Lys Pro Ala Pro Ala Glu Val Lys
820 825 830

25

Thr Val Pro Asn Asp Ala Thr Gln Thr Lys Glu Asn Glu Ser Lys Ala
835 840 845

30

<210> 9
<211> 1692
<212> DNA
<213> Homo sapiens;

35

<220>
<221> CDS
<222> (121)..(1080)
<223>

40

<300>
<308> X56677
<309> 1991-03-19
<313> (1)..(1692)

<400> 9
attcagactg ccagcacttt gctatctaca gccggggctc ccgagcggca gaaagttccg 60

45

gccactctct gccgcttggg ttgggcgaaa gccaggaccg tgccgcgccca ccgccaggat 120

atg gag cta ctg tcg cca ccg ctc cgc gac gta gac ctg acg gcc ccc 168
Met Glu Leu Leu Ser Pro Pro Leu Arg Asp Val Asp Leu Thr Ala Pro

1	5	10	15	
5	20	25	30	216
gac ggc tct ctc tgc tcc ttt gcc aca acg gac gac ttc tat gac gac Asp Gly Ser Leu Cys Ser Phe Ala Thr Thr Asp Asp Phe Tyr Asp Asp				
10	35	40	45	264
ccg tgt ttc gac tcc ccg gac ctg cgc ttc ttc gaa gac ctg gac ccg Pro Cys Phe Asp Ser Pro Asp Leu Arg Phe Phe Glu Asp Leu Asp Pro				
15	50	55	60	312
cgc ctg atg cac gtg ggc gcg ctc ctg aaa ccc gaa gag cac tcg cac Arg Leu Met His Val Gly Ala Leu Leu Lys Pro Glu Glu His Ser His				
20	65	70	75	360
ttc ccc gcg gcg gtg cac ccg gcc ccg ggc gca cgt gag gac gag cat Phe Pro Ala Ala Val His Pro Ala Pro Gly Ala Arg Glu Asp Glu His				
25	85	90	95	408
gtg cgc gcg ccc agc ggg cac cac cag gcg ggc cgc tgc cta ctg tgg Val Arg Ala Pro Ser Gly His His Gln Ala Gly Arg Cys Leu Leu Trp				
30	100	105	110	456
gcc tgc aag gcg tgc aag cgc aag acc acc aac gcc gac cgc cgc aag Ala Cys Lys Ala Cys Lys Arg Lys Thr Thr Asn Ala Asp Arg Arg Lys				
35	115	120	125	504
gcc gcc acc atg cgc gag cgg cgc cgc ctg agc aaa gta aat gag gcc Ala Ala Thr Met Arg Glu Arg Arg Arg Leu Ser Lys Val Asn Glu Ala				
40	130	135	140	552
ttt gag aca ctc aag cgc tgc acg tcg agc aat cca aac cag cgg ttg Phe Glu Thr Leu Lys Arg Cys Thr Ser Ser Asn Pro Asn Gln Arg Leu				
45	145	150	155	600
ccc aag gtg gag atc ctg cgc aac gcc atc cgc tat atc gag ggc ctg Pro Lys Val Glu Ile Leu Arg Asn Ala Ile Arg Tyr Ile Glu Gly Leu				
50	165	170	175	648
cag gct ctg ctg cgc gac cag gac gcc gcg ccc cct ggc gca gcc gcc Gln Ala Leu Leu Arg Asp Gln Asp Ala Ala Pro Pro Gly Ala Ala Ala				
55	180	185	190	696
ttc tat gcg ccg ggc ccg ctg ccc ccg ggc cgc ggc ggc gag cac tac Phe Tyr Ala Pro Gly Pro Leu Pro Pro Gly Arg Gly Gly Glu His Tyr				
60				744
agc ggc gac tcc gac gcg tcc agc ccg cgc tcc aac tgc tcc gac ggc Ser Gly Asp Ser Asp Ala Ser Ser Pro Arg Ser Asn Cys Ser Asp Gly				

	195	200	205	
	atg atg gac tac agc ggc ccc ccg agc ggc gcc cgg cgg cgg aac tgc			792
	Met Met Asp Tyr Ser Gly Pro Pro Ser Gly Ala Arg Arg Arg Asn Cys			
5	210	215	220	
	tac gaa ggc gcc tac tac aac gag gcg ccc agc gaa ccc agg ccc ggg			840
	Tyr Glu Gly Ala Tyr Tyr Asn Glu Ala Pro Ser Glu Pro Arg Pro Gly			
	225	230	235	240
10				
	aag agt gcg gcg gtg tgc agc cta gac tac ctg tcc agc atc gtg gag			888
	Lys Ser Ala Ala Val Ser Ser Leu Asp Tyr Leu Ser Ser Ile Val Glu			
	245	250	255	
15				
	cgc atc tcc acc gag agc cct gcg gcg ccc gcc ctg ctg gcg gac			936
	Arg Ile Ser Thr Glu Ser Pro Ala Ala Pro Ala Leu Leu Leu Ala Asp			
	260	265	270	
	gtg cct tct gag tgc cct ccg cgc agg caa gag gct gcc gcc ccc agc			984
20	Val Pro Ser Glu Ser Pro Pro Arg Arg Gln Glu Ala Ala Ala Pro Ser			
	275	280	285	
	gag gga gag agc agc ggc gac ccc acc cag tca ccg gac gcc gcc ccg			1032
	Glu Gly Glu Ser Ser Gly Asp Pro Thr Gln Ser Pro Asp Ala Ala Pro			
25	290	295	300	
	cag tgc cct gcg ggt gcg aac ccc aac ccg ata tac cag gtg ctg tga			1080
	Gln Cys Pro Ala Gly Ala Asn Pro Asn Pro Ile Tyr Gln Val Leu			
	305	310	315	
30				
	gggggatgtg gccgcccaac cccgccaggg atggtgccct aggggtccctc gcgccccaaa			1140
	gattgaactt aaatgcccc ctcccaacag cgctttaaaa gcgccatctc ttgaggtagg			1200
35				
	agaggcggag aactgaagtt tccgcccccc ccgacagggc aaggacacag cgcggttttt			1260
	tccacgcagc acccttctcg gagacccatt gcgatggcog ctccgtgttc ctcggtgggc			1320
	cagagctgaa ccttgagggg ctaggttcac gtttctcgcg ccctccatgg tgagaccctc			1380
40				
	gcagacctaa ccctgccccg ggatgcaccg gttatttggg ggggcgtgag acagtgcact			1440
	ccggtcccaa atgtagcagg tgtaaccgta accaccccc aaccgtttc ccggttcagg			1500
45				
	accacttttt gtaatacttt ttgtaatota ttctgtaaa taagagtctg tttgccagag			1560
	aggagccctt ggggctgtat ttatctctga ggcaggggtg gtggtgctac agggaatttg			1620

tacgtttata ccgcaggcgg gcgagccgcg ggcgctcgct caggtgatca aaataaaggc 1680

gctaatttat aa 1692

5

<210> 10

<211> 319

<212> PRT

<213> Homo sapiens;

10

<400> 10

Met Glu Leu Leu Ser Pro Pro Leu Arg Asp Val Asp Leu Thr Ala Pro
1 5 10 15

15

Asp Gly Ser Leu Cys Ser Phe Ala Thr Thr Asp Asp Phe Tyr Asp Asp
20 25 30

20

Pro Cys Phe Asp Ser Pro Asp Leu Arg Phe Phe Glu Asp Leu Asp Pro
35 40 45

25

Arg Leu Met His Val Gly Ala Leu Leu Lys Pro Glu Glu His Ser His
50 55 60

30

Phe Pro Ala Ala Val His Pro Ala Pro Gly Ala Arg Glu Asp Glu His
65 70 75 80

35

Val Arg Ala Pro Ser Gly His His Gln Ala Gly Arg Cys Leu Leu Trp
85 90 95

Ala Cys Lys Ala Cys Lys Arg Lys Thr Thr Asn Ala Asp Arg Arg Lys
100 105 110

40

Ala Ala Thr Met Arg Glu Arg Arg Arg Leu Ser Lys Val Asn Glu Ala
115 120 125

45

Phe Glu Thr Leu Lys Arg Cys Thr Ser Ser Asn Pro Asn Gln Arg Leu
130 135 140

Pro Lys Val Glu Ile Leu Arg Asn Ala Ile Arg Tyr Ile Glu Gly Leu
 145 150 155 160

5 Gln Ala Leu Leu Arg Asp Gln Asp Ala Ala Pro Pro Gly Ala Ala Ala
 165 170 175

10 Phe Tyr Ala Pro Gly Pro Leu Pro Pro Gly Arg Gly Gly Glu His Tyr
 180 185 190

15 Ser Gly Asp Ser Asp Ala Ser Ser Pro Arg Ser Asn Cys Ser Asp Gly
 195 200 205

Met Met Asp Tyr Ser Gly Pro Pro Ser Gly Ala Arg Arg Arg Asn Cys
 210 215 220

20 Tyr Glu Gly Ala Tyr Tyr Asn Glu Ala Pro Ser Glu Pro Arg Pro Gly
 225 230 235 240

25 Lys Ser Ala Ala Val Ser Ser Leu Asp Tyr Leu Ser Ser Ile Val Glu
 245 250 255

30 Arg Ile Ser Thr Glu Ser Pro Ala Ala Pro Ala Leu Leu Leu Ala Asp
 260 265 270

35 Val Pro Ser Glu Ser Pro Pro Arg Arg Gln Glu Ala Ala Ala Pro Ser
 275 280 285

40 Glu Gly Glu Ser Ser Gly Asp Pro Thr Gln Ser Pro Asp Ala Ala Pro
 290 295 300

45 Gln Cys Pro Ala Gly Ala Asn Pro Asn Pro Ile Tyr Gln Val Leu
 305 310 315

45 <210> 11
 <211> 1427
 <212> DNA
 <213> Homo sapiens;

	agc ctg cag gag ttg ctg aga gag cag gtg gag aac tac tat agc ctg	486
	Ser Leu Gln Glu Leu Leu Arg Glu Gln Val Glu Asn Tyr Tyr Ser Leu	
	135 140 145	
5	ccg gga cag agc tgc tcg gag ccc acc agc ccc acc tcc aac tgc tct	534
	Pro Gly Gln Ser Cys Ser Glu Pro Thr Ser Pro Thr Ser Asn Cys Ser	
	150 155 160	
10	gat ggc atg ccc gaa tgt aac agt cct gtc tgg tcc aga aag agc agt	582
	Asp Gly Met Pro Glu Cys Asn Ser Pro Val Trp Ser Arg Lys Ser Ser	
	165 170 175 180	
15	act ttt gac agc atc tac tgt cct gat gta tca aat gta tat gcc aca	630
	Thr Phe Asp Ser Ile Tyr Cys Pro Asp Val Ser Asn Val Tyr Ala Thr	
	185 190 195	
20	gat aaa aac tcc tta tcc agc ttg gat tgc tta tcc aac ata gtg gac	678
	Asp Lys Asn Ser Leu Ser Ser Leu Asp Cys Leu Ser Asn Ile Val Asp	
	200 205 210	
25	cgg atc acc tcc tca gag caa cct ggg ttg cct ctc cag gat ctg gct	726
	Arg Ile Thr Ser Ser Glu Gln Pro Gly Leu Pro Leu Gln Asp Leu Ala	
	215 220 225	
30	tct ctc tct cca gtt gcc agc acc gat tca cag cct cga act cca ggg	774
	Ser Leu Ser Pro Val Ala Ser Thr Asp Ser Gln Pro Arg Thr Pro Gly	
	230 235 240	
35	gct tct agt tcc agg ctt atc tat cat gtg cta tga actaattttc	820
	Ala Ser Ser Ser Arg Leu Ile Tyr His Val Leu	
	245 250 255	
40	tgggtctatat gaattcttcc aggagggcct aatacacagg acgaagaagg cttcaaaaag	880
45	tcccaaacca agacaacatg tacataaaga tttcttttca gttgtaaatt tgtaaagatt	940
	accttgccac ttataagaa agtgtattta actaaaaagt catcattgca aataatactt	1000
	tcttcttctt tattattctt tgcttagata ttaatacata gticcagtaa tactatttct	1060
	gatagggggc cattgattga gggtagcttg ttogaatgct taacttatat atacatatat	1120
	atatattata aatattgctc atcaaatgt ctctggtggt tagagcttta ttttttctt	1180
	taaaacatta aaacagctga gaatcagtta aatggaattt taaatatatt taactatttc	1240
	ttttctcttt aatccttttag ttatattgta ttaaataaaa atataatact gctaatgta	1300

tatattttga tcttttcttg taagaaatgt atctttttaa tgtaagcaca aaatagtact 1360

ttgtggatca tttcaagata taagaaattt tggaaattcc accataaata aaatttttta 1420

5 ctacaag 1427

<210> 12

<211> 255

10 <212> PRT

<213> Homo sapiens;

<400> 12

15 Met Asp Val Met Asp Gly Cys Gln Phe Ser Pro Ser Glu Tyr Phe Tyr
1 5 10 15

20 Asp Gly Ser Cys Ile Pro Ser Pro Glu Gly Glu Phe Gly Asp Glu Phe
20 25 30

25 Val Pro Arg Val Ala Ala Phe Gly Ala His Lys Ala Glu Leu Gln Gly
35 40 45

Ser Asp Glu Asp Glu His Val Arg Ala Pro Thr Gly His His Gln Ala
50 55 60

30 Gly His Cys Leu Met Trp Ala Cys Lys Ala Cys Lys Arg Lys Ser Thr
65 70 75 80

35 Thr Met Asp Arg Arg Lys Ala Ala Thr Met Arg Glu Arg Arg Arg Leu
85 90 95

40 Lys Lys Val Asn Gln Ala Phe Glu Thr Leu Lys Arg Cys Thr Thr Thr
100 105 110

45 Asn Pro Asn Gln Arg Leu Pro Lys Val Glu Ile Leu Arg Asn Ala Ile
115 120 125

Arg Tyr Ile Glu Ser Leu Gln Glu Leu Leu Arg Glu Gln Val Glu Asn
130 135 140

Tyr Tyr Ser Leu Pro Gly Gln Ser Cys Ser Glu Pro Thr Ser Pro Thr
 145 150 155 160
 5
 Ser Asn Cys Ser Asp Gly Met Pro Glu Cys Asn Ser Pro Val Trp Ser
 165 170 175
 10
 Arg Lys Ser Ser Thr Phe Asp Ser Ile Tyr Cys Pro Asp Val Ser Asn
 180 185 190
 15
 Val Tyr Ala Thr Asp Lys Asn Ser Leu Ser Ser Leu Asp Cys Leu Ser
 195 200 205
 20
 Asn Ile Val Asp Arg Ile Thr Ser Ser Glu Gln Pro Gly Leu Pro Leu
 210 215 220
 25
 Gln Asp Leu Ala Ser Leu Ser Pro Val Ala Ser Thr Asp Ser Gln Pro
 225 230 235 240
 30
 Arg Thr Pro Gly Ala Ser Ser Ser Arg Leu Ile Tyr His Val Leu
 245 250 255
 <210> 13
 <211> 675
 <212> DNA
 <213> Homo sapiens;
 35
 <220>
 <221> CDS
 <222> (1).. (675)
 <223>
 40
 <300>
 <308> BT007233
 <309> 2003-05-13
 <313> (1).. (675)
 45
 <400> 13
 atg gag ctg tat gag aca tcc ccc tac ttc tac cag gaa ccc cgc ttc
 Met Glu Leu Tyr Glu Thr Ser Pro Tyr Phe Tyr Gln Glu Pro Arg Phe

1	5	10	15	
				96
5	20	25	30	
				144
10	35	40	45	
				192
15	50	55	60	
				240
20	85	90	95	
				288
25	100	105	110	
				336
30	115	120	125	
				384
35	130	135	140	
				432
40	145	150	155	
				480
45	165	170	175	
				528
				576
				624

	195	200	205	
	aca gtg gaa gat gtg tct gtg gcc ttc cca gat gaa acc atg ccc aac			672
	Thr Val Glu Asp Val Ser Val Ala Phe Pro Asp Glu Thr Met Pro Asn			
5	210	215	220	
	tag			675
10	<210> 14			
	<211> 224			
	<212> PRT			
	<213> Homo sapiens;			
15	<400> 14			
	Met Glu Leu Tyr Glu Thr Ser Pro Tyr Phe Tyr Gln Glu Pro Arg Phe			
	1 5 10 15			
20	Tyr Asp Gly Glu Asn Tyr Leu Pro Val His Leu Gln Gly Phe Glu Pro			
	20 25 30			
25	Pro Gly Tyr Glu Arg Thr Glu Leu Thr Leu Ser Pro Glu Ala Pro Gly			
	35 40 45			
30	Pro Leu Glu Asp Lys Gly Leu Gly Thr Pro Glu His Cys Pro Gly Gln			
	50 55 60			
35	Cys Leu Pro Trp Ala Cys Lys Val Cys Lys Arg Lys Ser Val Ser Val			
	65 70 75 80			
40	Asp Arg Arg Arg Ala Ala Thr Leu Arg Glu Lys Arg Arg Leu Lys Lys			
	85 90 95			
45	Val Asn Glu Ala Phe Glu Ala Leu Lys Arg Ser Thr Leu Leu Asn Pro			
	100 105 110			
45	Asn Gln Arg Leu Pro Lys Val Glu Ile Leu Arg Ser Ala Ile Gln Tyr			
	115 120 125			

Ile Glu Arg Leu Gln Ala Leu Leu Ser Ser Leu Asn Gln Glu Glu Arg
 130 135 140

5 Asp Leu Arg Tyr Arg Gly Gly Gly Gly Pro Gln Pro Gly Val Pro Ser
 145 150 155 160

10 Glu Cys Ser Ser His Ser Ala Ser Cys Ser Pro Glu Trp Gly Ser Ala
 165 170 175

15 Leu Glu Phe Ser Ala Asn Pro Gly Asp His Leu Leu Thr Ala Asp Pro
 180 185 190

Thr Asp Ala His Asn Leu His Ser Leu Thr Ser Ile Val Asp Ser Ile
 195 200 205

20 Thr Val Glu Asp Val Ser Val Ala Phe Pro Asp Glu Thr Met Pro Asn
 210 215 220

25 <210> 15
 <211> 26
 <212> DNA
 <213> Artificial Sequence

30 <220>
 <223> SRY forward primer

35 <400> 15
 gcctcaggac atattaatct ctggag 26

40 <210> 16
 <211> 23
 <212> DNA
 <213> Artificial Sequence

<220>
 <223> SRY reverse primer

45 <400> 16
 gctgatctct gaattctgca tgc 23

<210> 17
<211> 26
<212> DNA
<213> Artificial Sequence
5
<220>
<223> SRY probe

<400> 17
10 aggcgcaagt tggctcaaca gaatcc 26

<210> 18
<211> 25
15 <212> DNA
<213> Artificial Sequence

<220>
<223> IL2 forward primer
20
<400> 18
gccttggtg ttataagtag gaggc 25

25 <210> 19
<211> 21
<212> DNA
<213> Artificial Sequence

30 <220>
<223> IL2 reverse primer

<400> 19
35 agtgccaatt cgatgatgag c 21

<210> 20
<211> 29
<212> DNA
40 <213> Artificial Sequence

<220>
<223> IL2 probe

45 <400> 20
tctcctcaga aattccacca cagttgctg 29

PCT REQUEST

Original (for SUBMISSION)

VIII-5-1	Declaration: Non-prejudicial disclosure or exceptions to lack of novelty Declaration as to non-prejudicial disclosures or exceptions to lack of novelty (Rules 4.17(v) and 51bis.1(a)(v)): Name (LAST, First)	in relation to this international application Cardio Incorporated declares that the subject matter claimed in this international application was disclosed as follows:
VIII-5-1(i)	Kind of disclosure:	other: Scientific Meeting
VIII-5-1(ii)	Date of disclosure:	28 March 2003 (28.03.2003)
VIII-5-1(iii)	Title of disclosure:	The 67th Annual Scientific Meeting of the Japanese Circulation Society
VIII-5-1(iv)	Place of disclosure:	Room 10
VIII-5-1(i)	Kind of disclosure:	other: The Website on the Internet
VIII-5-1(ii)	Date of disclosure:	28 March 2003 (28.03.2003)
VIII-5-1(iii)	Title of disclosure:	The 67th Annual Scientific Meeting of the Japanese Circulation Society
VIII-5-1(v)	This declaration is made for the purposes of:	all designations

International Application No
PCT/JP2004/001024

IPC 7 A61F2/00 A61L27/38 C12N5/06 A61K31/715

B. FIELDS SEARCHED

IPC 7 A61L C12N

EPO-Internal, BIOSIS, PAJ, WPI Data

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 6 432 711 B1 (DINSMORE JONATHAN H ET AL) 13 August 2002 (2002-08-13)	1,2,8, 10-17, 22,23
Y	abstract column 5, line 62 - column 6, line 25; examples 1-3 ----- -/--	18-21, 24-26

☒ Patent family members are listed in annex.

'&' document member of the same patent family

Mateo Rose11, A.M.

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	SHIMIZU TATSUYA ET AL: "Fabrication of pulsatile cardiac tissue grafts using a novel 3-dimensional cell sheet manipulation technique and temperature-responsive cell culture surfaces." CIRCULATION RESEARCH. 22 FEB 2002, vol. 90, no. 3, 22 February 2002 (2002-02-22), pages e40-E48, XP002285777 ISSN: 1524-4571 cited in the application the whole document	18-21, 24-26
Y	TERUO OKANO: "Cardiac tissue reconstruction based on cell sheet engineering" JAPANESE CIRCULATION SOCIETY, 'Online! 2002, pages 1-4, XP002285778 Retrieved from the Internet: URL:http://www.j-circ.or.jp/english/sessions/reports/66th-ss/okano.htm> 'retrieved on 2004-06-23! the whole document	18-21, 24,26
X	WO 01/07568 A (DIACRIN INC) 1 February 2001 (2001-02-01) page 2, lines 18-24 page 3, columns 15-24 page 33, line 14 - page 34, line 7	1,5,6, 9-17,22, 23
X	KELLAR ROBERT S ET AL: "Scaffold-based three-dimensional human fibroblast culture provides a structural matrix that supports angiogenesis in infarcted heart tissue" CIRCULATION, vol. 104, no. 17, 23 October 2001 (2001-10-23), pages 2063-2068, XP002285779 ISSN: 0009-7322 abstract page 2064, left-hand column, paragraph 2 - page 2065, right-hand column, paragraph 1	1,6,10, 16,17, 22,23
	----- -/--	

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	MIYAGAWA SHIGERU ET AL: "A tissue engineered contractile cardiac graft improves the cardiac performance in infarct rat heart" 23 October 2001 (2001-10-23), CIRCULATION, VOL. 104, NR. 17 SUPPLEMENT, PAGE(S) II.599 , SCIENTIFIC SESSIONS 2001 OF THE AMERICAN HEART ASSOCIATION; ANAHEIM, CALIFORNIA, USA; NOVEMBER 11-14, 2001 , XP008031972 ISSN: 0009-7322 abstract	1, 10-15, 17-24, 26
P, A	BACH A D ET AL: "Expression of Trisk 51, agrin and nicotinic-acetylcholine receptor epsilon-subunit during muscle development in a novel three-dimensional muscle-neuronal co-culture system." CELL & TISSUE RESEARCH, vol. 314, no. 2, November 2003 (2003-11), pages 263-274, XP002285780 ISSN: 0302-766X abstract page 265, left-hand column, paragraph 4 - right-hand column, paragraph 1 page 266, right-hand column, paragraph 1 page 269, right-hand column, paragraph 1 - page 270, left-hand column, paragraph 1	1, 4, 5, 9-16

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 6432711	B1	13-08-2002	US 2002187550 A1	12-12-2002
			CA 2174746 A1	11-05-1995
			EP 0725817 A1	14-08-1996
			WO 9512665 A1	11-05-1995
WO 0107568	A	01-02-2001	AU 770889 B2	04-03-2004
			AU 6234600 A	13-02-2001
			CA 2378643 A1	01-02-2001
			EP 1200559 A2	02-05-2002
			JP 2003505475 T	12-02-2003
			WO 0107568 A2	01-02-2001
			US 2003113301 A1	19-06-2003
			US 6673604 B1	06-01-2004

INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP2004/001024

Box No. I Nucleotide and/or amino acid sequence(s) (Continuation of item 1.b of the first sheet)

1. With regard to any nucleotide and/or amino acid sequence disclosed in the international application and necessary to the claimed invention, the international search was carried out on the basis of:
 - a. type of material
 - ☒ a sequence listing
 - ☐ table(s) related to the sequence listing
 - b. format of material
 - ☒ in written format
 - ☒ in computer readable form
 - c. time of filing/furnishing
 - ☒ contained in the international application as filed
 - ☐ filed together with the international application in computer readable form
 - ☐ furnished subsequently to this Authority for the purpose of search
2. ☐ In addition, in the case that more than one version or copy of a sequence listing and/or table relating thereto has been filed or furnished, the required statements that the information in the subsequent or additional copies is identical to that in the application as filed or does not go beyond the application as filed, as appropriate, were furnished.
3. Additional comments:

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.